

# PP-H 3000x1500x6 mm valkoinen

Artikelnr P2201502

Beständig Delvis beständig Ej beständig

| Kemikalie                             | Pitoisuus | Temp.  | Beständighet |
|---------------------------------------|-----------|--------|--------------|
| 1,4-Dioxane                           | 100       | 20 Å°C |              |
| 2-Hydroxypropionic acid (lactic acid) | 90        | 20 Å°C |              |
| Acetic acid                           | 100       | 20 Å°C |              |
| Acetone                               | 100       | 20 Å°C |              |
| Ammonia                               | â€        | 20 Å°C |              |
| Ammonium chloride                     | â€        | 20 Å°C |              |
| Amyl alcohol                          | â€        | 20 Å°C |              |
| Benzene                               | â€        | 20 Å°C |              |
| Bleaching solution                    | â€        | 20 Å°C |              |
| Boric acid                            | 100       | 20 Å°C |              |
| Brake fluid                           | â€        | 20 Å°C |              |
| Butyl acetate                         | â€        | 20 Å°C |              |
| Calcium chloride                      | â€        | 20 Å°C |              |
| Carbon disulphide                     | 100       | 20 Å°C |              |
| Carbon tetrachloride                  | â€        | 20 Å°C |              |
| Chlorine (gas)                        | 100       | 20 Å°C |              |
| Chlorobenzene                         | 100       | 20 Å°C |              |
| Chloroform                            | â€        | 20 Å°C |              |
| Citric acid                           | 10        | 20 Å°C |              |
| Cresol                                | â€        | 20 Å°C |              |
| Cyclohexanone                         | 100       | 20 Å°C |              |
| Cyclohexene                           | 100       | 20 Å°C |              |
| Diesel                                | â€        | 20 Å°C |              |
| Diethylene oxide                      | â€        | 20 Å°C |              |
| Ethyl acetate                         | 100       | 20 Å°C |              |
| Ethyl alcohol (ethanol)               | 96        | 20 Å°C |              |
| Ethylene chloride                     | 100       | 20 Å°C |              |

| Kemikalie                        | Pitoisuus   | Temp.  | Beständighet |
|----------------------------------|-------------|--------|--------------|
| Food oil                         | â€”         | 20 Å°C | ●            |
| Formaldehyde, aqueous            | 40          | 20 Å°C | ●            |
| Formic acid                      | 10          | 20 Å°C | ●            |
| Frost protection agent           | â€”         | 20 Å°C | ●            |
| Fuel oil                         | â€”         | 20 Å°C | ●            |
| Fuel, aromatic free              | â€”         | 20 Å°C | ●            |
| Glycerine                        | 100         | 20 Å°C | ●            |
| Glycol                           | 100         | 20 Å°C | ●            |
| Heptane                          | 100         | 20 Å°C | ●            |
| Hydrochloric acid                | 10          | 20 Å°C | ●            |
| Hydrochloric acid (concentrated) | â€”         | 20 Å°C | ●            |
| Hydrofluoric acid                | 40          | 20 Å°C | ●            |
| Hydrogen peroxide                | 10          | 20 Å°C | ●            |
| Hydrogen sulfide, aqueous        | â€”         | 20 Å°C | ●            |
| Isopropyl alcohol                | 100         | 20 Å°C | ●            |
| Linseed oil                      | â€”         | 20 Å°C | ●            |
| Mercurochrome                    | â€”         | 20 Å°C | ●            |
| Methyl alcohol (methanol)        | 100         | 20 Å°C | ●            |
| Methyl ethyl ketone (MEK)        | 100         | 20 Å°C | ●            |
| Methylene chloride               | 100         | 20 Å°C | ●            |
| Milk                             | â€”         | 20 Å°C | ●            |
| Mineral oils (aromatic free)     | â€”         | 20 Å°C | ●            |
| Nitric acid                      | 50          | 20 Å°C | ●            |
| Nitric acid                      | 10          | 20 Å°C | ●            |
| Nitrobenzene                     | â€”         | 20 Å°C | ●            |
| Oxalic acid                      | â€”         | 20 Å°C | ●            |
| Ozone (gas)                      | â‰‰ 0.5 ppm | 20 Å°C | ●            |
| Paraffin oil                     | 100         | 20 Å°C | ●            |
| Perchloroethylene                | â€”         | 20 Å°C | ●            |
| Petroleum ether                  | 100         | 20 Å°C | ●            |
| Phenol, aqueous                  | ca. 9       | 20 Å°C | ●            |
| Phosphoric acid                  | 50          | 20 Å°C | ●            |
| Potassium hydroxide solution     | 50          | 20 Å°C | ●            |
| Premium fuel                     | â€”         | 20 Å°C | ●            |
| Propyl alcohol                   | â€”         | 20 Å°C | ●            |

| Kemikalie                                | Pitoisuus | Temp.  | Beständighet |
|------------------------------------------|-----------|--------|--------------|
| Pyridine                                 | â€”       | 20 Å°C | ●            |
| Silicone oil                             | â€”       | 20 Å°C | ●            |
| Sodium carbonate, aqueous                | â€”       | 20 Å°C | ●            |
| Sodium chloride, aqueous                 | â€”       | 20 Å°C | ●            |
| Sodium hydrogen sulfite                  | â€”       | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 15        | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 60        | 20 Å°C | ●            |
| Sodium nitrate, aqueous                  | â€”       | 20 Å°C | ●            |
| Sodium thiosulfate                       | â€”       | 20 Å°C | ●            |
| Sulphuric acid                           | 96        | 20 Å°C | ●            |
| Tetrahydrofuran (THF)                    | 100       | 20 Å°C | ●            |
| Toluene                                  | 100       | 20 Å°C | ●            |
| Transformer oil                          | â€”       | 20 Å°C | ●            |
| Trichloroethylene                        | 100       | 20 Å°C | ●            |
| Vinegar, standard                        | 5 - 10    | 20 Å°C | ●            |
| Water                                    | â€”       | 20 Å°C | ●            |
| Xylene                                   | â€”       | 20 Å°C | ●            |