



# PVC U 2000x1000x1,5 mm valkoinen

Artikelnr P2201956

## 1. Tekniskt datablad

| Egenskap                                      | Värde               | Enhet               | Standard         |
|-----------------------------------------------|---------------------|---------------------|------------------|
| Tiheys                                        | 1.53                | g/cm <sup>3</sup>   | ASTM D792        |
| Venymisrajan jännitys                         | 48.8                | MPa                 | ASTM D638        |
| Joustavuusmoduli (vetolujuus)                 | 2669                | MPa                 | ASTM D638        |
| Murtolujuus                                   | 40                  | MPa                 | ISO 527          |
| Murtovenymä                                   | 14                  | %                   | ISO 527          |
| Sulamispiste                                  | 189.2               | °C                  | ASTM D3418       |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 93.3                | °C                  | UL 746B          |
| Maksimi käyttölämpötila                       | 60                  | °C                  |                  |
| Alin lämpötila                                | -15                 | °C                  | UL 746B          |
| Lämpötilaköyry (HDT/A)                        | 106.7               | °C                  | ASTM D648        |
| Vicat-pehmenemislämpötila (VST/B/50)          | 75                  | °C                  | ISO 306          |
| Dielektrinen voimakkuus                       | 40                  | kV/mm               | IEC 60243-1      |
| Tilavuusresistanssi                           | 10 <sup>-14</sup> µ | Ω·cm                | DIN EN 62631-3-1 |
| Dielektrinen vakio (1 MHz)                    | 3.1                 | -                   | IEC 60250        |
| Dielektrinen vakio (100 Hz)                   | 3.2                 | -                   | IEC 60250        |
| Dielektrinen hajoamiskerroin (1 MHz)          | 0.0                 | -                   | IEC 60250        |
| Taivutuslujuus                                | 73.1                | MPa                 | ASTM D790        |
| Lämpöjohtavuus                                | 0.14                | W/(m·K)             | ISO 22007-4      |
| Pintaresistanssi                              | 10 <sup>-14</sup> Ω | Ω                   | DIN EN 62631-3-2 |
| Vertailukemisindeksi (CTI)                    | 600                 | V                   | IEC 60112        |
| Imeytymisen maksimointi                       | 0.5                 | %                   | ASTM D570        |
| Vesihaku kyllästymiseen                       | 0.5                 | %                   | ASTM D570        |
| Särkykesto (Charpy)                           | 4                   | kJ/m <sup>2</sup>   | ISO 179          |
| Iskunkestävyys (Charpy)                       | 550                 | kJ/m <sup>2</sup>   | DIN EN ISO 8256  |
| Lämpölaajenemiskerroin                        | 1.03                | 10 <sup>-6</sup> /K | ASTM D696        |
| Kovuus Shore D                                | 85                  | ° Shore D           | ASTM D2240       |
| Kulmapaineen kovuus                           | 100                 | MPa                 | ISO 2039         |

| Egenskap | V rde | Enhet | Standard |
|----------|-------|-------|----------|
|----------|-------|-------|----------|

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

| Kemikalie                             | Konc.   | Resultat |
|---------------------------------------|---------|----------|
| 1,4-Dioxane                           | 100%    | ●        |
| 2-Hydroxypropionic acid (lactic acid) | 90%     | ●        |
| Acetic acid                           | 100%    | ●        |
| Acetone                               | 100%    | ●        |
| Ammonia                               | conc.   | ●        |
| Ammonium chloride                     |         | ●        |
| Amyl alcohol                          |         | ●        |
| Apple juice                           |         | ●        |
| Benzene                               |         | ●        |
| Bleaching solution                    | 12.5 cl | ●        |
| Boric acid                            | 100%    | ●        |
| Brake fluid                           |         | ●        |
| Butyl acetate                         |         | ●        |
| Calcium chloride                      |         | ●        |
| Carbon disulphide                     | 100%    | ●        |
| Carbon tetrachloride                  |         | ●        |
| Chlorine (gas)                        | 100%    |          |
| Chlorobenzene                         | 100%    | ●        |
| Chloroform                            |         | ●        |
| Citric acid                           | 10%     | ●        |
| Cresol                                |         | ●        |
| Cyclohexanone                         | 100%    | ●        |
| Cyclohexene                           | 100%    | ●        |
| Diesel                                |         | ●        |
| Diethylene oxide                      |         | ●        |
| Ethyl acetate                         | 100%    | ●        |
| Ethyl alcohol (ethanol)               | 96%     | ●        |
| Ethylene chloride                     | 100%    | ●        |
| Food oil                              |         | ●        |
| Formaldehyde (aqueous)                | 40%     | ●        |

| Kemikalie                        | Konc.       | Resultat |
|----------------------------------|-------------|----------|
| Formic acid                      | 10%         | ●        |
| Frost protection agent           | â€”         | ●        |
| Fuel (aromatic free)             | â€”         | ●        |
| Fuel oil                         | â€”         | ●        |
| Glycerine                        | 100%        | ●        |
| Glycol                           | 100%        | ●        |
| Heptane                          | 100%        | ●        |
| Hydrochloric acid                | 10%         | ●        |
| Hydrochloric acid (concentrated) | conc.       | ●        |
| Hydrofluoric acid                | 40%         | ●        |
| Hydrogen peroxide                | 10%         | ●        |
| Hydrogen sulfide (aqueous)       | â€”         | ●        |
| Isopropyl alcohol                | 100%        | ●        |
| Linseed oil                      | â€”         | ●        |
| Mercurochrome                    | â€”         | ●        |
| Methyl alcohol (methanol)        | 100%        | ●        |
| Methyl ethyl ketone (MEK)        | 100%        | ●        |
| Methylene chloride               | 100%        | ●        |
| Milk                             | â€”         | ●        |
| Mineral oils (aromatic free)     | â€”         | ●        |
| Nitric acid                      | 50%         | ●        |
| Nitric acid                      | 10%         | ●        |
| Nitrobenzene                     | â€”         | ●        |
| Oxalic acid                      | â€”         | ●        |
| Ozone (gas)                      | â‰¤ 0.5 ppm | ●        |
| Paraffin oil                     | 100%        | ●        |
| Perchloroethylene                | â€”         | ●        |
| Petroleum                        | 100%        | ●        |
| Petroleum ether                  | 100%        | ●        |
| Phenol (aqueous)                 | ca. 9%      | ●        |
| Phosphoric acid                  | 50%         | ●        |
| Potassium hydroxide solution     | 50%         | ●        |
| Premium fuel                     | â€”         | ●        |
| Propyl alcohol                   | â€”         | ●        |

| Kemikalie                                | Konc.   | Resultat |
|------------------------------------------|---------|----------|
| Pyridine                                 | â€”     | ●        |
| Silicone oil                             | â€”     | ●        |
| Sodium carbonate (aqueous)               | â€”     | ●        |
| Sodium chloride (aqueous)                | â€”     | ●        |
| Sodium hydrogen sulfite                  | â€”     | ●        |
| Sodium hydroxide solution (caustic soda) | 15%     | ●        |
| Sodium hydroxide solution (caustic soda) | 60%     | ●        |
| Sodium nitrate (aqueous)                 | â€”     | ●        |
| Sodium thiosulfate                       | â€”     | ●        |
| Sulphuric acid                           | 96%     | ●        |
| Tetrahydrofuran (THF)                    | 100%    | ●        |
| Toluene                                  | 100%    | ●        |
| Transformer oil                          | â€”     | ●        |
| Trichloroethylene                        | 100%    | ●        |
| Vinegar (standard)                       | 5 - 10% | ●        |
| Water                                    | â€”     | ●        |
| Xylene                                   | â€”     | ●        |