PLASTSHOP.SE

Kemisk beständighet

PlastShop.se - 2026-03-28

PVC U 2000x1000x6 mm vaalea harmaa UV

Artikelnr P1201188

Beständig Delvis beständig Ej beständig

Kemikalie	Pitoisuus	Temp.	Beständighet
1,4-Dioxane	100%	20 °C	Ej beständig
2-Hydroxypropionic acid (lactic acid)	90%	20 °C	Beständig
Acetic acid	100%	20 °C	Beständig
Acetone	100%	20 °C	Ej beständig
Ammonia	conc.	20 °C	Beständig
Ammonium chloride	-	20 °C	Beständig
Amyl alcohol	-	20 °C	Beständig
Apple juice	-	20 °C	Beständig
Benzene	-	20 °C	Ej beständig
Bleaching solution	12.5 cl	20 °C	Beständig
Boric acid	100%	20 °C	Beständig
Brake fluid	-	20 °C	Beständig
Butyl acetate	-	20 °C	Ej beständig
Calcium chloride	-	20 °C	Beständig
Carbon disulphide	100%	20 °C	Ej beständig
Carbon tetrachloride	-	20 °C	Ej beständig
Chlorine (gas)	100%	20 °C	Delvis beständig
Chlorobenzene	100%	20 °C	Ej beständig
Chloroform	-	20 °C	Ej beständig
Citric acid	10%	20 °C	Beständig
Cresol	-	20 °C	Ej beständig
Cyclohexanone	100%	20 °C	Ej beständig
Cyclohexene	100%	20 °C	Beständig
Diesel	-	20 °C	Beständig
Diethylene oxide	-	20 °C	Ej beständig
Ethyl acetate	100%	20 °C	Ej beständig

Kemikalie	Pitoisuus	Temp.	Beständighet
Ethyl alcohol (ethanol)	96%	20 °C	🟢
Ethylene chloride	100%	20 °C	🔴
Food oil	-	20 °C	🟢
Formaldehyde (aqueous)	40%	20 °C	🟢
Formic acid	10%	20 °C	🟢
Frost protection agent	-	20 °C	🟢
Fuel (aromatic free)	-	20 °C	🟢
Fuel oil	-	20 °C	🟢
Glycerine	100%	20 °C	🟢
Glycol	100%	20 °C	🟢
Heptane	100%	20 °C	🟢
Hydrochloric acid	10%	20 °C	🟢
Hydrochloric acid (concentrated)	conc.	20 °C	🟢
Hydrofluoric acid	40%	20 °C	🟢
Hydrogen peroxide	10%	20 °C	🟢
Hydrogen sulfide (aqueous)	-	20 °C	🟢
Isopropyl alcohol	100%	20 °C	🟢
Linseed oil	-	20 °C	🟢
Mercurochrome	-	20 °C	🟡
Methyl alcohol (methanol)	100%	20 °C	🟢
Methyl ethyl ketone (MEK)	100%	20 °C	🔴
Methylene chloride	100%	20 °C	🔴
Milk	-	20 °C	🟢
Mineral oils (aromatic free)	-	20 °C	🟢
Nitric acid	50%	20 °C	🟢
Nitric acid	10%	20 °C	🟢
Nitrobenzene	-	20 °C	🔴
Oxalic acid	-	20 °C	🟢
Ozone (gas)	≤ 0.5 ppm	20 °C	🟢
Paraffin oil	100%	20 °C	🟢
Perchloroethylene	-	20 °C	🔴
Petroleum	100%	20 °C	🟢
Petroleum ether	100%	20 °C	🟢
Phenol (aqueous)	ca. 9%	20 °C	🟡

Kemikalie	Pitoisuus	Temp.	Beständighet
Phosphoric acid	50%	20 °C	🟢
Potassium hydroxide solution	50%	20 °C	🟢
Premium fuel	-	20 °C	🔴
Propyl alcohol	-	20 °C	🟢
Pyridine	-	20 °C	🔴
Silicone oil	-	20 °C	🟢
Sodium carbonate (aqueous)	-	20 °C	🟢
Sodium chloride (aqueous)	-	20 °C	🟢
Sodium hydrogen sulfite	-	20 °C	🟢
Sodium hydroxide solution (caustic soda)	15%	20 °C	🟢
Sodium hydroxide solution (caustic soda)	60%	20 °C	🟢
Sodium nitrate (aqueous)	-	20 °C	🟢
Sodium thiosulfate	-	20 °C	🟢
Sulphuric acid	96%	20 °C	🟢
Tetrahydrofuran (THF)	100%	20 °C	🔴
Toluene	100%	20 °C	🔴
Transformer oil	-	20 °C	🟢
Trichloroethylene	100%	20 °C	🔴
Vinegar (standard)	5 - 10%	20 °C	🟢
Water	-	20 °C	🟢
Xylene	-	20 °C	🔴