



PA12 16x1000 mm luonnollinen

Artikelnr P1000287
Material PA

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	1.04	g/cm³	
Venymisrajan jännitys	66	MPa	ISO 527
Joustavuusmoduli (vetolujuus)	1470	MPa	ISO 527
Murtolujuus	45	MPa	ISO 527
Murtovenymä	50	%	ISO 527
Sulamispiste	180	°C	DIN EN ISO 11357
Maksimaalinen käyttölämpötila (lyhytaikainen)	133	°C	UL746B
Maksimi käyttölämpötila	110	°C	
Lämpökäyrä (HDT/A)	115	°C	ISO 75
Lämpökäyrä (HDT/B)	135	°C	ISO 75
Vicat-pehmenemislämpötila (VST/B/50)	50	°C	ISO 306
Dielektrinen voimakkuus	34	kV/mm	IEC 60243-1
Tilavuusresistanssi	10 ¹¹	Ω	IEC 60093
Dielektrinen vakio (1 MHz)	1	-	IEC 60250
Dielektrinen hajoamiskerroin (1 MHz)	1	-	IEC 60250
Paloaluokitus (UL 94)	60695		UL 94
Taivutuslujuus	53	MPa	DIN EN ISO 527-2
Pintaresistanssi	~10 ¹³	Ω	IEC 60093
Vertailukulkemisindeksi (CTI)	600	V	IEC 60112
Imeytymisen maksimointi	3	%	ISO 62
Vesihaku kyllästymiseen	3	%	ISO 62
Särkyäkesto (Charpy)	7	kJ/m²	DIN EN ISO 179-1
Lämpölaajenemiskerroin	0.9	10 ⁻⁴ /K	ISO 11359
Kovuus Shore D	83	° Shore D	ISO 868

Egenskap	Värde	Enhet	Standard
Kulmapaineen kovuus	90	MPa	ISO 2039

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic acid (lactic acid)	90	●
Acetone	100	●
Ammonia	conc.	●
Ammonium chloride	-	●
Amyl alcohol	-	●
Apple juice	-	●
Benzene	-	●
Bleaching solution	12.5 cl	●
Boric acid	100	●
Brake fluid	-	●
Butyl acetate	-	●
Calcium chloride	-	●
Carbon disulphide	100	●
Carbon tetrachloride	-	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	-	●
Citric acid	10	●
Cresol	-	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel	-	●
Diethylene oxide	-	●
Ethyl acetate	100	●
Ethyl alcohol (ethanol)	96	●
Ethylene chloride	100	●
Food oil	-	●
Formaldehyde (aqueous)	40	●
Formic acid	10	●

Kemikalie	Konc.	Resultat
Fuel (aromatic free)	-	●
Fuel oil	-	●
Glycerine	100	●
Glycol	100	●
Heptane	100	●
Hydrochloric acid	10	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40	●
Hydrogen peroxide	10	●
Hydrogen sulfide (aqueous)	-	●
Isopropyl alcohol	100	●
Linseed oil	-	●
Mercurochrome	-	●
Methyl alcohol (methanol)	100	●
Methyl ethyl ketone (MEK)	100	●
Methylene chloride	100	●
Milk	-	●
Mineral oils (aromatic free)	-	●
Nitric acid	50	●
Nitric acid	10	●
Nitrobenzene	-	●
Oxalic acid	-	●
Ozone (gas)	≤ 0.5 ppm	●
Paraffin oil	100	●
Perchloroethylene	-	●
Petroleum	100	●
Petroleum ether	100	●
Phenol (aqueous)	ca. 9	●
Phosphoric acid	50	●
Potassium hydroxide solution	50	●
Premium fuel	-	●
Propyl alcohol	-	●
Pyridine	-	●
Silicone oil	-	●

Kemikalie	Konc.	Resultat
Sodium carbonate (aqueous)	-	●
Sodium chloride (aqueous)	-	●
Sodium hydroxide solution (caustic soda)	15	●
Sodium nitrate (aqueous)	-	●
Sodium thiosulfate	-	●
Sulphuric acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer oil	-	●
Trichloroethylene	100	●
Vinegar (standard)	5 - 10	●
Water	-	●
Xylene	-	●