



PA12 GF30 40x1000 mm luonnollinen

Artikelnummer: P1000607

3. Kemiallinen kestävyys

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKAALI	BETYG	PITOIS.	LÄMPÖT.
1,4-Dioxane	partially_resistant	100%	
2-Hydroxypropionic acid (lactic acid)	not_resistant	90%	
Acetone	partially_resistant	100%	
Ammonia	resistant	conc.%	
Ammonium chloride	resistant		
Amyl alcohol	partially_resistant		
Apple juice	resistant		
Benzene	resistant		
Bleaching solution	not_resistant	12.5 cl%	
Boric acid	partially_resistant	100%	
Brake fluid	resistant		
Butyl acetate	resistant		
Calcium chloride	resistant		
Carbon disulphide	resistant	100%	
Carbon tetrachloride	resistant		
Chlorine (gas)	not_resistant	100%	
Chlorobenzene	partially_resistant	100%	
Chloroform	not_resistant		
Citric acid	resistant	10%	

KEMIKAALI	BETYG	PITOIS.	LÄMPÖT.
Cresol	not_resistant		
Cyclohexanone	resistant	100%	
Cyclohexene	partially_resistant	100%	
Diesel	resistant		
Diethylene oxide	resistant		
Ethyl acetate	resistant	100%	
Ethyl alcohol (ethanol)	partially_resistant	96%	
Ethylene chloride	not_resistant	100%	
Food oil	resistant		
Formaldehyde (aqueous)	partially_resistant	40%	
Formic acid	partially_resistant	10%	
Fuel (aromatic free)	resistant		
Fuel oil	resistant		
Glycerine	resistant	100%	
Glycol	resistant	100%	
Heptane	resistant	100%	
Hydrochloric acid	partially_resistant	10%	
Hydrochloric acid (concentrated)	not_resistant	conc.%	
Hydrofluoric acid	not_resistant	40%	
Hydrogen peroxide	not_resistant	10%	
Hydrogen sulfide (aqueous)	resistant		
Isopropyl alcohol	not_resistant	100%	
Linseed oil	resistant		
Mercurochrome	not_resistant		
Methyl alcohol (methanol)	not_resistant	100%	
Methyl ethyl ketone (MEK)	not_resistant	100%	
Methylene chloride	not_resistant	100%	
Milk	resistant		
Mineral oils (aromatic free)	resistant		
Nitric acid	not_resistant	50%	
Nitric acid	not_resistant	10%	

KEMIKAALI	BETYG	PITOIS.	LÄMPÖT.
Nitrobenzene	partially_resistant		
Oxalic acid	resistant		
Ozone (gas)	not_resistant	≤ 0.5 ppm%	
Paraffin oil	resistant	100%	
Perchloroethylene	resistant		
Petroleum	resistant	100%	
Petroleum ether	resistant	100%	
Phenol (aqueous)	not_resistant	ca. 9%	
Phosphoric acid	not_resistant	50%	
Potassium hydroxide solution	resistant	50%	
Premium fuel	resistant		
Propyl alcohol	not_resistant		
Pyridine	partially_resistant		
Silicone oil	resistant		
Sodium carbonate (aqueous)	resistant		
Sodium chloride (aqueous)	resistant		
Sodium hydroxide solution (caustic soda)	resistant	15%	
Sodium nitrate (aqueous)	resistant		
Sodium thiosulfate	resistant		
Sulphuric acid	not_resistant	96%	
Tetrahydrofuran (THF)	partially_resistant	100%	
Toluene	resistant	100%	
Transformer oil	resistant		
Trichloroethylene	partially_resistant	100%	
Vinegar (standard)	resistant	5 - 10%	
Water	resistant		
Xylene	resistant		