



# PA6.6 160x1000 mm luonnollinen

Artikelnr P1001969

## 1. Tekniskt datablad

| Egenskap                                      | Värde | Enhet     | Standard       |
|-----------------------------------------------|-------|-----------|----------------|
| Tiheys                                        | 1.14  | g/cm³     | ISO 1183       |
| Venymisrajan jännitys                         | 85    | MPa       | DIN EN ISO 527 |
| Joustavuusmoduli (vetolujuus)                 | 3100  | MPa       | ISO 527-2      |
| Murtovenymä                                   | 40    | %         | ISO 527-2      |
| Sulamispiste                                  | 260   | °C        | ISO 3146       |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 175   | °C        |                |
| Maksimi käyttölämpötila                       | 95    | °C        |                |
| Alin lämpötila                                | -30   | °C        |                |
| Lämpökestävyys (HDT/A)                        | 85    | °C        | ISO 75-2       |
| Dielektrinen voimakkuus                       | 27    | kV/mm     | IEC 60243-1    |
| Tilavuusresistanssi                           | 10⁻³  | g/cm³     | IEC 60093      |
| Dielektrinen vakio (1 MHz)                    | 3.55  | -         | IEC 60250      |
| Dielektrinen vakio (100 Hz)                   | 3.8   | -         | IEC 60250      |
| Dielektrinen hajaamiskerroin (1 MHz)          | 0.02  | -         | IEC 60250      |
| Dielektrinen hajaamiskerroin (100 Hz)         | 0.0   | -         | IEC 60250      |
| Taivutuslujuus                                | 998.3 | MPa       | ISO 178        |
| Lämpöjohtavuus                                | 0.28  | W/(m·K)   | DIN 52612      |
| Pintaresistanssi                              | 10⁻³  | Ω         | IEC 60093      |
| Vertailukulkemisindeksi (CTI)                 | 600   | V         | IEC 60112      |
| Imeytymisen maksimointi                       | 2.4   | %         | ISO 62         |
| Vesihaku kyllästymiseen                       | 8     | %         | ISO 62         |
| Särkyäkesto (Charpy)                          | 6     | kJ/m²     | ISO 179/1eA    |
| Iskunkestävyys (Charpy)                       | 50    | kJ/m²     | ISO 179        |
| Lämpölaajenemiskerroin                        | 0.8   | 10⁻⁵/K    | ISO 11359      |
| Kovuus Shore D                                | 83    | ° Shore D | DIN EN ISO 868 |
| Kulmapaineen kovuus                           | 174   | MPa       | ISO 2039-1     |

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

| Kemikalie               | Konc.   | Resultat       |
|-------------------------|---------|----------------|
| 1,4-Dioxane             | 100     | <span>●</span> |
| 2-Hydroxypropionic Acid | 90      | <span>●</span> |
| Acetic Acid             | 100     | <span>●</span> |
| Acetone                 | 100     | <span>●</span> |
| Ammonia                 | conc.   | <span>●</span> |
| Ammonium Chloride       | â€”     | <span>●</span> |
| Amyl Alcohol            | â€”     | <span>●</span> |
| Apple Juice             | â€”     | <span>●</span> |
| Benzene                 | â€”     | <span>●</span> |
| Bleaching Solution      | 12.5 cl | <span>●</span> |
| Boric Acid              | 100     | <span>●</span> |
| Brake Fluid             | â€”     | <span>●</span> |
| Butyl Acetate           | â€”     | <span>●</span> |
| Calcium Chloride        | â€”     | <span>●</span> |
| Carbon Disulfide        | 100     | <span>●</span> |
| Carbon Tetrachloride    | â€”     | <span>●</span> |
| Chlorine (gas)          | 100     | <span>●</span> |
| Chlorobenzene           | 100     | <span>●</span> |
| Chloroform              | â€”     | <span>●</span> |
| Citric Acid             | 10      | <span>●</span> |
| Cresol                  | â€”     | <span>●</span> |
| Cyclohexanone           | 100     | <span>●</span> |
| Cyclohexene             | 100     | <span>●</span> |
| Diesel Fuel             | â€”     | <span>●</span> |
| Diethylene Oxide        | â€”     | <span>●</span> |
| Ethyl Acetate           | 100     | <span>●</span> |
| Ethyl Alcohol           | 96      | <span>●</span> |
| Ethylene Chloride       | 100     | <span>●</span> |
| Food Oil                | â€”     | <span>●</span> |
| Formaldehyde (aqueous)  | 40      | <span>●</span> |
| Formic Acid             | 10      | <span>●</span> |
| Frost Protection Agent  | â€”     | <span>●</span> |

| Kemikalie                        | Konc.       | Resultat    |
|----------------------------------|-------------|-------------|
| Fuel (aromatic free)             | â€”         | <div></div> |
| Glycerine                        | 100         | <div></div> |
| Glycol                           | 100         | <div></div> |
| Heating Oil                      | â€”         | <div></div> |
| Heptane                          | 100         | <div></div> |
| Hydrochloric Acid                | 10          | <div></div> |
| Hydrochloric Acid (concentrated) | conc.       | <div></div> |
| Hydrofluoric Acid                | 40          | <div></div> |
| Hydrogen Peroxide                | 10          | <div></div> |
| Hydrogen Sulfide (aqueous)       | â€”         | <div></div> |
| Isopropyl Alcohol                | 100         | <div></div> |
| Linseed Oil                      | â€”         | <div></div> |
| Mercurochrome                    | â€”         | <div></div> |
| Methyl Alcohol                   | 100         | <div></div> |
| Methyl Ethyl Ketone (MEK)        | 100         | <div></div> |
| Methylene Chloride               | 100         | <div></div> |
| Milk                             | â€”         | <div></div> |
| Mineral Oils (aromatic free)     | â€”         | <div></div> |
| Nitric Acid                      | 10          | <div></div> |
| Nitric Acid                      | 50          | <div></div> |
| Nitrobenzene                     | â€”         | <div></div> |
| Oxalic Acid                      | â€”         | <div></div> |
| Ozone Gas                        | â‰‰ 0.5 ppm | <div></div> |
| Paraffine Oil                    | 100         | <div></div> |
| Perchloroethylene                | â€”         | <div></div> |
| Petroleum                        | 100         | <div></div> |
| Petroleum Ether                  | 100         | <div></div> |
| Phenol (aqueous)                 | ca. 9       | <div></div> |
| Phosphoric Acid                  | 50          | <div></div> |
| Potassium Hydroxide liquor       | 50          | <div></div> |
| Premium Fuel                     | â€”         | <div></div> |
| Propyl Alcohol                   | â€”         | <div></div> |
| Pyridine                         | â€”         | <div></div> |
| Silicone Oil                     | â€”         | <div></div> |
| Sodium Carbonate (aqueous)       | â€”         | <div></div> |

| Kemikalie                 | Konc.  | Resultat |
|---------------------------|--------|----------|
| Sodium Chloride (aqueous) | â€”    | ●        |
| Sodium Hydrogen Sulfite   | â€”    | ●        |
| Sodium Hydroxide liquor   | 60     | ●        |
| Sodium Hydroxide liquor   | 15     | ●        |
| Sodium Nitrate (aqueous)  | â€”    | ●        |
| Sodium Thiosulfate        | â€”    | ●        |
| Sulfuric Acid             | 96     | ●        |
| Tetrahydrofuran (THF)     | 100    | ●        |
| Toluene                   | 100    | ●        |
| Transformer Oil           | â€”    | ●        |
| Trichloroethylene         | 100    | ●        |
| Vinegar (standard)        | 5 - 10 | ●        |
| Water                     | â€”    | ●        |
| Xylene                    | â€”    | ●        |