



PA6.6 70x1000 mm musta

Artikelnr P1001868  
Material PA

1. Tekniskt datablad

| Egenskap                                      | Värde            | Enhet               | Standard       |
|-----------------------------------------------|------------------|---------------------|----------------|
| Tiheys                                        | 1.14             | g/cm³               | ISO 1183       |
| Venymisrajan jännitys                         | 85               | MPa                 | DIN EN ISO 527 |
| Joustavuusmoduli (vetolujuus)                 | 3100             | MPa                 | ISO 527-2      |
| Murtovenymä                                   | 40               | %                   | ISO 527-2      |
| Sulamispiste                                  | 260              | °C                  | ISO 3146       |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 175              | °C                  |                |
| Maksimi käyttölämpötila                       | 95               | °C                  |                |
| Alin lämpötila                                | -30              | °C                  |                |
| Lämpökäyrä (HDT/A)                            | 85               | °C                  | ISO 75-2       |
| Dielektrinen voimakkuus                       | 27               | kV/mm               | IEC 60243-1    |
| Tilavuusresistanssi                           | 10 <sup>14</sup> | Ω·cm                | IEC 60093      |
| Dielektrinen vakio (1 MHz)                    | 3.55             | -                   | IEC 60250      |
| Dielektrinen vakio (100 Hz)                   | 3.8              | -                   | IEC 60250      |
| Dielektrinen hajoamiskerroin (1 MHz)          | 0.02             | -                   | IEC 60250      |
| Dielektrinen hajoamiskerroin (100 Hz)         | 0.0              | -                   | IEC 60250      |
| Taivutuslujuus                                | 998.3            | MPa                 | ISO 178        |
| Lämmönjohtavuus                               | 0.28             | W/(m·K)             | DIN 52612      |
| Pintaresistanssi                              | 10 <sup>13</sup> | Ω                   | IEC 60093      |
| Vertailukulkemisindeksi (CTI)                 | 600              | V                   | IEC 60112      |
| Imeytymisen maksimointi                       | 2.4              | %                   | ISO 62         |
| Vesihaku kyllästymiseen                       | 8                | %                   | ISO 62         |
| Särkyäkesto (Charpy)                          | 6                | kJ/m²               | ISO 179/1eA    |
| Iskunkestävyys (Charpy)                       | 50               | kJ/m²               | ISO 179        |
| Lämpölaajenemiskerroin                        | 0.8              | 10 <sup>-4</sup> /K | ISO 11359      |
| Kovuus Shore D                                | 83               | ° Shore D           | DIN EN ISO 868 |

| Egenskap            | Värde | Enhet | Standard   |
|---------------------|-------|-------|------------|
| Kulmapaineen kovuus | 174   | MPa   | ISO 2039-1 |

2. Kemisk beständighet

● Beständig   ● Delvis beständig   ● Ej beständig

| Kemikalie               | Konc.   | Resultat       |
|-------------------------|---------|----------------|
| 1,4-Dioxane             | 100     | <span>●</span> |
| 2-Hydroxypropionic Acid | 90      | <span>●</span> |
| Acetic Acid             | 100     | <span>●</span> |
| Acetone                 | 100     | <span>●</span> |
| Ammonia                 | conc.   | <span>●</span> |
| Ammonium Chloride       | -       | <span>●</span> |
| Amyl Alcohol            | -       | <span>●</span> |
| Apple Juice             | -       | <span>●</span> |
| Benzene                 | -       | <span>●</span> |
| Bleaching Solution      | 12.5 cl | <span>●</span> |
| Boric Acid              | 100     | <span>●</span> |
| Brake Fluid             | -       | <span>●</span> |
| Butyl Acetate           | -       | <span>●</span> |
| Calcium Chloride        | -       | <span>●</span> |
| Carbon Disulfide        | 100     | <span>●</span> |
| Carbon Tetrachloride    | -       | <span>●</span> |
| Chlorine (gas)          | 100     | <span>●</span> |
| Chlorobenzene           | 100     | <span>●</span> |
| Chloroform              | -       | <span>●</span> |
| Citric Acid             | 10      | <span>●</span> |
| Cresol                  | -       | <span>●</span> |
| Cyclohexanone           | 100     | <span>●</span> |
| Cyclohexene             | 100     | <span>●</span> |
| Diesel Fuel             | -       | <span>●</span> |
| Diethylene Oxide        | -       | <span>●</span> |
| Ethyl Acetate           | 100     | <span>●</span> |
| Ethyl Alcohol           | 96      | <span>●</span> |
| Ethylene Chloride       | 100     | <span>●</span> |
| Food Oil                | -       | <span>●</span> |

| Kemikalie                        | Konc.     | Resultat    |
|----------------------------------|-----------|-------------|
| Formaldehyde (aqueous)           | 40        | <div></div> |
| Formic Acid                      | 10        | <div></div> |
| Frost Protection Agent           | -         | <div></div> |
| Fuel (aromatic free)             | -         | <div></div> |
| Glycerine                        | 100       | <div></div> |
| Glycol                           | 100       | <div></div> |
| Heating Oil                      | -         | <div></div> |
| Heptane                          | 100       | <div></div> |
| Hydrochloric Acid                | 10        | <div></div> |
| Hydrochloric Acid (concentrated) | conc.     | <div></div> |
| Hydrofluoric Acid                | 40        | <div></div> |
| Hydrogen Peroxide                | 10        | <div></div> |
| Hydrogen Sulfide (aqueous)       | -         | <div></div> |
| Isopropyl Alcohol                | 100       | <div></div> |
| Linseed Oil                      | -         | <div></div> |
| Mercurochrome                    | -         | <div></div> |
| Methyl Alcohol                   | 100       | <div></div> |
| Methyl Ethyl Ketone (MEK)        | 100       | <div></div> |
| Methylene Chloride               | 100       | <div></div> |
| Milk                             | -         | <div></div> |
| Mineral Oils (aromatic free)     | -         | <div></div> |
| Nitric Acid                      | 10        | <div></div> |
| Nitric Acid                      | 50        | <div></div> |
| Nitrobenzene                     | -         | <div></div> |
| Oxalic Acid                      | -         | <div></div> |
| Ozone Gas                        | ≤ 0.5 ppm | <div></div> |
| Paraffine Oil                    | 100       | <div></div> |
| Perchloroethylene                | -         | <div></div> |
| Petroleum                        | 100       | <div></div> |
| Petroleum Ether                  | 100       | <div></div> |
| Phenol (aqueous)                 | ca. 9     | <div></div> |
| Phosphoric Acid                  | 50        | <div></div> |
| Potassium Hydroxide liquor       | 50        | <div></div> |
| Premium Fuel                     | -         | <div></div> |
| Propyl Alcohol                   | -         | <div></div> |

| Kemikalie                  | Konc.  | Resultat    |
|----------------------------|--------|-------------|
| Pyridine                   | -      | <div></div> |
| Silicone Oil               | -      | <div></div> |
| Sodium Carbonate (aqueous) | -      | <div></div> |
| Sodium Chloride (aqueous)  | -      | <div></div> |
| Sodium Hydrogen Sulfite    | -      | <div></div> |
| Sodium Hydroxide liquor    | 60     | <div></div> |
| Sodium Hydroxide liquor    | 15     | <div></div> |
| Sodium Nitrate (aqueous)   | -      | <div></div> |
| Sodium Thiosulfate         | -      | <div></div> |
| Sulfuric Acid              | 96     | <div></div> |
| Tetrahydrofuran (THF)      | 100    | <div></div> |
| Toluene                    | 100    | <div></div> |
| Transformer Oil            | -      | <div></div> |
| Trichloroethylene          | 100    | <div></div> |
| Vinegar (standard)         | 5 - 10 | <div></div> |
| Water                      | -      | <div></div> |
| Xylene                     | -      | <div></div> |