



PA6.6 90x3000 mm musta

Artikelnr P1001914
Material PA

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	1.14	g/cm³	ISO 1183
Venymisrajan jännitys	85	MPa	DIN EN ISO 527
Joustavuusmoduli (vetolujuus)	3100	MPa	ISO 527-2
Murtovenymä	40	%	ISO 527-2
Sulamispiste	260	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	175	°C	
Maksimi käyttölämpötila	95	°C	
Alin lämpötila	-30	°C	
Lämpökäyrä (HDT/A)	85	°C	ISO 75-2
Dielektrinen voimakkuus	27	kV/mm	IEC 60243-1
Tilavuusresistanssi	10 ¹⁴	Ω·cm	IEC 60093
Dielektrinen vakio (1 MHz)	3.55	-	IEC 60250
Dielektrinen vakio (100 Hz)	3.8	-	IEC 60250
Dielektrinen hajoamiskerroin (1 MHz)	0.02	-	IEC 60250
Dielektrinen hajoamiskerroin (100 Hz)	0.0	-	IEC 60250
Taivutuslujuus	998.3	MPa	ISO 178
Lämmönjohtavuus	0.28	W/(m·K)	DIN 52612
Pintaresistanssi	10 ¹³	Ω	IEC 60093
Vertailukulkemisindeksi (CTI)	600	V	IEC 60112
Imeytymisen maksimointi	2.4	%	ISO 62
Vesihaku kyllästymiseen	8	%	ISO 62
Särkyäkesto (Charpy)	6	kJ/m²	ISO 179/1eA
Iskunkestävyys (Charpy)	50	kJ/m²	ISO 179
Lämpölaajenemiskerroin	0.8	10 ⁻⁴ /K	ISO 11359
Kovuus Shore D	83	° Shore D	DIN EN ISO 868

Egenskap	Värde	Enhet	Standard
Kulmapaineen kovuus	174	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonium Chloride	-	●
Amyl Alcohol	-	●
Apple Juice	-	●
Benzene	-	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	-	●
Butyl Acetate	-	●
Calcium Chloride	-	●
Carbon Disulfide	100	●
Carbon Tetrachloride	-	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	-	●
Citric Acid	10	●
Cresol	-	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel Fuel	-	●
Diethylene Oxide	-	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Food Oil	-	●

Kemikalie	Konc.	Resultat
Formaldehyde (aqueous)	40	●
Formic Acid	10	●
Frost Protection Agent	-	●
Fuel (aromatic free)	-	●
Glycerine	100	●
Glycol	100	●
Heating Oil	-	●
Heptane	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	-	●
Isopropyl Alcohol	100	●
Linseed Oil	-	●
Mercurochrome	-	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Milk	-	●
Mineral Oils (aromatic free)	-	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobenzene	-	●
Oxalic Acid	-	●
Ozone Gas	≤ 0.5 ppm	●
Paraffine Oil	100	●
Perchloroethylene	-	●
Petroleum	100	●
Petroleum Ether	100	●
Phenol (aqueous)	ca. 9	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	-	●
Propyl Alcohol	-	●

Kemikalie	Konc.	Resultat
Pyridine	-	
Silicone Oil	-	
Sodium Carbonate (aqueous)	-	
Sodium Chloride (aqueous)	-	
Sodium Hydrogen Sulfite	-	
Sodium Hydroxide liquor	60	
Sodium Hydroxide liquor	15	
Sodium Nitrate (aqueous)	-	
Sodium Thiosulfate	-	
Sulfuric Acid	96	
Tetrahydrofuran (THF)	100	
Toluene	100	
Transformer Oil	-	
Trichloroethylene	100	
Vinegar (standard)	5 - 10	
Water	-	
Xylene	-	