



PE-500 140x2000 mm luonnollinen

Artikelnr P2200629

Beständig Delvis beständig Ej beständig

Kemikalie	Pitoisuus	Temp.	Beständighet
1,4-Dioxane	100%	20 Å°C	Beständig
2-Hydroxypropionic Acid	90%	20 Å°C	Beständig
Acetaldehyde	â€	20 Å°C	Beständig
Acetic Acid	100%	20 Å°C	Beständig
Acetic acid	100%	20 Å°C	Beständig
Acetic acid	3%	100 Å°C	Beständig
Acetic acid	3% w/w	20 Å°C	Beständig
Acetic acid	3%	100 Å°C	Beständig
Acetic acid	3%	100 Å°C	Beständig
Acetic acid, aqueous	70%	20 Å°C	Beständig
Acetic anhydride	â€	20 Å°C	Beständig
Acetone	â€	20 Å°C	Beständig
Acetone	100%	20 Å°C	Beständig
Acronal dispersions	â€	20 Å°C	Beständig
Acrylonitrile	â€	20 Å°C	Beständig
Allyl acetate	â€	20 Å°C	Beständig
Allyl alcohol	96%	20 Å°C	Beständig
Allyl chloride	â€	20 Å°C	Beständig
Aluminium chloride, aqueous	any	20 Å°C	Beständig
Aluminium chloride, solid	â€	20 Å°C	Beständig
Aluminium fluoride	Conc.	20 Å°C	Beständig
Aluminium hydroxide	â€	20 Å°C	Beständig
Aluminium metaphosphate	â€	20 Å°C	Beständig
Aluminium sulphate, aqueous saturated	â€	20 Å°C	Beständig
Aluminium sulphate, solid	â€	20 Å°C	Beständig
Ammonia	concentrated	20 Å°C	Beständig
Ammonia, gaseous	â€	20 Å°C	Beständig

Kemikalie	Pitoisuus	Temp.	BestÄndighet
Ammonia, liquid	â€™	20 Å°C	●
Ammonium Chloride	â€™	20 Å°C	●
Amyl Alcohol	â€™	20 Å°C	●
Aniline	any	20 Å°C	●
Anisole	â€™	20 Å°C	●
Apple Juice	â€™	20 Å°C	●
Aqua regia	â€™	20 Å°C	●
Beer	â€™	20 Å°C	●
Benzaldehyde, aqueous	any	20 Å°C	●
Benzene	technically grade	20 Å°C	●
Benzene	â€™	20 Å°C	●
Benzoic acid, aqueous	any	20 Å°C	●
Benzyl alcohol	â€™	20 Å°C	●
Bitumen	â€™	20 Å°C	●
Bleaching Solution	12.5 cl	20 Å°C	●
Boric Acid	100%	20 Å°C	●
Brake Fluid	â€™	20 Å°C	●
Bromine, liquid	100%	20 Å°C	●
Butanol, aqueous	any	20 Å°C	●
Butter	â€™	20 Å°C	●
Butyl Acetate	â€™	20 Å°C	●
Calcium Chloride	â€™	20 Å°C	●
Calcium carbonate	â€™	20 Å°C	●
Calcium carbonate	â€™	20 Å°C	●
Calcium hypochlorite, aqueous suspension	any	20 Å°C	●
Camphor	â€™	20 Å°C	●
Carbon Disulfide	100%	20 Å°C	●
Carbon Tetrachloride	â€™	20 Å°C	●
Carbon disulphide	â€™	20 Å°C	●
Caustic soda	any	20 Å°C	●
Chlorine (gas)	100%	20 Å°C	●
Chlorine, liquid	â€™	20 Å°C	●
Chloroacetic acid, aqueous	â%□85%	20 Å°C	●
Chlorobenzene	â€™	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	BestÄndighet
Chlorobenzene	100%	20 Å°C	●
Chloroform	â€”	20 Å°C	●
Chloroform	technically grade	20 Å°C	●
Chromosulphuric acid	â€”	20 Å°C	●
Cider	â€”	20 Å°C	●
Citric Acid	10%	20 Å°C	●
Citrus fruit juices	â€”	20 Å°C	●
Coconut oil	â€”	20 Å°C	●
Cod liver oil	â€”	20 Å°C	●
Cresol	100%	20 Å°C	●
Cresol	â€”	20 Å°C	●
Cyclohexane	â€”	20 Å°C	●
Cyclohexanol	â€”	20 Å°C	●
Cyclohexanone	100%	20 Å°C	●
Cyclohexanone	â€”	20 Å°C	●
Cyclohexene	100%	20 Å°C	●
Detergents	â€”	20 Å°C	●
Dibutyl ether	â€”	20 Å°C	●
Dibutyl phthalate	â€”	20 Å°C	●
Dichloroacetic acid	â€”	20 Å°C	●
Dichloroethane	â€”	20 Å°C	●
Diesel Fuel	â€”	20 Å°C	●
Diesel fuel	â€”	20 Å°C	●
Diethylene Oxide	â€”	20 Å°C	●
Diglycolic acid, aqueous	30%	20 Å°C	●
Dimethyl formamide	â€”	20 Å°C	●
Dimethylamine	â€”	20 Å°C	●
Dioxane	â€”	20 Å°C	●
Ethanol	10%	100 Å°C	●
Ethanol	10%	100 Å°C	●
Ethanol	10% v/v	20 Å°C	●
Ethanol	10%	100 Å°C	●
Ethyl Acetate	100%	20 Å°C	●
Ethyl Alcohol	96%	20 Å°C	●
Ethyl acetate	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Ethylene Chloride	100%	20 Å°C	●
Ethylene alcohol	96%	20 Å°C	●
Ethylene chloride	â€”	20 Å°C	●
Ethylene diamine	â€”	20 Å°C	●
Ethylene glycol	â€”	20 Å°C	●
Ferric chloride, aqueous	any	20 Å°C	●
Ferric nitrate, aqueous saturated	â€”	20 Å°C	●
Ferric sulphate, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) chloride, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) sulfate, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) chloride, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) nitrate, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) sulfate, aqueous saturated	â€”	20 Å°C	●
Food Oil	â€”	20 Å°C	●
Formaldehyde (aqueous)	40%	20 Å°C	●
Formaldehyde, aqueous	â‰ƒ40%	20 Å°C	●
Formic Acid	10%	20 Å°C	●
Formic acid, aqueous	85%	20 Å°C	●
Frigen 12 (Freon 12)	100%	20 Å°C	●
Frost Protection Agent	â€”	20 Å°C	●
Fruit juices	any	20 Å°C	●
Fuel (aromatic free)	â€”	20 Å°C	●
Fuel oil	â€”	20 Å°C	●
Furfural	â€”	20 Å°C	●
Glycerin, aqueous	any	20 Å°C	●
Glycerine	100%	20 Å°C	●
Glycol	100%	20 Å°C	●
Glykol, aqueous	as supplied	20 Å°C	●
Glysantin	â€”	20 Å°C	●
Heating Oil	â€”	20 Å°C	●
Heptane	100%	20 Å°C	●
Heptane	â€”	20 Å°C	●
Hexane	â€”	20 Å°C	●
Honey	â€”	20 Å°C	●
Hydrobromic acid, aqueous	50%	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Hydrochloric Acid	10%	20 Å°C	●
Hydrochloric Acid (concentrated)	concentrated	20 Å°C	●
Hydrochloric acid, aqueous	any	20 Å°C	●
Hydrofluoric Acid	40%	20 Å°C	●
Hydrogen Peroxide	10%	20 Å°C	●
Hydrogen Sulfide (aqueous solution)	â€”	20 Å°C	●
Ink	â€”	20 Å°C	●
Iodine in potassium iodide solution	3% iodine	20 Å°C	●
Isooctane	â€”	20 Å°C	●
Isopropanol	â€”	20 Å°C	●
Isopropyl Alcohol	100%	20 Å°C	●
Isopropyl ether	â€”	20 Å°C	●
Jam	â€”	20 Å°C	●
Kerosene	â€”	20 Å°C	●
Linseed Oil	â€”	20 Å°C	●
Linseed oil	technically grade	20 Å°C	●
Lithium bromide	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Maleic acid, aqueous	any	20 Å°C	●
Menthol	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Mercury	â€”	20 Å°C	●
Methanol	technically grade	20 Å°C	●
Methyl Alcohol	100%	20 Å°C	●
Methyl Ethyl Ketone (MEK)	100%	20 Å°C	●
Methyl chloride	gaseous, technically grade	20 Å°C	●
Methyl ethyl ketone	technically grade	20 Å°C	●
Methylene Chloride	100%	20 Å°C	●
Milk	â€”	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral Oil (aromatic free)	â€”	20 Å°C	●
Molasses	â€”	20 Å°C	●
Motor oil (heavy duty oil) without additives	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Naphtha	â€”	20 Å°C	●
Naphthalene	â€”	20 Å°C	●
Nitric Acid	10%	20 Å°C	●
Nitric Acid (50%)	50%	20 Å°C	●
Nitric acid, aqueous	50%	20 Å°C	●
Nitric acid, aqueous	25%	20 Å°C	●
Nitrobenzene	â€”	20 Å°C	●
Nitrobenzene	â€”	20 Å°C	●
Oils, ethereal	â€”	20 Å°C	●
Oils, vegetable and animal	â€”	20 Å°C	●
Oleic acid	â€”	20 Å°C	●
Oleum	any	20 Å°C	●
Olive oil	â€”	20 Å°C	●
Olive oil	â€”	100 Å°C	●
Olive oil	â€”	100 Å°C	●
Olive oil	â€”	100 Å°C	●
Oxalic Acid	â€”	20 Å°C	●
Oxalic acid, aqueous	any	20 Å°C	●
Oxygen	â€”	20 Å°C	●
Ozone	50 ppm	20 Å°C	●
Ozone Gas	â‰‰0.5 ppm	20 Å°C	●
Paraffine Oil	100%	20 Å°C	●
Perchloric acid, aqueous	70%	20 Å°C	●
Perchloric acid, aqueous	50%	20 Å°C	●
Perchloric acid, aqueous	20%	20 Å°C	●
Perchloroethylene	â€”	20 Å°C	●
Petroleum	â€”	20 Å°C	●
Petroleum	100%	20 Å°C	●
Petroleum Ether	100%	20 Å°C	●
Petroleum ether	â€”	20 Å°C	●
Phenol	â€”	20 Å°C	●
Phenol (aqueous)	â‰‰9%	20 Å°C	●
Phosphoric Acid	50%	20 Å°C	●
Phosphoric acid, aqueous	80% L 95%	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	BestÄndighet
Phosphoric acid, aqueous	50%	20 Å°C	●
Phosphorus trichloride	â€”	20 Å°C	●
Photographic developers	â€”	20 Å°C	●
Photographic emulsions	as supplied	20 Å°C	●
Photographic fixing baths	as supplied	20 Å°C	●
Phthalic acid, aqueous	50%	20 Å°C	●
Polyester resins	â€”	20 Å°C	●
Potassium Hydroxide liquor	50%	20 Å°C	●
Premium Fuel	â€”	20 Å°C	●
Propionic acid, aqueous	any	20 Å°C	●
Propyl Alcohol	â€”	20 Å°C	●
Pyridine	â€”	20 Å°C	●
Pyridine	â€”	20 Å°C	●
Sea water	â€”	20 Å°C	●
Silicon dioxide	â€”	20 Å°C	●
Silicon dioxide	â€”	20 Å°C	●
Silicone Oil	â€”	20 Å°C	●
Silicone oil	technically grade	20 Å°C	●
Sodium Carbonate (aqueous)	â€”	20 Å°C	●
Sodium Chloride (aqueous)	â€”	20 Å°C	●
Sodium Hydrogen Sulfite	â€”	20 Å°C	●
Sodium Hydroxide liquor	15%	20 Å°C	●
Sodium Hydroxide liquor (60%)	60%	20 Å°C	●
Sodium Nitrate (aqueous)	â€”	20 Å°C	●
Sodium Thiosulfate	â€”	20 Å°C	●
Sodium borate	â€”	20 Å°C	●
Sodium bromide	â€”	20 Å°C	●
Sodium hydroxide, aqueous	any	20 Å°C	●
Sodium hydroxide, solid	â€”	20 Å°C	●
Stearic acid	â€”	20 Å°C	●
Sugar syrup	â€”	20 Å°C	●
Sulfuric Acid	96%	20 Å°C	●
Sulphuric acid, aqueous	70%	20 Å°C	●
Sulphuric acid, aqueous	â‰¥50%	20 Å°C	●
Sulphuric acid, aqueous	80%	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Sulphuric acid, aqueous	98%	20 Å°C	●
Tallow	technically grade	20 Å°C	●
Tannic acid (tannin), aqueous	10%	20 Å°C	●
Tetrahydrofuran	technically grade	20 Å°C	●
Tetrahydrofuran (THF)	100%	20 Å°C	●
Thionyl chloride	â€”	20 Å°C	●
Thiophene	â€”	20 Å°C	●
Tin (II) chloride, aqueous	any	20 Å°C	●
Tin (IV) chloride, aqueous	saturated	20 Å°C	●
Titanium dioxide	â€”	20 Å°C	●
Titanium dioxide	â€”	20 Å°C	●
Toluene	100%	20 Å°C	●
Toluene	technically grade	20 Å°C	●
Transformer Oil	â€”	20 Å°C	●
Transformer oil (insulating oil)	technically grade	20 Å°C	●
Trichloroacetic acid	technically grade	20 Å°C	●
Trichloroethylene	technically grade	20 Å°C	●
Trichloroethylene	100%	20 Å°C	●
Triethanolamine	â€”	20 Å°C	●
Triethanolamine	â€”	20 Å°C	●
Turpentine oil	technically grade	20 Å°C	●
Urea, aqueous	â‰ƒ33%	20 Å°C	●
Vaseline	technically grade	20 Å°C	●
Vinegar (standard)	5-10%	20 Å°C	●
Washing up liquids	usual	20 Å°C	●
Water	â€”	20 Å°C	●
Water, distilled	â€”	20 Å°C	●
Wine	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●
Zinc sludge	â€”	20 Å°C	●