



# PE-500 350x1000 mm luonnollinen

Artikelnr P2200654

Beständig Delvis beständig Ej beständig

| Kemikalie                             | Pitoisuus    | Temp.   | Beständighet |
|---------------------------------------|--------------|---------|--------------|
| 1,4-Dioxane                           | 100%         | 20 Å°C  | Beständig    |
| 2-Hydroxypropionic Acid               | 90%          | 20 Å°C  | Beständig    |
| Acetaldehyde                          | â€”          | 20 Å°C  | Beständig    |
| Acetic Acid                           | 100%         | 20 Å°C  | Beständig    |
| Acetic acid                           | 3%           | 100 Å°C | Beständig    |
| Acetic acid                           | 3% w/w       | 20 Å°C  | Beständig    |
| Acetic acid                           | 100%         | 20 Å°C  | Beständig    |
| Acetic acid                           | 3%           | 100 Å°C | Beständig    |
| Acetic acid                           | 3%           | 100 Å°C | Beständig    |
| Acetic acid, aqueous                  | 70%          | 20 Å°C  | Beständig    |
| Acetic anhydride                      | â€”          | 20 Å°C  | Beständig    |
| Acetone                               | â€”          | 20 Å°C  | Beständig    |
| Acetone                               | 100%         | 20 Å°C  | Beständig    |
| Acronal dispersions                   | â€”          | 20 Å°C  | Beständig    |
| Acrylonitrile                         | â€”          | 20 Å°C  | Beständig    |
| Allyl acetate                         | â€”          | 20 Å°C  | Beständig    |
| Allyl alcohol                         | 96%          | 20 Å°C  | Beständig    |
| Allyl chloride                        | â€”          | 20 Å°C  | Beständig    |
| Aluminium chloride, aqueous           | any          | 20 Å°C  | Beständig    |
| Aluminium chloride, solid             | â€”          | 20 Å°C  | Beständig    |
| Aluminium fluoride                    | Conc.        | 20 Å°C  | Beständig    |
| Aluminium hydroxide                   | â€”          | 20 Å°C  | Beständig    |
| Aluminium metaphosphate               | â€”          | 20 Å°C  | Beständig    |
| Aluminium sulphate, aqueous saturated | â€”          | 20 Å°C  | Beständig    |
| Aluminium sulphate, solid             | â€”          | 20 Å°C  | Beständig    |
| Ammonia                               | concentrated | 20 Å°C  | Beständig    |
| Ammonia, gaseous                      | â€”          | 20 Å°C  | Beständig    |

| Kemikalie                                | Pitoisuus         | Temp.  | BestÄndighet |
|------------------------------------------|-------------------|--------|--------------|
| Ammonia, liquid                          | â€”               | 20 Å°C | ●            |
| Ammonium Chloride                        | â€”               | 20 Å°C | ●            |
| Amyl Alcohol                             | â€”               | 20 Å°C | ●            |
| Aniline                                  | any               | 20 Å°C | ●            |
| Anisole                                  | â€”               | 20 Å°C | ●            |
| Apple Juice                              | â€”               | 20 Å°C | ●            |
| Aqua regia                               | â€”               | 20 Å°C | ●            |
| Beer                                     | â€”               | 20 Å°C | ●            |
| Benzaldehyde, aqueous                    | any               | 20 Å°C | ●            |
| Benzene                                  | â€”               | 20 Å°C | ●            |
| Benzene                                  | technically grade | 20 Å°C | ●            |
| Benzoic acid, aqueous                    | any               | 20 Å°C | ●            |
| Benzyl alcohol                           | â€”               | 20 Å°C | ●            |
| Bitumen                                  | â€”               | 20 Å°C | ●            |
| Bleaching Solution                       | 12.5 cl           | 20 Å°C | ●            |
| Boric Acid                               | 100%              | 20 Å°C | ●            |
| Brake Fluid                              | â€”               | 20 Å°C | ●            |
| Bromine, liquid                          | 100%              | 20 Å°C | ●            |
| Butanol, aqueous                         | any               | 20 Å°C | ●            |
| Butter                                   | â€”               | 20 Å°C | ●            |
| Butyl Acetate                            | â€”               | 20 Å°C | ●            |
| Calcium Chloride                         | â€”               | 20 Å°C | ●            |
| Calcium carbonate                        | â€”               | 20 Å°C | ●            |
| Calcium carbonate                        | â€”               | 20 Å°C | ●            |
| Calcium hypochlorite, aqueous suspension | any               | 20 Å°C | ●            |
| Camphor                                  | â€”               | 20 Å°C | ●            |
| Carbon Disulfide                         | 100%              | 20 Å°C | ●            |
| Carbon Tetrachloride                     | â€”               | 20 Å°C | ●            |
| Carbon disulphide                        | â€”               | 20 Å°C | ●            |
| Caustic soda                             | any               | 20 Å°C | ●            |
| Chlorine (gas)                           | 100%              | 20 Å°C | ●            |
| Chlorine, liquid                         | â€”               | 20 Å°C | ●            |
| Chloroacetic acid, aqueous               | â‰¥85%            | 20 Å°C | ●            |
| Chlorobenzene                            | â€”               | 20 Å°C | ●            |

| Kemikalie                | Pitoisuus         | Temp.   | BestÄndighet |
|--------------------------|-------------------|---------|--------------|
| Chlorobenzene            | 100%              | 20 Å°C  | ●            |
| Chloroform               | technically grade | 20 Å°C  | ●            |
| Chloroform               | â€”               | 20 Å°C  | ●            |
| Chromosulphuric acid     | â€”               | 20 Å°C  | ●            |
| Cider                    | â€”               | 20 Å°C  | ●            |
| Citric Acid              | 10%               | 20 Å°C  | ●            |
| Citrus fruit juices      | â€”               | 20 Å°C  | ●            |
| Coconut oil              | â€”               | 20 Å°C  | ●            |
| Cod liver oil            | â€”               | 20 Å°C  | ●            |
| Cresol                   | â€”               | 20 Å°C  | ●            |
| Cresol                   | 100%              | 20 Å°C  | ●            |
| Cyclohexane              | â€”               | 20 Å°C  | ●            |
| Cyclohexanol             | â€”               | 20 Å°C  | ●            |
| Cyclohexanone            | â€”               | 20 Å°C  | ●            |
| Cyclohexanone            | 100%              | 20 Å°C  | ●            |
| Cyclohexene              | 100%              | 20 Å°C  | ●            |
| Detergents               | â€”               | 20 Å°C  | ●            |
| Dibutyl ether            | â€”               | 20 Å°C  | ●            |
| Dibutyl phthalate        | â€”               | 20 Å°C  | ●            |
| Dichloroacetic acid      | â€”               | 20 Å°C  | ●            |
| Dichloroethane           | â€”               | 20 Å°C  | ●            |
| Diesel Fuel              | â€”               | 20 Å°C  | ●            |
| Diesel fuel              | â€”               | 20 Å°C  | ●            |
| Diethylene Oxide         | â€”               | 20 Å°C  | ●            |
| Diglycolic acid, aqueous | 30%               | 20 Å°C  | ●            |
| Dimethyl formamide       | â€”               | 20 Å°C  | ●            |
| Dimethylamine            | â€”               | 20 Å°C  | ●            |
| Dioxane                  | â€”               | 20 Å°C  | ●            |
| Ethanol                  | 10%               | 100 Å°C | ●            |
| Ethanol                  | 10% v/v           | 20 Å°C  | ●            |
| Ethanol                  | 10%               | 100 Å°C | ●            |
| Ethanol                  | 10%               | 100 Å°C | ●            |
| Ethyl Acetate            | 100%              | 20 Å°C  | ●            |
| Ethyl Alcohol            | 96%               | 20 Å°C  | ●            |
| Ethyl acetate            | â€”               | 20 Å°C  | ●            |

| Kemikalie                                 | Pitoisuus   | Temp.  | Beständighet |
|-------------------------------------------|-------------|--------|--------------|
| Ethylene Chloride                         | 100%        | 20 Å°C | ●            |
| Ethylene alcohol                          | 96%         | 20 Å°C | ●            |
| Ethylene chloride                         | â€”         | 20 Å°C | ●            |
| Ethylene diamine                          | â€”         | 20 Å°C | ●            |
| Ethylene glycol                           | â€”         | 20 Å°C | ●            |
| Ferric chloride, aqueous                  | any         | 20 Å°C | ●            |
| Ferric nitrate, aqueous saturated         | â€”         | 20 Å°C | ●            |
| Ferric sulphate, aqueous saturated        | â€”         | 20 Å°C | ●            |
| Ferrous (II) chloride, aqueous saturated  | â€”         | 20 Å°C | ●            |
| Ferrous (II) sulfate, aqueous saturated   | â€”         | 20 Å°C | ●            |
| Ferrous (III) chloride, aqueous saturated | â€”         | 20 Å°C | ●            |
| Ferrous (III) nitrate, aqueous saturated  | â€”         | 20 Å°C | ●            |
| Ferrous (III) sulfate, aqueous saturated  | â€”         | 20 Å°C | ●            |
| Food Oil                                  | â€”         | 20 Å°C | ●            |
| Formaldehyde (aqueous)                    | 40%         | 20 Å°C | ●            |
| Formaldehyde, aqueous                     | â‰ƒ40%      | 20 Å°C | ●            |
| Formic Acid                               | 10%         | 20 Å°C | ●            |
| Formic acid, aqueous                      | 85%         | 20 Å°C | ●            |
| Frigen 12 (Freon 12)                      | 100%        | 20 Å°C | ●            |
| Frost Protection Agent                    | â€”         | 20 Å°C | ●            |
| Fruit juices                              | any         | 20 Å°C | ●            |
| Fuel (aromatic free)                      | â€”         | 20 Å°C | ●            |
| Fuel oil                                  | â€”         | 20 Å°C | ●            |
| Furfural                                  | â€”         | 20 Å°C | ●            |
| Glycerin, aqueous                         | any         | 20 Å°C | ●            |
| Glycerine                                 | 100%        | 20 Å°C | ●            |
| Glycol                                    | 100%        | 20 Å°C | ●            |
| Glykol, aqueous                           | as supplied | 20 Å°C | ●            |
| Glysantin                                 | â€”         | 20 Å°C | ●            |
| Heating Oil                               | â€”         | 20 Å°C | ●            |
| Heptane                                   | 100%        | 20 Å°C | ●            |
| Heptane                                   | â€”         | 20 Å°C | ●            |
| Hexane                                    | â€”         | 20 Å°C | ●            |
| Honey                                     | â€”         | 20 Å°C | ●            |
| Hydrobromic acid, aqueous                 | 50%         | 20 Å°C | ●            |

| Kemikalie                                    | Pitoisuus                  | Temp.  | Beständighet |
|----------------------------------------------|----------------------------|--------|--------------|
| Hydrochloric Acid                            | 10%                        | 20 Å°C | ●            |
| Hydrochloric Acid (concentrated)             | concentrated               | 20 Å°C | ●            |
| Hydrochloric acid, aqueous                   | any                        | 20 Å°C | ●            |
| Hydrofluoric Acid                            | 40%                        | 20 Å°C | ●            |
| Hydrogen Peroxide                            | 10%                        | 20 Å°C | ●            |
| Hydrogen Sulfide (aqueous solution)          | â€”                        | 20 Å°C | ●            |
| Ink                                          | â€”                        | 20 Å°C | ●            |
| Iodine in potassium iodide solution          | 3% iodine                  | 20 Å°C | ●            |
| Isooctane                                    | â€”                        | 20 Å°C | ●            |
| Isopropanol                                  | â€”                        | 20 Å°C | ●            |
| Isopropyl Alcohol                            | 100%                       | 20 Å°C | ●            |
| Isopropyl ether                              | â€”                        | 20 Å°C | ●            |
| Jam                                          | â€”                        | 20 Å°C | ●            |
| Kerosene                                     | â€”                        | 20 Å°C | ●            |
| Linseed Oil                                  | â€”                        | 20 Å°C | ●            |
| Linseed oil                                  | technically grade          | 20 Å°C | ●            |
| Lithium bromide                              | â€”                        | 20 Å°C | ●            |
| Magnesium stearate                           | â€”                        | 20 Å°C | ●            |
| Magnesium stearate                           | â€”                        | 20 Å°C | ●            |
| Maleic acid, aqueous                         | any                        | 20 Å°C | ●            |
| Menthol                                      | â€”                        | 20 Å°C | ●            |
| Mercurochrome                                | â€”                        | 20 Å°C | ●            |
| Mercury                                      | â€”                        | 20 Å°C | ●            |
| Methanol                                     | technically grade          | 20 Å°C | ●            |
| Methyl Alcohol                               | 100%                       | 20 Å°C | ●            |
| Methyl Ethyl Ketone (MEK)                    | 100%                       | 20 Å°C | ●            |
| Methyl chloride                              | gaseous, technically grade | 20 Å°C | ●            |
| Methyl ethyl ketone                          | technically grade          | 20 Å°C | ●            |
| Methylene Chloride                           | 100%                       | 20 Å°C | ●            |
| Milk                                         | â€”                        | 20 Å°C | ●            |
| Milk                                         | â€”                        | 20 Å°C | ●            |
| Mineral Oil (aromatic free)                  | â€”                        | 20 Å°C | ●            |
| Molasses                                     | â€”                        | 20 Å°C | ●            |
| Motor oil (heavy duty oil) without additives | â€”                        | 20 Å°C | ●            |

| Kemikalie                  | Pitoisuus  | Temp.   | Beständighet |
|----------------------------|------------|---------|--------------|
| Naphtha                    | â€”        | 20 Å°C  | ●            |
| Naphthalene                | â€”        | 20 Å°C  | ●            |
| Nitric Acid                | 10%        | 20 Å°C  | ●            |
| Nitric Acid (50%)          | 50%        | 20 Å°C  | ●            |
| Nitric acid, aqueous       | 50%        | 20 Å°C  | ●            |
| Nitric acid, aqueous       | 25%        | 20 Å°C  | ●            |
| Nitrobenzene               | â€”        | 20 Å°C  | ●            |
| Nitrobenzene               | â€”        | 20 Å°C  | ●            |
| Oils, ethereal             | â€”        | 20 Å°C  | ●            |
| Oils, vegetable and animal | â€”        | 20 Å°C  | ●            |
| Oleic acid                 | â€”        | 20 Å°C  | ●            |
| Oleum                      | any        | 20 Å°C  | ●            |
| Olive oil                  | â€”        | 20 Å°C  | ●            |
| Olive oil                  | â€”        | 100 Å°C | ●            |
| Olive oil                  | â€”        | 100 Å°C | ●            |
| Olive oil                  | â€”        | 100 Å°C | ●            |
| Oxalic Acid                | â€”        | 20 Å°C  | ●            |
| Oxalic acid, aqueous       | any        | 20 Å°C  | ●            |
| Oxygen                     | â€”        | 20 Å°C  | ●            |
| Ozone                      | 50 ppm     | 20 Å°C  | ●            |
| Ozone Gas                  | â‰‰0.5 ppm | 20 Å°C  | ●            |
| Paraffine Oil              | 100%       | 20 Å°C  | ●            |
| Perchloric acid, aqueous   | 20%        | 20 Å°C  | ●            |
| Perchloric acid, aqueous   | 50%        | 20 Å°C  | ●            |
| Perchloric acid, aqueous   | 70%        | 20 Å°C  | ●            |
| Perchloroethylene          | â€”        | 20 Å°C  | ●            |
| Petroleum                  | 100%       | 20 Å°C  | ●            |
| Petroleum                  | â€”        | 20 Å°C  | ●            |
| Petroleum Ether            | 100%       | 20 Å°C  | ●            |
| Petroleum ether            | â€”        | 20 Å°C  | ●            |
| Phenol                     | â€”        | 20 Å°C  | ●            |
| Phenol (aqueous)           | â‰‰9%      | 20 Å°C  | ●            |
| Phosphoric Acid            | 50%        | 20 Å°C  | ●            |
| Phosphoric acid, aqueous   | 80% L 95%  | 20 Å°C  | ●            |

| Kemikalie                     | Pitoisuus         | Temp.  | Beständighet |
|-------------------------------|-------------------|--------|--------------|
| Phosphoric acid, aqueous      | 50%               | 20 Å°C | ●            |
| Phosphorus trichloride        | â€”               | 20 Å°C | ●            |
| Photographic developers       | â€”               | 20 Å°C | ●            |
| Photographic emulsions        | as supplied       | 20 Å°C | ●            |
| Photographic fixing baths     | as supplied       | 20 Å°C | ●            |
| Phthalic acid, aqueous        | 50%               | 20 Å°C | ●            |
| Polyester resins              | â€”               | 20 Å°C | ●            |
| Potassium Hydroxide liquor    | 50%               | 20 Å°C | ●            |
| Premium Fuel                  | â€”               | 20 Å°C | ●            |
| Propionic acid, aqueous       | any               | 20 Å°C | ●            |
| Propyl Alcohol                | â€”               | 20 Å°C | ●            |
| Pyridine                      | â€”               | 20 Å°C | ●            |
| Pyridine                      | â€”               | 20 Å°C | ●            |
| Sea water                     | â€”               | 20 Å°C | ●            |
| Silicon dioxide               | â€”               | 20 Å°C | ●            |
| Silicon dioxide               | â€”               | 20 Å°C | ●            |
| Silicone Oil                  | â€”               | 20 Å°C | ●            |
| Silicone oil                  | technically grade | 20 Å°C | ●            |
| Sodium Carbonate (aqueous)    | â€”               | 20 Å°C | ●            |
| Sodium Chloride (aqueous)     | â€”               | 20 Å°C | ●            |
| Sodium Hydrogen Sulfite       | â€”               | 20 Å°C | ●            |
| Sodium Hydroxide liquor       | 15%               | 20 Å°C | ●            |
| Sodium Hydroxide liquor (60%) | 60%               | 20 Å°C | ●            |
| Sodium Nitrate (aqueous)      | â€”               | 20 Å°C | ●            |
| Sodium Thiosulfate            | â€”               | 20 Å°C | ●            |
| Sodium borate                 | â€”               | 20 Å°C | ●            |
| Sodium bromide                | â€”               | 20 Å°C | ●            |
| Sodium hydroxide, aqueous     | any               | 20 Å°C | ●            |
| Sodium hydroxide, solid       | â€”               | 20 Å°C | ●            |
| Stearic acid                  | â€”               | 20 Å°C | ●            |
| Sugar syrup                   | â€”               | 20 Å°C | ●            |
| Sulfuric Acid                 | 96%               | 20 Å°C | ●            |
| Sulphuric acid, aqueous       | â‰ƒ50%            | 20 Å°C | ●            |
| Sulphuric acid, aqueous       | 70%               | 20 Å°C | ●            |
| Sulphuric acid, aqueous       | 80%               | 20 Å°C | ●            |

| Kemikalie                        | Pitoisuus         | Temp.  | Beständighet |
|----------------------------------|-------------------|--------|--------------|
| Sulphuric acid, aqueous          | 98%               | 20 Å°C | ●            |
| Tallow                           | technically grade | 20 Å°C | ●            |
| Tannic acid (tannin), aqueous    | 10%               | 20 Å°C | ●            |
| Tetrahydrofuran                  | technically grade | 20 Å°C | ●            |
| Tetrahydrofuran (THF)            | 100%              | 20 Å°C | ●            |
| Thionyl chloride                 | â€”               | 20 Å°C | ●            |
| Thiophene                        | â€”               | 20 Å°C | ●            |
| Tin (II) chloride, aqueous       | any               | 20 Å°C | ●            |
| Tin (IV) chloride, aqueous       | saturated         | 20 Å°C | ●            |
| Titanium dioxide                 | â€”               | 20 Å°C | ●            |
| Titanium dioxide                 | â€”               | 20 Å°C | ●            |
| Toluene                          | technically grade | 20 Å°C | ●            |
| Toluene                          | 100%              | 20 Å°C | ●            |
| Transformer Oil                  | â€”               | 20 Å°C | ●            |
| Transformer oil (insulating oil) | technically grade | 20 Å°C | ●            |
| Trichloroacetic acid             | technically grade | 20 Å°C | ●            |
| Trichloroethylene                | technically grade | 20 Å°C | ●            |
| Trichloroethylene                | 100%              | 20 Å°C | ●            |
| Triethanolamine                  | â€”               | 20 Å°C | ●            |
| Triethanolamine                  | â€”               | 20 Å°C | ●            |
| Turpentine oil                   | technically grade | 20 Å°C | ●            |
| Urea, aqueous                    | â‰ƒ33%            | 20 Å°C | ●            |
| Vaseline                         | technically grade | 20 Å°C | ●            |
| Vinegar (standard)               | 5-10%             | 20 Å°C | ●            |
| Washing up liquids               | usual             | 20 Å°C | ●            |
| Water                            | â€”               | 20 Å°C | ●            |
| Water, distilled                 | â€”               | 20 Å°C | ●            |
| Wine                             | â€”               | 20 Å°C | ●            |
| Xylene                           | â€”               | 20 Å°C | ●            |
| Xylene                           | â€”               | 20 Å°C | ●            |
| Zinc sludge                      | â€”               | 20 Å°C | ●            |