



PEEK Ceram 40x3000 mm harmaa

Artikelnr P1500731

Best ndig Delvis best ndig Ej best ndig

Kemikalie	Pitoisuus	Temp.	Best�ndighet
1,4-Dioxane	100	20 �C	Best�ndig
2-Hydroxypropionic acid (lactic acid)	90	20 �C	Best�ndig
Acetic acid	100	20 �C	Best�ndig
Acetone	100	20 �C	Best�ndig
Ammonia	��	20 �C	Best�ndig
Ammonium chloride	��	20 �C	Best�ndig
Amyl alcohol	��	20 �C	Best�ndig
Apple juice	��	20 �C	Best�ndig
Benzene	��	20 �C	Best�ndig
Boric acid	100	20 �C	Best�ndig
Brake fluid	��	20 �C	Best�ndig
Butyl acetate	��	20 �C	Best�ndig
Calcium chloride	��	20 �C	Best�ndig
Carbon tetrachloride	��	20 �C	Best�ndig
Chlorine (gas)	100	20 �C	Best�ndig
Chlorobenzene	100	20 �C	Best�ndig
Chloroform	��	20 �C	Best�ndig
Citric acid	10	20 �C	Best�ndig
Cyclohexanone	100	20 �C	Best�ndig
Cyclohexene	100	20 �C	Best�ndig
Diesel	��	20 �C	Best�ndig
Diethylene oxide	��	20 �C	Best�ndig
Ethyl acetate	100	20 �C	Best�ndig
Ethyl alcohol (ethanol)	96	20 �C	Best�ndig
Ethylene chloride	100	20 �C	Best�ndig
Food oil	��	20 �C	Best�ndig
Formaldehyde (aqueous)	40	20 �C	Best�ndig

Kemikalie	Pitoisuus	Temp.	Beständighet
Formic acid	10	20 Å°C	●
Frost protection agent	â€”	20 Å°C	●
Fuel oil	â€”	20 Å°C	●
Fuel, aromatic free	â€”	20 Å°C	●
Glycerine	100	20 Å°C	●
Glycol	100	20 Å°C	●
Heptane	100	20 Å°C	●
Hydrochloric acid	10	20 Å°C	●
Hydrochloric acid (concentrated)	â€”	20 Å°C	●
Hydrofluoric acid	40	20 Å°C	●
Hydrogen peroxide	10	20 Å°C	●
Hydrogen sulfide (aqueous)	â€”	20 Å°C	●
Isopropyl alcohol	100	20 Å°C	●
Linseed oil	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Methyl alcohol (methanol)	100	20 Å°C	●
Methyl ethyl ketone (MEK)	100	20 Å°C	●
Methylene chloride	100	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral oils (aromatic free)	â€”	20 Å°C	●
Nitric acid	10	20 Å°C	●
Nitric acid	50	20 Å°C	●
Nitrobenzene	â€”	20 Å°C	●
Oxalic acid	â€”	20 Å°C	●
Ozone (gas)	â€”	20 Å°C	●
Paraffin oil	100	20 Å°C	●
Perchloroethylene	â€”	20 Å°C	●
Petroleum	100	20 Å°C	●
Petroleum ether	100	20 Å°C	●
Phenol (aqueous)	9	20 Å°C	●
Phosphoric acid	50	20 Å°C	●
Potassium hydroxide solution	50	20 Å°C	●
Premium fuel	â€”	20 Å°C	●
Propyl alcohol	â€”	20 Å°C	●
Pyridine	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Silicone oil	â€”	20 Å°C	●
Sodium carbonate (aqueous)	â€”	20 Å°C	●
Sodium chloride (aqueous)	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (caustic soda)	60	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15	20 Å°C	●
Sodium nitrate (aqueous)	â€”	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Vinegar (standard)	5-10	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●