



PEEK MG 25x3000 mm musta

Artikelnr P1501625

Beständig

Delvis beständig

Ej beständig

Kemikalie	Pitoisuus	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€”	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Amyl alcohol	â€”	20 Å°C	
Apple juice	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€”	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	
Food oil	â€”	20 Å°C	
Formaldehyde (aqueous)	40	20 Å°C	

Kemikalie	Pitoisuus	Temp.	BestÄndighet
Formic acid	10	20 Å°C	
Frost protection agent	â€”	20 Å°C	
Fuel oil	â€”	20 Å°C	
Fuel, aromatic free	â€”	20 Å°C	
Glycerine	100	20 Å°C	
Glycol	100	20 Å°C	
Heptane	100	20 Å°C	
Hydrochloric acid	10	20 Å°C	
Hydrochloric acid (concentrated)	â€”	20 Å°C	
Hydrofluoric acid	40	20 Å°C	
Hydrogen peroxide	10	20 Å°C	
Hydrogen sulfide (aqueous)	â€”	20 Å°C	
Isopropyl alcohol	100	20 Å°C	
Linseed oil	â€”	20 Å°C	
Mercurochrome	â€”	20 Å°C	
Methyl alcohol (methanol)	100	20 Å°C	
Methyl ethyl ketone (MEK)	100	20 Å°C	
Methylene chloride	100	20 Å°C	
Milk	â€”	20 Å°C	
Mineral oils (aromatic free)	â€”	20 Å°C	
Nitric acid	10	20 Å°C	
Nitric acid	50	20 Å°C	
Nitrobenzene	â€”	20 Å°C	
Oxalic acid	â€”	20 Å°C	
Ozone (gas)	â€”	20 Å°C	
Paraffin oil	100	20 Å°C	
Perchloroethylene	â€”	20 Å°C	
Petroleum	100	20 Å°C	
Petroleum ether	100	20 Å°C	
Phenol (aqueous)	9	20 Å°C	
Phosphoric acid	50	20 Å°C	
Potassium hydroxide solution	50	20 Å°C	
Premium fuel	â€”	20 Å°C	
Propyl alcohol	â€”	20 Å°C	
Pyridine	â€”	20 Å°C	

Kemikalie	Pitoisuus	Temp.	Beständighet
Silicone oil	â€”	20 Å°C	●
Sodium carbonate (aqueous)	â€”	20 Å°C	●
Sodium chloride (aqueous)	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (caustic soda)	60	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15	20 Å°C	●
Sodium nitrate (aqueous)	â€”	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Vinegar (standard)	5-10	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●