



PET 180x3000 mm luonnollinen

Artikelnr P1003665

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	1.46	g/cm ³	ISO 1183
Venymisrajan jännitys	52	MPa	ISO 527
Joustavuusmoduli (vetolujuus)	3400	MPa	ISO 527-2
Murtolujuus	58	MPa	ISO 527
Murtovenymä	5	%	ISO 527-2
Sulamispiste	224	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	138.75	°C	UL746B
Maksimi käyttölämpötila	97	°C	
Alin lämpötila	-25	°C	
Lämpöalkäyrä (HDT/A)	85	°C	ISO 75
Lämpöalkäyrä (HDT/B)	100	°C	ISO 75
Vicat-pehmenemislämpötila (VST/B/50)	219	°C	ISO 306
Dielektrinen voimakkuus	22	kV/mm	IEC 60243-1
Tilavuusresistanssi	10 ¹⁴ Ω	Ω·cm	DIN EN 62631-3-1
Dielektrinen vakio (1 MHz)	3.3	-	IEC 60250
Dielektrinen hajoamiskerroin (1 MHz)	0.0	-	IEC 60250
Dielektrinen hajoamiskerroin (100 Hz)	0.0	-	IEC 60250
Taivutuslujuus	75.25	MPa	ISO 178
Lämpöjohtavuus	0.33	W/(m·K)	DIN 52612
Pintaresistanssi	10 ¹⁴ Ω	Ω	IEC 60093
Vertailukemisindeksi (CTI)	600	V	IEC 60112
Imeytymisen maksimointi	0.02	%	ISO 62
Vesihaku kyllästymiseen	0.02	%	ISO 62
Särkyäkesto (Charpy)	90	kJ/m ²	ISO 180
Iskunkestävyys (Charpy)	37	kJ/m ²	ISO 179/1eU
Lämpölaajenemiskerroin	0.8	10 ⁻⁶ /K	DIN 11359

Egenskap	V�rde	Enhet	Standard
Kovuus Shore D	77	�� Shore D	ISO 868
Rockwell-kovuus	112	M-scale	
Kulmapaineen kovuus	166	MPa	ISO 2039

2. Kemisk best ndighet

● Best ndig
 ● Delvis best ndig
 ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
1,4-Dioxane	100	●
Acetic acid	100	●
Acetic acid	100	●
Acetic acid	100%	●
Acetone	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonia	conc.	●
Apple juice	���	●
Apple juice	���	●
Benzene	���	●
Benzene	���	●
Bleaching solution	���	●
Brake fluid	���	●
Brake fluid	���	●
Butyl acetate	���	●
Butyl acetate	���	●
Calcium chloride	���	●
Calcium chloride	���	●
Carbon disulphide	100	●
Carbon disulphide	100	●
Carbon tetrachloride	���	●
Carbon tetrachloride	���	●
Carbon tetrachloride	���	●
Chlorobenzene	100	●
Chlorobenzene	100	●
Chlorobenzene	100%	●

Kemikalie	Konc.	Resultat
Chloroform	â€”	
Chloroform	â€”	
Citric acid	10	
Citric acid	10	
Diesel	â€”	
Diesel	â€”	
Diethylene oxide	â€”	
Diethylene oxide	â€”	
Ethyl acetate	100	
Ethyl acetate	100	
Ethyl alcohol (ethanol)	96%	
Ethyl alcohol (ethanol)	96	
Ethyl alcohol (ethanol)	96	
Ethylene chloride	100	
Ethylene chloride	100	
Food oil	â€”	
Food oil	â€”	
Food oil	â€”	
Formic acid	10	
Formic acid	10	
Frost protection agent	â€”	
Frost protection agent	â€”	
Fuel oil	â€”	
Fuel oil	â€”	
Fuel, aromatic free	â€”	
Fuel, aromatic free	â€”	
Glycerine	100%	
Glycerine	100	
Glycerine	100	
Glycol	100	
Glycol	100	
Heptane	100	
Heptane	100	
Hydrochloric acid	conc.	

Kemikalie	Konc.	Resultat
Hydrochloric acid	10	●
Hydrochloric acid	conc.	●
Hydrochloric acid	10	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40	●
Hydrofluoric acid	40%	●
Hydrofluoric acid	40	●
Hydrogen peroxide	10	●
Hydrogen peroxide	10	●
Hydrogen sulfide, aqueous	â€”	●
Isopropyl alcohol	100	●
Isopropyl alcohol	100	●
Isopropyl alcohol	100%	●
Linseed oil	â€”	●
Linseed oil	â€”	●
Mercurochrome	â€”	●
Methyl alcohol (methanol)	100	●
Methyl alcohol (methanol)	100%	●
Methyl alcohol (methanol)	100	●
Methyl ethyl ketone (MEK)	100	●
Methyl ethyl ketone (MEK)	100	●
Methylene chloride	100	●
Methylene chloride	100	●
Milk	â€”	●
Milk	â€”	●
Mineral oils, aromatic free	â€”	●
Mineral oils, aromatic free	â€”	●
Nitric acid	50	●
Nitric acid	10	●
Nitric acid	50	●
Nitric acid	10%	●
Nitric acid	10	●
Paraffin oil	100	●
Paraffin oil	100	●
Perchloroethylene	â€”	●

Kemikalie	Konc.	Resultat
Perchloroethylene	â€”	●
Petroleum	100	●
Petroleum	100%	●
Petroleum ether	100	●
Petroleum ether	100%	●
Petroleum ether	100	●
Phenol, aqueous	ca.9	●
Phosphoric acid	50	●
Phosphoric acid	50	●
Potassium hydroxide solution	50	●
Potassium hydroxide solution	50	●
Premium fuel	â€”	●
Premium fuel	â€”	●
Propyl alcohol	â€”	●
Propyl alcohol	â€”	●
Silicone oil	â€”	●
Silicone oil	â€”	●
Sodium carbonate, aqueous	â€”	●
Sodium carbonate, aqueous	â€”	●
Sodium chloride, aqueous	â€”	●
Sodium chloride, aqueous	â€”	●
Sodium hydrogen sulfite	â€”	●
Sodium hydrogen sulfite	â€”	●
Sodium hydrogen sulfite	â€”	●
Sodium hydroxide solution (caustic soda)	60	●
Sodium hydroxide solution (caustic soda)	60	●
Sodium hydroxide solution (caustic soda)	15	●
Sodium hydroxide solution (caustic soda)	15	●
Sodium nitrate, aqueous	â€”	●
Sodium thiosulfate	â€”	●
Sulphuric acid	96	●
Sulphuric acid	96	●
Tetrahydrofuran (THF)	100	●
Tetrahydrofuran (THF)	100	●

Kemikalie	Konc.	Resultat
Toluene	100%	
Toluene	100	
Toluene	100	
Transformer oil	â€”	
Transformer oil	â€”	
Trichloroethylene	100	
Trichloroethylene	100	
Vinegar, standard	5-10%	
Vinegar, standard	5-10	
Vinegar, standard	5-10	
Water	â€”	
Water	â€”	
Xylene	â€”	
Xylene	â€”	