



PET 90x3000 mm musta

Artikelnr P1003564

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	1.46	g/cm ³	ISO 1183
Venymisrajan jännitys	52	MPa	ISO 527
Joustavuusmoduli (vetolujuus)	3400	MPa	ISO 527-2
Murtolujuus	58	MPa	ISO 527
Murtovenymä	5	%	ISO 527-2
Sulamispiste	224	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	138.75	°C	UL746B
Maksimi käyttölämpötila	97	°C	
Alin lämpötila	-25	°C	
Lämpötilakäyrä (HDT/A)	85	°C	ISO 75
Lämpötilakäyrä (HDT/B)	100	°C	ISO 75
Vicat-pehmenemislämpötila (VST/B/50)	219	°C	ISO 306
Dielektrinen voimakkuus	22	kV/mm	IEC 60243-1
Tilavuusresistanssi	10 ¹⁴ Ω	Ω·cm	DIN EN 62631-3-1
Dielektrinen vakio (1 MHz)	3.3	-	IEC 60250
Dielektrinen hajoamiskerroin (1 MHz)	0.0	-	IEC 60250
Dielektrinen hajoamiskerroin (100 Hz)	0.0	-	IEC 60250
Taivutuslujuus	75.25	MPa	ISO 178
Lämpöjohtavuus	0.33	W/(m·K)	DIN 52612
Pintaresistanssi	10 ¹⁴ Ω	Ω	IEC 60093
Vertailukemisindeksi (CTI)	600	V	IEC 60112
Imeytymisen maksimointi	0.02	%	ISO 62
Vesihaku kyllästymiseen	0.02	%	ISO 62
Särkyäkesto (Charpy)	90	kJ/m ²	ISO 180
Iskunkestävyys (Charpy)	37	kJ/m ²	ISO 179/1eU
Lämpölaajenemiskerroin	0.8	10 ⁻⁶ /K	DIN 11359

Egenskap	V�rde	Enhet	Standard
Kovuus Shore D	77	� Shore D	ISO 868
Rockwell-kovuus	112	M-scale	
Kulmapaineen kovuus	166	MPa	ISO 2039

2. Kemisk best ndighet

● Best ndig
 ● Delvis best ndig
 ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
1,4-Dioxane	100	●
Acetic acid	100	●
Acetic acid	100%	●
Acetic acid	100	●
Acetone	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonia	conc.	●
Apple juice	��	●
Apple juice	��	●
Benzene	��	●
Benzene	��	●
Bleaching solution	��	●
Brake fluid	��	●
Brake fluid	��	●
Butyl acetate	��	●
Butyl acetate	��	●
Calcium chloride	��	●
Calcium chloride	��	●
Carbon disulphide	100	●
Carbon disulphide	100	●
Carbon tetrachloride	��	●
Carbon tetrachloride	��	●
Carbon tetrachloride	��	●
Chlorobenzene	100	●
Chlorobenzene	100%	●
Chlorobenzene	100	●

Kemikalie	Konc.	Resultat
Chloroform	â€”	
Chloroform	â€”	
Citric acid	10	
Citric acid	10	
Diesel	â€”	
Diesel	â€”	
Diethylene oxide	â€”	
Diethylene oxide	â€”	
Ethyl acetate	100	
Ethyl acetate	100	
Ethyl alcohol (ethanol)	96%	
Ethyl alcohol (ethanol)	96	
Ethyl alcohol (ethanol)	96	
Ethylene chloride	100	
Ethylene chloride	100	
Food oil	â€”	
Food oil	â€”	
Food oil	â€”	
Formic acid	10	
Formic acid	10	
Frost protection agent	â€”	
Frost protection agent	â€”	
Fuel oil	â€”	
Fuel oil	â€”	
Fuel, aromatic free	â€”	
Fuel, aromatic free	â€”	
Glycerine	100	
Glycerine	100%	
Glycerine	100	
Glycol	100	
Glycol	100	
Heptane	100	
Heptane	100	
Hydrochloric acid	conc.	

Kemikalie	Konc.	Resultat
Hydrochloric acid	10	
Hydrochloric acid	10	
Hydrochloric acid	conc.	
Hydrochloric acid (concentrated)	conc.	
Hydrofluoric acid	40	
Hydrofluoric acid	40	
Hydrofluoric acid	40%	
Hydrogen peroxide	10	
Hydrogen peroxide	10	
Hydrogen sulfide, aqueous	â€”	
Isopropyl alcohol	100%	
Isopropyl alcohol	100	
Isopropyl alcohol	100	
Linseed oil	â€”	
Linseed oil	â€”	
Mercurochrome	â€”	
Methyl alcohol (methanol)	100	
Methyl alcohol (methanol)	100	
Methyl alcohol (methanol)	100%	
Methyl ethyl ketone (MEK)	100	
Methyl ethyl ketone (MEK)	100	
Methylene chloride	100	
Methylene chloride	100	
Milk	â€”	
Milk	â€”	
Mineral oils, aromatic free	â€”	
Mineral oils, aromatic free	â€”	
Nitric acid	10	
Nitric acid	10	
Nitric acid	10%	
Nitric acid	50	
Nitric acid	50	
Paraffin oil	100	
Paraffin oil	100	
Perchloroethylene	â€”	

Kemikalie	Konc.	Resultat
Perchloroethylene	â€”	
Petroleum	100	
Petroleum	100%	
Petroleum ether	100	
Petroleum ether	100	
Petroleum ether	100%	
Phenol, aqueous	ca.9	
Phosphoric acid	50	
Phosphoric acid	50	
Potassium hydroxide solution	50	
Potassium hydroxide solution	50	
Premium fuel	â€”	
Premium fuel	â€”	
Propyl alcohol	â€”	
Propyl alcohol	â€”	
Silicone oil	â€”	
Silicone oil	â€”	
Sodium carbonate, aqueous	â€”	
Sodium carbonate, aqueous	â€”	
Sodium chloride, aqueous	â€”	
Sodium chloride, aqueous	â€”	
Sodium hydrogen sulfite	â€”	
Sodium hydrogen sulfite	â€”	
Sodium hydrogen sulfite	â€”	
Sodium hydroxide solution (caustic soda)	60	
Sodium hydroxide solution (caustic soda)	15	
Sodium hydroxide solution (caustic soda)	15	
Sodium hydroxide solution (caustic soda)	60	
Sodium nitrate, aqueous	â€”	
Sodium thiosulfate	â€”	
Sulphuric acid	96	
Sulphuric acid	96	
Tetrahydrofuran (THF)	100	
Tetrahydrofuran (THF)	100	

Kemikalie	Konc.	Resultat
Toluene	100	
Toluene	100	
Toluene	100%	
Transformer oil	â€”	
Transformer oil	â€”	
Trichloroethylene	100	
Trichloroethylene	100	
Vinegar, standard	5-10	
Vinegar, standard	5-10%	
Vinegar, standard	5-10	
Water	â€”	
Water	â€”	
Xylene	â€”	
Xylene	â€”	