



PMMA E 30x2000 mm l  pin  kyv  

Artikelnr P1200653

● Best  ndig

● Delvis best  ndig

● Ej best  ndig

Kemikalie	Pitoisuus	Temp.	Best��ndighet
Acetic acid	100%	20 ��C	��
Acetone	100%	20 ��C	��
Ammonia	conc.	20 ��C	��
Amyl alcohol	����	20 ��C	��
Apple juice	����	20 ��C	��
Benzene	����	20 ��C	��
Butyl acetate	����	20 ��C	��
Calcium chloride	����	20 ��C	��
Carbon disulphide	100%	20 ��C	��
Carbon tetrachloride	����	20 ��C	��
Chlorine gas	100%	20 ��C	��
Chloroform	����	20 ��C	��
Citric acid	10%	20 ��C	��
Cresol	����	20 ��C	��
Cyclohexanone	100%	20 ��C	��
Cyclohexene	100%	20 ��C	��
Diesel	����	20 ��C	��
Diethylene oxide	����	20 ��C	��
Ethyl acetate	100%	20 ��C	��
Ethyl alcohol (ethanol)	96%	20 ��C	��
Ethylene chloride	100%	20 ��C	��
Formaldehyde, aqueous	40%	20 ��C	��
Formic acid	10%	20 ��C	��
Fuel oil	����	20 ��C	��
Fuel, aromatic free	����	20 ��C	��
Glycerine	100%	20 ��C	��
Glycol	100%	20 ��C	��

Kemikalie	Pitoisuus	Temp.	Beständighet
Heptane	100%	20 Å°C	●
Hydrochloric acid	10%	20 Å°C	●
Hydrochloric acid (concentrated)	conc.	20 Å°C	●
Hydrofluoric acid	40%	20 Å°C	●
Hydrogen peroxide	10%	20 Å°C	●
Hydrogen sulfide, aqueous	â€”	20 Å°C	●
Isopropyl alcohol	100%	20 Å°C	●
Linseed oil	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Methyl alcohol (methanol)	100%	20 Å°C	●
Methyl ethyl ketone (MEK)	100%	20 Å°C	●
Methylene chloride	100%	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral oils, aromatic free	â€”	20 Å°C	●
Nitric acid	10%	20 Å°C	●
Nitric acid (50%)	50%	20 Å°C	●
Nitrobenzene	â€”	20 Å°C	●
Oxalic acid	â€”	20 Å°C	●
Ozone (gas)	â‰¤ 0.5 ppm	20 Å°C	●
Paraffin oil	100%	20 Å°C	●
Perchloroethylene	â€”	20 Å°C	●
Petroleum	100%	20 Å°C	●
Petroleum ether	100%	20 Å°C	●
Phenol, aqueous	ca. 9%	20 Å°C	●
Phosphoric acid	50%	20 Å°C	●
Potassium hydroxide solution	50%	20 Å°C	●
Premium fuel	â€”	20 Å°C	●
Silicone oil	â€”	20 Å°C	●
Sodium carbonate, aqueous	â€”	20 Å°C	●
Sodium chloride, aqueous	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (60%)	60%	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15%	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Sulphuric acid	96%	20 Å°C	●
Tetrahydrofuran (THF)	100%	20 Å°C	●
Toluene	100%	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100%	20 Å°C	●
Vinegar, standard	5-10%	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●