



# POM C FG 36x1000 mm luonnollinen

Artikelnr P1006229

## 1. Tekniskt datablad

| Egenskap                                      | Värde                           | Enhet               | Standard         |
|-----------------------------------------------|---------------------------------|---------------------|------------------|
| Tiheys                                        | 1.24                            | g/cm <sup>3</sup>   | ASTM D792        |
| Venymisrajan jännitys                         | 51                              | MPa                 | DIN EN ISO 527-2 |
| Joustavuusmoduli (vetolujuus)                 | 1200                            | MPa                 | ASTM D790        |
| Murtolujuus                                   | 76.5                            | MPa                 | ISO 527          |
| Murtovenymä                                   | 300                             | %                   | ASTM D638        |
| Sulamispiste                                  | 222                             | °C                  | ISO 3146         |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 129                             | °C                  | UL746B           |
| Maksimi käyttölämpötila                       | 90                              | °C                  |                  |
| Alin lämpötila                                | -46.25                          | °C                  |                  |
| Lämpötilaköyry (HDT/A)                        | 105                             | °C                  | ASTM D648        |
| Lämpötilaköyry (HDT/B)                        | 155                             | °C                  | ISO 75           |
| Vicat-pehmenemislämpötila (VST/B/50)          | 50                              | °C                  | ISO 306          |
| Dielektrinen voimakkuus                       | 85                              | kV/mm               | IEC 60243-1      |
| Tilavuusresistanssi                           | 10 <sup>11</sup> Å <sup>2</sup> | Å <sup>2</sup>      | IEC 60093        |
| Dielektrinen vakio (1 MHz)                    | 3.7                             | -                   | IEC 60250        |
| Dielektrinen hajoamiskerroin (1 MHz)          | 0.0                             | -                   | IEC 60250        |
| Dielektrinen hajoamiskerroin (100 Hz)         | 0.0                             | -                   | IEC 60250        |
| Paloaluokitus (UL 94)                         | 60695                           |                     | UL 94            |
| Taivutuslujuus                                | 58                              | MPa                 | ASTM D638        |
| Lämpöjohtavuus                                | 0.3                             | W/(mÅ·K)            | DIN 52612        |
| Pintaresistanssi                              | 10 <sup>11</sup> Å <sup>3</sup> | Å <sup>3</sup>      | IEC 60093        |
| Vertailukulkemisindeksi (CTI)                 | 600                             | V                   | IEC 60112        |
| Imeytymisen maksimointi                       | 2.2                             | %                   | ASTM D955        |
| Vesihaku kyllästymiseen                       | 0.5                             | %                   | ASTM D570        |
| Särkyäkesto (Charpy)                          | 6                               | kJ/mÅ <sup>2</sup>  | DIN EN ISO 179-1 |
| Iskunkestävyys (Charpy)                       | 19                              | kJ/mÅ <sup>2</sup>  | ISO 179/1eU      |
| Lämpölaajenemiskerroin                        | 0.4                             | 10 <sup>-6</sup> /K | ISO 11359        |

| Egenskap            | V rde | Enhet     | Standard   |
|---------------------|-------|-----------|------------|
| Kovuus Shore D      | 83    |   Shore D | ISO 868    |
| Kulmapaineen kovuus | 230   | MPa       | ISO 2039-1 |

## 2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

| Kemikalie                             | Konc.   | Resultat |
|---------------------------------------|---------|----------|
| 1,4-Dioxane                           | 100%    | ●        |
| 2-Hydroxypropionic acid (lactic acid) | 90%     | ●        |
| Acetic acid                           | 100%    | ●        |
| Acetone                               | 100%    | ●        |
| Ammonia                               | conc.   | ●        |
| Ammonium chloride                     |         | ●        |
| Amyl alcohol                          |         | ●        |
| Apple juice                           |         | ●        |
| Benzene                               |         | ●        |
| Bleaching solution                    | 12.5 cl | ●        |
| Boric acid                            | 100%    | ●        |
| Brake fluid                           |         | ●        |
| Butyl acetate                         |         | ●        |
| Calcium chloride                      |         | ●        |
| Carbon disulphide                     | 100%    | ●        |
| Carbon tetrachloride                  |         | ●        |
| Chlorobenzene                         | 100%    | ●        |
| Chloroform                            |         | ●        |
| Citric acid                           | 10%     | ●        |
| Cyclohexanone                         | 100%    | ●        |
| Cyclohexene                           | 100%    | ●        |
| Diesel                                |         | ●        |
| Diethylene oxide                      |         | ●        |
| Ethyl acetate                         | 100%    | ●        |
| Ethyl alcohol (ethanol)               | 96%     | ●        |
| Food oil                              |         | ●        |
| Formaldehyde, aqueous                 | 40%     | ●        |
| Formic acid                           | 10%     | ●        |

| Kemikalie                        | Konc.      | Resultat |
|----------------------------------|------------|----------|
|                                  |            |          |
| Frost protection agent           | â€”        | ●        |
| Fuel oil                         | â€”        | ●        |
| Fuel, aromatic free              | â€”        | ●        |
| Glycerine                        | 100%       | ●        |
| Glycol                           | 100%       | ●        |
| Heptane                          | 100%       | ●        |
| Hydrochloric acid                | 10%        | ●        |
| Hydrochloric acid (concentrated) | conc.      | ●        |
| Hydrofluoric acid                | 40%        | ●        |
| Hydrogen peroxide                | 10%        | ●        |
| Hydrogen sulfide, aqueous        | â€”        | ●        |
| Isopropyl alcohol                | 100%       | ●        |
| Linseed oil                      | â€”        | ●        |
| Mercurochrome                    | â€”        | ●        |
| Methyl alcohol (methanol)        | 100%       | ●        |
| Methyl ethyl ketone (MEK)        | 100%       | ●        |
| Methylene chloride               | 100%       | ●        |
| Milk                             | â€”        | ●        |
| Mineral oils (aromatic free)     | â€”        | ●        |
| Nitric acid                      | 10%        | ●        |
| Nitric acid (50%)                | 50%        | ●        |
| Nitrobenzene                     | â€”        | ●        |
| Oxalic acid                      | â€”        | ●        |
| Ozone (gas)                      | â‰¤0.5 ppm | ●        |
| Paraffin oil                     | 100%       | ●        |
| Perchloroethylene                | â€”        | ●        |
| Petroleum                        | 100%       | ●        |
| Petroleum ether                  | 100%       | ●        |
| Phenol, aqueous                  | ca. 9%     | ●        |
| Phosphoric acid                  | 50%        | ●        |
| Potassium hydroxide solution     | 50%        | ●        |
| Premium fuel                     | â€”        | ●        |
| Propyl alcohol                   | â€”        | ●        |
| Silicone oil                     | â€”        | ●        |

| Kemikalie                       | Konc. | Resultat    |
|---------------------------------|-------|-------------|
| Sodium carbonate, aqueous       | â€”   | <div></div> |
| Sodium chloride, aqueous        | â€”   | <div></div> |
| Sodium hydrogen sulfite         | â€”   | <div></div> |
| Sodium hydroxide solution (15%) | 15%   | <div></div> |
| Sodium hydroxide solution (60%) | 60%   | <div></div> |
| Sodium nitrate, aqueous         | â€”   | <div></div> |
| Sulphuric acid                  | 96%   | <div></div> |
| Tetrahydrofuran (THF)           | 100%  | <div></div> |
| Toluene                         | 100%  | <div></div> |
| Transformer oil                 | â€”   | <div></div> |
| Trichloroethylene               | 100%  | <div></div> |
| Vinegar, standard               | 5-10% | <div></div> |
| Water                           | â€”   | <div></div> |
| Xylene                          | â€”   | <div></div> |