

PP-H 180x2000 mm harmaa

Artikelnr P1010071

1. Tekniskt datablad

| Egenskap | Värde | Enhet | Standard |
|---|--------------------|-------------------|------------------|
| Tiheys | 0.91 | g/cm ³ | ISO 1183 |
| Venymisrajan jännitys | 36 | MPa | ISO 527 |
| Joustavuusmoduli (vetolujuus) | 1700 | MPa | ISO 527-2 |
| Murtolujuus | 30 | MPa | ISO 527 |
| Murtovenymä | 8 | % | ISO 527-2 |
| Sulamispiste | 161 | °C | DIN EN ISO 11357 |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 127 | °C | UL746B |
| Maksimi käyttölämpötila | 80 | °C | |
| Alin lämpötila | -7 | °C | |
| Lämpötilakäyrä (HDT/A) | 54 | °C | ISO 75 |
| Lämpötilakäyrä (HDT/B) | 90 | °C | ISO 75 |
| Vicat-pehmenemislämpötila (VST/B/50) | 50 | °C | ISO 306 |
| Dielektrinen voimakkuus | 40 | kV/mm | IEC 60243-1 |
| Tilavuusresistanssi | 10 ¹¹ Ω | Ω | DIN EN 62631-3-1 |
| Dielektrinen vakio (1 MHz) | 2.4 | - | IEC 60250 |
| Dielektrinen hajoamiskerroin (1 MHz) | 13.4 | - | IEC 60250 |
| Dielektrinen hajoamiskerroin (100 Hz) | 0.0 | - | IEC 60250 |
| Paloalokitus (UL 94) | 60695 | | UL 94 |
| Taivutuslujuus | 37 | MPa | DIN EN ISO 527-2 |
| Lämmönjohtavuus | 0.27 | W/(m·K) | ISO 22007-4 |
| Pintaresistanssi | 10 ¹¹ Ω | Ω | IEC 60093 |
| Vertailukemisindeksi (CTI) | 600 | V | IEC 60112 |
| Imeytymisen maksimointi | 0.2 | % | ISO 62 |
| Vesihaku kylmistymiseen | 0.2 | % | ISO 62 |
| Särkyäkesto (Charpy) | 9 | kJ/m ² | ISO 179/1eA |
| Iskunkestävyys (Charpy) | 7.7 | kJ/m ² | ISO 179 |

| Egenskap | Värde | Enhet | Standard |
|-----------------------|-------|----------------------|-------------|
| Löslighetskoefficient | 1.6 | 10 ⁻⁴ g/K | ISO 11359-2 |
| Kovus Shore D | 72 | Å° Shore D | ISO 868 |
| Kulmapaineen kovuus | 110 | MPa | ISO 2039 |

2. Kemisk beständighet

● Beständig
 ● Delvis beständig
 ● Ej beständig

| Kemikalie | Konc. | Resultat |
|---------------------------------------|-------|----------|
| 1,4-Dioxane | 100 | ● |
| 2-Hydroxypropionic acid (lactic acid) | 90 | ● |
| Acetic acid | 100 | ● |
| Acetone | 100 | ● |
| Ammonia | â€” | ● |
| Ammonium chloride | â€” | ● |
| Amyl alcohol | â€” | ● |
| Benzene | â€” | ● |
| Bleaching solution | â€” | ● |
| Boric acid | 100 | ● |
| Brake fluid | â€” | ● |
| Butyl acetate | â€” | ● |
| Calcium chloride | â€” | ● |
| Carbon disulphide | 100 | ● |
| Carbon tetrachloride | â€” | ● |
| Chlorine (gas) | 100 | ● |
| Chlorobenzene | 100 | ● |
| Chloroform | â€” | ● |
| Citric acid | 10 | ● |
| Cresol | â€” | ● |
| Cyclohexanone | 100 | ● |
| Cyclohexene | 100 | ● |
| Diesel | â€” | ● |
| Diethylene oxide | â€” | ● |
| Ethyl acetate | 100 | ● |
| Ethyl alcohol (ethanol) | 96 | ● |
| Ethylene chloride | 100 | ● |

| Kemikalie | Konc. | Resultat |
|----------------------------------|-------------|----------|
| Food oil | â€” | ● |
| Formaldehyde, aqueous | 40 | ● |
| Formic acid | 10 | ● |
| Frost protection agent | â€” | ● |
| Fuel oil | â€” | ● |
| Fuel, aromatic free | â€” | ● |
| Glycerine | 100 | ● |
| Glycol | 100 | ● |
| Heptane | 100 | ● |
| Hydrochloric acid | 10 | ● |
| Hydrochloric acid (concentrated) | â€” | ● |
| Hydrofluoric acid | 40 | ● |
| Hydrogen peroxide | 10 | ● |
| Hydrogen sulfide, aqueous | â€” | ● |
| Isopropyl alcohol | 100 | ● |
| Linseed oil | â€” | ● |
| Mercurochrome | â€” | ● |
| Methyl alcohol (methanol) | 100 | ● |
| Methyl ethyl ketone (MEK) | 100 | ● |
| Methylene chloride | 100 | ● |
| Milk | â€” | ● |
| Mineral oils (aromatic free) | â€” | ● |
| Nitric acid | 50 | ● |
| Nitric acid | 10 | ● |
| Nitrobenzene | â€” | ● |
| Oxalic acid | â€” | ● |
| Ozone (gas) | â‰¤ 0.5 ppm | ● |
| Paraffin oil | 100 | ● |
| Perchloroethylene | â€” | ● |
| Petroleum ether | 100 | ● |
| Phenol, aqueous | ca. 9 | ● |
| Phosphoric acid | 50 | ● |
| Potassium hydroxide solution | 50 | ● |
| Premium fuel | â€” | ● |
| Propyl alcohol | â€” | ● |

| Kemikalie | Konc. | Resultat |
|--|--------|----------|
| Pyridine | â€” | ● |
| Silicone oil | â€” | ● |
| Sodium carbonate, aqueous | â€” | ● |
| Sodium chloride, aqueous | â€” | ● |
| Sodium hydrogen sulfite | â€” | ● |
| Sodium hydroxide solution (caustic soda) | 60 | ● |
| Sodium hydroxide solution (caustic soda) | 15 | ● |
| Sodium nitrate, aqueous | â€” | ● |
| Sodium thiosulfate | â€” | ● |
| Sulphuric acid | 96 | ● |
| Tetrahydrofuran (THF) | 100 | ● |
| Toluene | 100 | ● |
| Transformer oil | â€” | ● |
| Trichloroethylene | 100 | ● |
| Vinegar, standard | 5 - 10 | ● |
| Water | â€” | ● |
| Xylene | â€” | ● |