



PPS 30x1000 mm luonnollinen

Artikelnr P1010765

Best ndig

Delvis best ndig

Ej best ndig

Kemikalie	Pitoisuus	Temp.	Best�ndighet
1,4-Dioxane	100	20 �C	
Acetone	100	20 �C	
Ammonia	��	20 �C	
Ammonium chloride	��	20 �C	
Benzene	��	20 �C	
Brake fluid	��	20 �C	
Butyl acetate	��	20 �C	
Calcium chloride	��	20 �C	
Carbon tetrachloride	��	20 �C	
Chlorobenzene	100	20 �C	
Chloroform	��	20 �C	
Diesel	��	20 �C	
Diethylene oxide	��	20 �C	
Ethyl acetate	100	20 �C	
Ethyl alcohol (ethanol)	96	20 �C	
Frost protection agent	��	20 �C	
Fuel, aromatic free	��	20 �C	
Glycerine	100	20 �C	
Hydrochloric acid (10%)	10	20 �C	
Hydrochloric acid (concentrated)	��	20 �C	
Isopropyl alcohol	100	20 �C	
Methyl alcohol (methanol)	100	20 �C	
Methyl ethyl ketone (MEK)	100	20 �C	
Methylene chloride	100	20 �C	
Mineral oils (aromatic free)	��	20 �C	
Nitric acid (10%)	10	20 �C	
Nitric acid (50%)	50	20 �C	

Kemikalie	Pitoisuus	Temp.	Beständighet
Perchloroethylene	â€”	20 Å°C	●
Phenol, aqueous	9	20 Å°C	●
Phosphoric acid	50	20 Å°C	●
Premium fuel	â€”	20 Å°C	●
Sodium chloride, aqueous	â€”	20 Å°C	●
Sodium hydroxide solution (15%)	15	20 Å°C	●
Sodium hydroxide solution (60%)	60	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●