



Artikelnr P2202718

Egenskap	V�rde	Enhet	Standard
Tetthet	1.65	g/cm� ³	DIN EN ISO 1183-1
StrekkgrenseSpenning	30.8	MPa	DIN EN ISO 527
Elastisitetsmodul (trek)	1640	MPa	DIN EN ISO 527
Brottsdeformasjon	50	%	DIN EN ISO 527
Maksimal drifttemperatur (kortvarig)	156	�C	
Maksimal driftstemperatur	150	�C	
Minstemperatur	-40	�C	
Vicat-mykningstemperatur (VST/B/50)	118	�C	DIN EN ISO 306
Dielektrisk Styrke	23	kV/mm	DIN IEC 60243-1
Termisk konduktivit�t	0.15	W/(m�K)	DIN 52612-1
Overflatemotstand	~10� ³ �	��	DIN EN 61340
Sk�ret slagfasthet (Charpy)	100	kJ/m� ²	DIN EN ISO 179-1eA
Termisk utvidelseskoeffisient	1	10� ⁻⁶ /K	ISO 11359-2
Hardhet Shore D	72.25	� Shore D	DIN EN ISO 868
Kuletrykkshardhet	56	MPa	DIN EN ISO 2039-1

● BestÃndig ● Delvis bestÃndig ● Ej bestÃndig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	
2-Hydroxypropionic Acid	90	
Acetic Acid	100	
Aceton	100	
Ammoniak	â€”	
Ammonium Chloride	â€”	
Amyl Alcohol	â€”	

Kemikalie	Konc.	Resultat
Apple Juice	â€”	●
Bensen	â€”	●
Bleaching Solution	â€”	●
Boric Acid	100	●
Brake Fluid	â€”	●
Br��nsle, aromatfritt	â€”	●
Butyl Acetate	â€”	●
Calcium Chloride	â€”	●
Carbon Disulfide	100	●
Carbon Tetrachloride	â€”	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	â€”	●
Diethylene Oxide	â€”	●
Eddik (standard)	5 - 10	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol (vattenl.)	ca. 9	●
Food Oil	â€”	●
Formaldehyd (vattenl.)	40	●
Formic Acid	10	●
Frost Protection Agent	â€”	●
Glycerin	100	●
Glykol	100	●
Heating Oil	â€”	●
Heptan	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	â€”	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●

Kemikalie	Konc.	Resultat
Klor (gas)	100	
Klorbensen	100	
Kloroform	â€”	
Kresol	â€”	
Linseed Oil	â€”	
Melk	â€”	
Merkurokrom	â€”	
Methyl Alcohol	100	
Methyl Ethyl Ketone (MEK)	100	
Methylene Chloride	100	
Mineral Oils (aromatic free)	â€”	
Nitric Acid	10	
Nitric Acid (50%)	50	
Nitrobensen	â€”	
Oxalic Acid	â€”	
Ozone Gas	â‰‰ 0.5 ppm	
Paraffine Oil	100	
Perkloretylen	â€”	
Petroleum	100	
Petroleum Ether	100	
Phosphoric Acid	50	
Potassium Hydroxide liquor	50	
Premium Fuel	â€”	
Propyl Alcohol	â€”	
Pyridin	â€”	
Silicone Oil	â€”	
Sodium Carbonate (aqueous)	â€”	
Sodium Chloride (aqueous)	â€”	
Sodium Hydrogen Sulfite	â€”	
Sodium Hydroxide liquor	15	
Sodium Hydroxide liquor (60)	60	
Sodium Nitrate (aqueous)	â€”	
Sodium Thiosulfate	â€”	
Sulfuric Acid	96	

Kemikalie	Konc.	Resultat
Tetrahydrofuran (THF)	100	
Toluen	100	
Transformer Oil	â€”	
Trikloreten	100	
Vann	â€”	
Xylen	â€”	