

PA6 C 100/50x3000 mm natur

Artikelnr P1200044

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tetthet	1.1	g/cm ³	ISO 1183
StreckgränseSpänning	75	MPa	ISO 527
Elastisitetsmodul (trek)	3500	MPa	ISO 527-2
Brottsdeformasjon	25	%	ISO 527-2
Smeltepunkt	220	Å°C	ISO 3146
Maksimal drifttemperatur (kortvarig)	170	Å°C	
Maksimal driftstemperatur	105	Å°C	
Minstemperatur	-30	Å°C	
Varme-forvringning (HDT/A)	80	Å°C	ISO 75-2
Dielektrisk Styrke	25	kV/mm	IEC 60243-1
VolumResistivitet	10 ¹⁴ Å	Î@Å-cm	IEC 60093
Dielektrisk konstant (1 MHz)	3.2	-	IEC 60250
Dielektrisk konstant (100 Hz)	3.6	-	IEC 60250
Dielektrisk dissipasjonsfaktor (1 MHz)	0.0	-	IEC 60250
Dielektrisk tapfaktor (100 Hz)	0.0	-	IEC 60250
BÄyhfÄlfasthet	85	MPa	ISO 527-2
Termisk konduktivitet	0.29	W/(mÅ-K)	DIN 52612
Overflatemotstand	10 ¹⁴ Å ³	Î@	IEC 60093
SammenligningskrypstrÄmsindeks (CTI)	600	V	IEC 60112
Fuktabsorpsjon til metning	2.3	%	ISO 62
Vannabsorpsjon til metning	6.5	%	ISO 62
SkÄyret slagfasthet (Charpy)	3.5	kJ/mÅ ²	ISO 179/1eA
Termisk utvidelseskoeffisient	0.8	10 ⁻⁶ Å ⁻¹ /K	ISO 11359
Kuletrykkshardhet	148.3	MPa	ISO 2039-1

2. Kemisk bestÄndighet

● BestÄndig ● Delvis bestÄndig ● Ej bestÄndig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Aceton	100	●
Ammoniak	conc.	●
Ammonium Chloride	â€	●
Amyl Alcohol	â€	●
Apple Juice	â€	●
Bensen	â€	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	â€	●
Br�nsle (aromatfritt)	â€	●
Butyl Acetate	â€	●
Calcium Chloride	â€	●
Carbon Disulfide	100	●
Carbon Tetrachloride	â€	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	â€	●
Diethylene Oxide	â€	●
Eddik (standard)	5 - 10	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol (vattenl.)	ca. 9	●
Food Oil	â€	●
Formaldehyd (vattenl.)	40	●
Formic Acid	10	●
Frost Protection Agent	â€	●
Glycerin	100	●
Glykol	100	●
Heating Oil	â€	●
Heptan	100	●

Kemikalie	Konc.	Resultat
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●
Kresol	â€”	●
Linseed Oil	â€”	●
Melk	â€”	●
Merkurokrom	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	â€”	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â‰ƒ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridin	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●

Kemikalie	Konc.	Resultat
Sodium Hydrogen Sulfit	â€”	●
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor	60	●
Sodium Nitrate (aqueous)	â€”	●
Sodium Thiosulfate	â€”	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluen	100	●
Transformer Oil	â€”	●
Trikloretan	100	●
Vann	â€”	●
Xylen	â€”	●