



PlastShop.se

Artikelnr P1001337

Egenskap	V�rde	Enhet	Standard
Tetthet	1.14	g/cm����	ISO 1183
Tetthet	1.13	g/cm����	ISO 1183
StrekkgrenseSpenning	70	MPa	DIN EN ISO 527
StrekkgrenseSpenning	83	MPa	ISO 527
Elastisitetsmodul (trek)	3250	MPa	ISO 527-2
Elastisitetsmodul (trek)	3330	MPa	ISO 527
Brottspenning	75	MPa	ISO 527-2
Brottspenning	54	MPa	ISO 527
Brottsdeformasjon	40	%	ISO 527-2
Brottsdeformasjon	50	%	ISO 527
Smeltepunkt	220	����	ISO 3146
Smeltepunkt	220	����	ISO 3146
Maksimal drifttemperatur (kortvarig)	160	����	
Maksimal drifttemperatur (kortvarig)	130	����	UL746B
Maksimal driftstemperatur	90.5	����	
Maksimal driftstemperatur	85	����	
Minstemperatur	-36	����	
Minstemperatur	-40	����	
Varme-forvrengning (HDT/A)	70	����	ISO 75-2
Varme-forvrengning (HDT/A)	75	����	ISO 75-2
Varme-forvrengning (HDT/B)	140	����	ISO 75-2
Varme-forvrengning (HDT/B)	190	����	ISO 75-2
Vicat-mykningstemperatur (VST/B/50)	190	����	ISO 306
Dielektrisk Styrke	30	kV/mm	IEC 60243-1
Dielektrisk Styrke	25	kV/mm	IEC 60243-1
VolumResistivit��	10��������	��������	IEC 60093

Kemikalie	Konc.	Resultat
Aceton	100	●
Ammoniak	conc.	●
Ammonium Chloride	â€”	●
Amyl Alcohol	â€”	●
Apple Juice	â€”	●
Bensen	â€”	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	â€”	●
Br��nsle (aromatfritt)	â€”	●
Butyl Acetate	â€”	●
Calcium Chloride	â€”	●
Carbon Disulfide	100	●
Carbon Tetrachloride	â€”	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	â€”	●
Diethylene Oxide	â€”	●
Eddik (standard)	5 - 10	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol (vattenl.)	ca. 9	●
Food Oil	â€”	●
Formaldehyd (vattenl.)	40	●
Formic Acid	10	●
Frost Protection Agent	â€”	●
Glycerin	100	●
Glykol	100	●
Heating Oil	â€”	●
Heptan	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●

Kemikalie	Konc.	Resultat
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●
Kresol	â€”	●
Linseed Oil	â€”	●
Melk	â€”	●
Merkurokrom	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	â€”	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â‰‰ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridin	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●
Sodium Hydrogen Sulfite	â€”	●
Sodium Hydroxide liquor	15	●

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor	60	
Sodium Nitrate (aqueous)	â€”	
Sodium Thiosulfate	â€”	
Sulfuric Acid	96	
Tetrahydrofuran (THF)	100	
Toluen	100	
Transformer Oil	â€”	
Trikloreten	100	
Vann	â€”	
Xylen	â€”	