



PA6 GF30 3000x610x12 mm svart

Artikelnr P1001534
Material PA

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tetthet	1.34	g/cm³	ISO 1183
Elastisitetsmodul (trek)	8700	MPa	ISO 527-2
Smeltepunkt	220	°C	ISO 3146
Maksimal drifttemperatur (kortvarig)	180	°C	
Maksimal drifttemperatur	100	°C	
Minstemperatur	-20	°C	
Varme-forvregning (HDT/A)	210	°C	ISO 75-2
VolumResistivitet	10 ¹⁴	Ω·cm	IEC 60093
Bøyhållfasthet	120	MPa	ISO 527-2
Termisk konduktivitet	0.28	W/(m·K)	DIN 52612
Overflatemotstand	10 ¹³	Ω	IEC 60093
Fuktabsorpsjon til metning	2.1	%	ISO 62
Vannabsorpsjon til metning	6.6	%	ISO 62
Skåret slagfasthet (Charpy)	5	kJ/m²	ISO 179/1eA
Slagseghet (Charpy)	50	kJ/m²	ISO 179/1eU
Termisk utvidelseskoeffisient	0.26	10 ⁻⁴ /K	DIN 11359
Kuletrykkshardhet	43	MPa	ISO 2039-1

2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	Delvis beständig
2-Hydroxypropionic Acid	90	Ej beständig
Acetic Acid	100	Beständig
Aceton	100	Delvis beständig

Kemikalie	Konc.	Resultat
Ammoniak	conc.	
Ammonium Chloride	-	
Amyl Alcohol	-	
Apple Juice	-	
Bensen	-	
Bleaching Solution	12.5 cl	
Boric Acid	100	
Brake Fluid	-	
Bränsle (aromatfritt)	-	
Butyl Acetate	-	
Calcium Chloride	-	
Carbon Disulfide	100	
Carbon Tetrachloride	-	
Citric Acid	10	
Cyklohexanon	100	
Cyklohexen	100	
Diesel Fuel	-	
Diethylene Oxide	-	
Eddik (standard)	5 - 10	
Ethyl Acetate	100	
Ethyl Alcohol	96	
Ethylene Chloride	100	
Fenol (vattenl.)	ca. 9	
Food Oil	-	
Formaldehyd (vattenl.)	40	
Formic Acid	10	
Frost Protection Agent	-	
Glycerin	100	
Glykol	100	
Heating Oil	-	
Heptan	100	
Hydrochloric Acid	10	
Hydrochloric Acid (concentrated)	conc.	
Hydrofluoric Acid	40	
Hydrogen Peroxide	10	

Kemikalie	Konc.	Resultat
Hydrogen Sulfide (aqueous)	-	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	-	●
Kresol	-	●
Linseed Oil	-	●
Melk	-	●
Merkurokrom	-	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	-	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	-	●
Oxalic Acid	-	●
Ozone Gas	≤ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	-	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	-	●
Propyl Alcohol	-	●
Pyridin	-	●
Silicone Oil	-	●
Sodium Carbonate (aqueous)	-	●
Sodium Chloride (aqueous)	-	●
Sodium Hydrogen Sulfite	-	●
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor	60	●
Sodium Nitrate (aqueous)	-	●
Sodium Thiosulfate	-	●

Kemikalie	Konc.	Resultat
Sulfuric Acid	96	
Tetrahydrofuran (THF)	100	
Toluen	100	
Transformer Oil	-	
Trikloreten	100	
Vann	-	
Xylen	-	