



PA6 GL 2000x1000x60 mm gr nn

Artikelnr P1600241

1. Tekniskt datablad

Egenskap	V�rde	Enhet	Standard
T�tthet	1.1	g/cm���	DIN EN ISO 1183-1
StreckgrenseSp�nning	67.5	MPa	DIN EN ISO 527
Elastisitetsmodul (trek)	3000	MPa	DIN EN ISO 527
Brottsdeformasjon	198.5	%	DIN EN ISO 527
Smeltepunkt	218	��C	ISO 11357-3
Maksimal drifttemperatur (kortvarig)	162.5	��C	
Maksimal driftstemperatur	109	��C	
Minstemperatur	-40	��C	
Varme-forvrengning (HDT/A)	90	��C	ISO 75
Dielektrisk Styrke	20	kV/mm	IEC 60243
VolumResistivit�t	10������	��������	DIN EN 62631-3-1
Dielektrisk konstant (1 MHz)	3.7	-	IEC 60250
Dielektrisk tapfaktor (100 Hz)	0.02	-	IEC 60250
Termisk konduktivit�t	0.3	W/(m���K)	DIN 52612-1
Overflatemotstand	10������	����	DIN EN 62631-3-2
Sammenligningskrypstr��msindeks (CTI)	600	V	IEC 60112
Fuktabsorpsjon til metning	5.65	%	DIN EN ISO 62
Vannabsorpsjon til metning	5.65	%	DIN EN ISO 62
Sk��ret slagfasthet (Charpy)	13	kJ/m���	DIN EN ISO 179
Termisk utvidelseskoeffisient	0.7	10������/K	DIN 53752
Hardhet Shore D	81	��� Shore D	ISO 868

2. Kemisk best  ndighet

   Best  ndig    Delvis best  ndig    Ej best  ndig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	��

Kemikalie	Konc.	Resultat
2-Hydroxypropionic Acid	90	
Acetic Acid	100	
Aceton	100	
Ammoniak	conc.	
Ammonium Chloride	â€”	
Amyl Alcohol	â€”	
Apple Juice	â€”	
Bensen	â€”	
Bleaching Solution	12.5 cl	
Boric Acid	100	
Brake Fluid	â€”	
Br��nsle (aromatfritt)	â€”	
Butyl Acetate	â€”	
Calcium Chloride	â€”	
Carbon Disulfide	100	
Carbon Tetrachloride	â€”	
Citric Acid	10	
Cyklohexanon	100	
Cyklohexen	100	
Diesel Fuel	â€”	
Diethylene Oxide	â€”	
Eddik (standard)	5 - 10	
Ethyl Acetate	100	
Ethyl Alcohol	96	
Ethylene Chloride	100	
Fenol (vattenl.)	ca. 9	
Food Oil	â€”	
Formaldehyd (vattenl.)	40	
Formic Acid	10	
Frost Protection Agent	â€”	
Glycerin	100	
Glykol	100	
Heating Oil	â€”	
Heptan	100	
Hydrochloric Acid	10	

Kemikalie	Konc.	Resultat
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●
Kresol	â€”	●
Linseed Oil	â€”	●
Melk	â€”	●
Merkurokrom	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	â€”	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â‰‰ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridin	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●
Sodium Hydrogen Sulfite	â€”	●

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor	60	●
Sodium Nitrate (aqueous)	â€”	●
Sodium Thiosulfate	â€”	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluen	100	●
Transformer Oil	â€”	●
Trikloreten	100	●
Vann	â€”	●
Xylen	â€”	●