



PC UV 3050x2050x8 mm gjennomsiktig

Artikelnr P1200191

Best ndig Delvis best ndig Ej best ndig

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
1,4-Dioxan	100%	20 �C	
2-Hydroxipropionsyra (mj�lkksyra)	90%	20 �C	
Aceton	100%	20 �C	
Ammoniak	conc.	20 �C	
Ammoniumklorid	��	20 �C	
Bensen	��	20 �C	
Bensin (premium)	��	20 �C	
Blekningsl�sning	12.5 cl	20 �C	
Borsyra	100%	20 �C	
Br�nsle, aromatfritt	��	20 �C	
Butylacetat	��	20 �C	
Citronsyra	10%	20 �C	
Cyklohexanon	100%	20 �C	
Cyklohexen	100%	20 �C	
Diesel	��	20 �C	
Dietylenoxid	��	20 �C	
Eddik, standard	5-10%	20 �C	
Eplejuice	��	20 �C	
Etylacetat	100%	20 �C	
Etylalkohol (etanol)	96%	20 �C	
Etylenklorid	100%	20 �C	
Fenol, vattenl.	ca. 9%	20 �C	
Flussyre	40%	20 �C	
Formaldehyd, vattenl.	40%	20 �C	
Fosforsyra	50%	20 �C	
Frostv�lske	��	20 �C	
Fyringsolje	��	20 �C	

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Glycerin	100%	20 �C	�
Glykol	100%	20 �C	�
Heptan	100%	20 �C	�
Hydrogenperoksid	10%	20 �C	�
Isopropylalkohol	100%	20 �C	�
Kalciumklorid	��	20 �C	�
Kaliumhydroxid��sning	50%	20 �C	�
Klor (gas)	100%	20 �C	�
Klorbensen	100%	20 �C	�
Kloroform	��	20 �C	�
Koldisulfid	100%	20 �C	�
Koltetraklorid	��	20 �C	�
Kresol	��	20 �C	�
Linolje	��	20 �C	�
Matolje	��	20 �C	�
Maursyre	10%	20 �C	�
Melk	��	20 �C	�
Merkurokrom	��	20 �C	�
Metylalkohol (metanol)	100%	20 �C	�
Metylenklorid	100%	20 �C	�
Metyletylketon (MEK)	100%	20 �C	�
Natriumkarbonat, vattenl.	��	20 �C	�
Natriumklorid, vattenl.	��	20 �C	�
Natriumnitrat, vattenl.	��	20 �C	�
Natriumv��tesulfit	��	20 �C	�
Natronlut (15%)	15%	20 �C	�
Natronlut (60%)	60%	20 �C	�
Nitrobensen	��	20 �C	�
Oxalsyra	��	20 �C	�
Ozon (gas)	��� 0.5 ppm	20 �C	�
Paraffinolja	100%	20 �C	�
Perkloretylen	��	20 �C	�
Petroleum	100%	20 �C	�
Petroleumeter	100%	20 �C	�

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Propylalkohol	��	20 �C	�
Pyridin	��	20 �C	�
Salpetersyra (10%)	10%	20 �C	�
Salpetersyra (50%)	50%	20 �C	�
Saltsyra	10%	20 �C	�
Saltsyra (konc.)	conc.	20 �C	�
Silikonolje	��	20 �C	�
Svavelsyra	96%	20 �C	�
Tetrahydrofuran (THF)	100%	20 �C	�
Toluen	100%	20 �C	�
Trikloret�n	100%	20 �C	�
Vann	��	20 �C	�
V��tesulfid, vattenl.	��	20 �C	�
Xylen	��	20 �C	�
��ttiksyra	100%	20 �C	�