



PE Ultra HD Ast 3000x1250x50 mm svart

Artikelnr P1400202

Best ndig

Delvis best ndig

Ej best ndig

Kemikalie		Konsentrasjon	Temp.	Best�ndighet
1,4-Dioxan	100%	20 �C		
2-Hydroxypropionic Acid	90%	20 �C		
Acetaldehyd	��	20 �C		
Acetic Acid	100%	20 �C		
Aceton	��	20 �C		
Aceton	100%	20 �C		
Acronal-dispersjoner	��	20 �C		
Akrylonitril	��	20 �C		
Allylacetat	��	20 �C		
Allylalkohol	96%	20 �C		
Allylklorid	��	20 �C		
Aluminiumfluorid	Conc.	20 �C		
Aluminiumhydroxid	��	20 �C		
Aluminiumklorid, fast	��	20 �C		
Aluminiumklorid, vattenl.	any	20 �C		
Aluminiummetafosfat	��	20 �C		
Aluminiumsulfat, fast	��	20 �C		
Aluminiumsulfat, vattenl. m�ttad	��	20 �C		
Ammoniak	concentrated	20 �C		
Ammoniak, flytande	��	20 �C		
Ammoniak, gas	��	20 �C		
Ammonium Chloride	��	20 �C		
Amyl Alcohol	��	20 �C		
Anilin	any	20 �C		
Anisol	��	20 �C		
Apple Juice	��	20 �C		
Bensen	technically grade	20 �C		

[illegible]

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Diklorethan	â€”	20 Â°C	
Diklor�ttiksyr�	â€”	20 Â°C	
Dimethyl formamide	â€”	20 Â°C	
Dimetylamin	â€”	20 Â°C	
Dioxan	â€”	20 Â°C	
Eddik (standard)	5-10%	20 Â°C	
Ethanol	10% v/v	20 Â°C	
Ethanol	10%	100 Â°C	
Ethanol	10%	100 Â°C	
Ethanol	10%	100 Â°C	
Ethyl Acetate	100%	20 Â°C	
Ethyl Alcohol	96%	20 Â°C	
Ethylene Chloride	100%	20 Â°C	
Etylacetat	â€”	20 Â°C	
Etylenalkohol	96%	20 Â°C	
Etylendiamin	â€”	20 Â°C	
Etylenglykol	â€”	20 Â°C	
Etylenklorid	â€”	20 Â°C	
Fenol	â€”	20 Â°C	
Fenol (vattenl.)	���9%	20 Â°C	
Ferrous (III) nitrate, aqueous saturated	â€”	20 Â°C	
Ferrous (III) sulfate, aqueous saturated	â€”	20 Â°C	
Food Oil	â€”	20 Â°C	
Formaldehyd (vattenl.)	40%	20 Â°C	
Formaldehyd, vattenl.	���40%	20 Â°C	
Formic Acid	10%	20 Â°C	
Fosforsyra, vattenl.	80% L 95%	20 Â°C	
Fosforsyra, vattenl.	50%	20 Â°C	
Fosfortriklorid	â€”	20 Â°C	
Frigen 12 (Freon 12)	100%	20 Â°C	
Frost Protection Agent	â€”	20 Â°C	
Fruktjuicer	any	20 Â°C	
Ftalsyra, vattenl.	50%	20 Â°C	
Furfurol	â€”	20 Â°C	

[illegible]

[illegible]

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Nitric Acid	10%	20 ��C	●
Nitric Acid (50%)	50%	20 ��C	●
Nitrobensen	���	20 ��C	●
Nitrobensen	���	20 ��C	●
Oils, ethereal	���	20 ��C	●
Oksygen	���	20 ��C	●
Oleum	any	20 ��C	●
Olive oil	���	100 ��C	●
Olive oil	���	20 ��C	●
Olive oil	���	100 ��C	●
Olive oil	���	100 ��C	●
Oljer, vegetabilske og animalske	���	20 ��C	●
Oljesyra	���	20 ��C	●
Oppvaskmiddel	���	20 ��C	●
Oxalic Acid	���	20 ��C	●
Oxalsyra, vattenl.	any	20 ��C	●
Ozon	50 ppm	20 ��C	●
Ozone Gas	���0.5 ppm	20 ��C	●
Paraffine Oil	100%	20 ��C	●
Parafin	���	20 ��C	●
Perkloretylen	���	20 ��C	●
Perklorsyra, vattenl.	50%	20 ��C	●
Perklorsyra, vattenl.	20%	20 ��C	●
Perklorsyra, vattenl.	70%	20 ��C	●
Petroleum	100%	20 ��C	●
Petroleum	���	20 ��C	●
Petroleum Ether	100%	20 ��C	●
Petroleumeter	���	20 ��C	●
Phosphoric Acid	50%	20 ��C	●
Photographic developers	���	20 ��C	●
Photographic emulsions	as supplied	20 ��C	●
Photographic fixing baths	as supplied	20 ��C	●
Polyesterhartser	���	20 ��C	●
Potassium Hydroxide liquor	50%	20 ��C	●

Kemikalie	Konsentrasjon	Temp.	BestÅndighet
Premium Fuel	â€”	20 Å°C	●
Propionsyra, vattenl.	any	20 Å°C	●
Propyl Alcohol	â€”	20 Å°C	●
Pyridin	â€”	20 Å°C	●
Pyridin	â€”	20 Å°C	●
Salpetersyra, vattenl.	25%	20 Å°C	●
Salpetersyra, vattenl.	50%	20 Å°C	●
Saltsyra, vattenl.	any	20 Å°C	●
Silicon dioxide	â€”	20 Å°C	●
Silicon dioxide	â€”	20 Å°C	●
Silicone Oil	â€”	20 Å°C	●
Silikonolje	technically grade	20 Å°C	●
SjÅ, vann	â€”	20 Å°C	●
SmÅ, r	â€”	20 Å°C	●
Sodium Carbonate (aqueous)	â€”	20 Å°C	●
Sodium Chloride (aqueous)	â€”	20 Å°C	●
Sodium Hydrogen Sulfite	â€”	20 Å°C	●
Sodium Hydroxide liquor	15%	20 Å°C	●
Sodium Hydroxide liquor (60%)	60%	20 Å°C	●
Sodium Nitrate (aqueous)	â€”	20 Å°C	●
Sodium Thiosulfate	â€”	20 Å°C	●
Sodium borate	â€”	20 Å°C	●
Stearinsyra	â€”	20 Å°C	●
Sukkersirup	â€”	20 Å°C	●
Sulfuric Acid	96%	20 Å°C	●
Svavelsyra, vattenl.	80%	20 Å°C	●
Svavelsyra, vattenl.	â‰‰50%	20 Å°C	●
Svavelsyra, vattenl.	70%	20 Å°C	●
Svavelsyra, vattenl.	98%	20 Å°C	●
SyltetÅ, y	â€”	20 Å°C	●
Talg	technically grade	20 Å°C	●
Tenn(II)klorid, vattenl.	any	20 Å°C	●
Tenn(IV)klorid, vattenl.	saturated	20 Å°C	●
Terpentinolje	technically grade	20 Å°C	●
Tetrahydrofuran	technically grade	20 Å°C	●

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Tetrahydrofuran (THF)	100%	20 �C	
Tiofen	��	20 �C	
Tionylklorid	��	20 �C	
Titanium dioxide	��	20 �C	
Titanium dioxide	��	20 �C	
Toluen	technically grade	20 �C	
Toluen	100%	20 �C	
Torskeleverije	��	20 �C	
Transformatorolja (isolerolja)	technically grade	20 �C	
Transformer Oil	��	20 �C	
Trichloracetic acid	technically grade	20 �C	
Trietanolamin	��	20 �C	
Trietanolamin	��	20 �C	
Trikloret�n	100%	20 �C	
Trikloret�n	technically grade	20 �C	
Urea, aqueous	���33%	20 �C	
Vann	��	20 �C	
Vann, destillert	��	20 �C	
Vaselin	technically grade	20 �C	
Vin	��	20 �C	
Washing up liquids	usual	20 �C	
Xylen	��	20 �C	
Xylen	��	20 �C	
Zinkslam	��	20 �C	
��ttiksyra	3%	100 �C	
��ttiksyra	100%	20 �C	
��ttiksyra	3%	100 �C	
��ttiksyra	3% w/w	20 �C	
��ttiksyra	3%	100 �C	
��ttiksyra, vattenl.	70%	20 �C	
��ttiksyraanhydrid	��	20 �C	
��I	��	20 �C	