



PE-1000 3000x1250x80 mm svart

Artikelnr P1400308

Beständig

Delvis beständig

Ej beständig

Kemikalie	Konsentrasjon	Temp.	Beständighet
1,4-Dioxan	100	20 Å°C	
2-Hydroxipropionsyra (mjölksyra)	90	20 Å°C	
Aceton	100	20 Å°C	
Ammoniak	â€”	20 Å°C	
Ammoniumklorid	â€”	20 Å°C	
Amylalkohol	â€”	20 Å°C	
Bensen	â€”	20 Å°C	
Bensin (premium)	â€”	20 Å°C	
Borsyra	100	20 Å°C	
Bremsevåske	â€”	20 Å°C	
Brännole, aromatfritt	â€”	20 Å°C	
Butylacetat	â€”	20 Å°C	
Citronsyra	10	20 Å°C	
Cyklohexanon	100	20 Å°C	
Cyklohexen	100	20 Å°C	
Diesel	â€”	20 Å°C	
Eddik, standard	5 - 10	20 Å°C	
Etylacetat	100	20 Å°C	
Etylalkohol (etanol)	96	20 Å°C	
Fenol, vattenl.	ca. 9	20 Å°C	
Formaldehyd, vattenl.	40	20 Å°C	
Fosforsyra	50	20 Å°C	
Frostvåske	â€”	20 Å°C	
Fyringsolje	â€”	20 Å°C	
Glycerin	100	20 Å°C	
Glykol	100	20 Å°C	
Heptan	100	20 Å°C	

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Hydrogenperoksid	10	20 �C	●
Isopropylalkohol	100	20 �C	●
Kalciumklorid	��	20 �C	●
Kaliumhydroxid��sning	50	20 �C	●
Kresol	��	20 �C	●
Linolje	��	20 �C	●
Matolje	��	20 �C	●
Maursyre	10	20 �C	●
Melk	��	20 �C	●
Merkurokrom	��	20 �C	●
Metylalkohol (metanol)	100	20 �C	●
Metylenklorid	100	20 �C	●
Mineraloljer, aromatfrie	��	20 �C	●
Natriumhydroxid��sning (natronlut)	15	20 �C	●
Natriumhydroxid��sning (natronlut)	60	20 �C	●
Natriumkarbonat, vattenl.	��	20 �C	●
Natriumklorid, vattenl.	��	20 �C	●
Natriumnitrat, vattenl.	��	20 �C	●
Natriumtiosulfat	��	20 �C	●
Natriumv��tesulfit	��	20 �C	●
Nitrobensen	��	20 �C	●
Oxalsyra	��	20 �C	●
Ozon (gas)	��� 0.5 ppm	20 �C	●
Paraffinolja	100	20 �C	●
Perkloretylen	��	20 �C	●
Petroleumeter	100	20 �C	●
Propylalkohol	��	20 �C	●
Salpetersyra	10	20 �C	●
Salpetersyra	50	20 �C	●
Saltsyra	10	20 �C	●
Saltsyra (konc.)	��	20 �C	●
Silikonolje	��	20 �C	●
Svavelsyra	96	20 �C	●
Transformatorolje	��	20 �C	●

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Vann	��	20 �C	�
Xylen	��	20 �C	�
�ttiksyra	100	20 �C	�