



## PE-1000 Reg Ast 2000x1000x10 mm svart

Artikelnummer: P1200319

### 3. Kjemisk bestandighet

**A** Utmärkt **B** God **C** Begrensad **D** Ej rekommenderad

KJEMIKALIE	BETYG	KONS.	TEMP.
1,4-Dioxan	resistant	100%	
2-Hydroxipropionsyra (mjølksyra)	resistant	90%	
Aceton	resistant	100%	
Ammoniak	resistant		
Ammoniumklorid	resistant		
Amylalkohol	resistant		
Bensen	resistant		
Bensin (premium)	resistant		
Borsyra	resistant	100%	
Bremsevæske	resistant		
Bränslé, aromatfritt	resistant		
Butylacetat	resistant		
Citronsyra	resistant	10%	
Cyklohexanon	resistant	100%	
Cyklohexen	resistant	100%	
Diesel	resistant		
Eddik, standard	resistant	5 - 10%	
Etylacetat	resistant	100%	
Etylalkohol (etanol)	resistant	96%	

KJEMIKALIE	BETYG	KONS.	TEMP.
Fenol, vattenl.	resistant	ca. 9%	
Formaldehyd, vattenl.	resistant	40%	
Fosforsyra	resistant	50%	
Frostvæske	resistant		
Fyringsolja	resistant		
Glycerin	resistant	100%	
Glykol	resistant	100%	
Heptan	resistant	100%	
Hydrogenperoxid	resistant	10%	
Isopropylalkohol	resistant	100%	
Kalciumklorid	resistant		
Kaliumhydroxidlösning	resistant	50%	
Kresol	resistant		
Linolja	resistant		
Matorolja	resistant		
Maursyra	resistant	10%	
Melk	resistant		
Merkurokrom	resistant		
Metylalkohol (metanol)	resistant	100%	
Metylenklorid	partially_resistant	100%	
Mineraloljer, aromatfrie	resistant		
Natriumhydroxidlösning (natronlut)	resistant	60%	
Natriumhydroxidlösning (natronlut)	resistant	15%	
Natriumkarbonat, vattenl.	resistant		
Natriumklorid, vattenl.	resistant		
Natriumnitrat, vattenl.	resistant		
Natriumtiosulfat	resistant		
Natriumvätesulfid	resistant		
Nitrobensen	resistant		
Oxalsyra	resistant		
Ozon (gas)	resistant	≤ 0.5 ppm%	

KJEMIKALIE	BETYG	KONS.	TEMP.
Paraffinolja	resistant	100%	
Perkloretylen	partially_resistant		
Petroleumeter	resistant	100%	
Propylalkohol	resistant		
Salpetersyra	partially_resistant	50%	
Salpetersyra	resistant	10%	
Saltsyra	resistant	10%	
Saltsyra (konc.)	resistant		
Silikonolja	resistant		
Svavelsyra	partially_resistant	96%	
Transformatorolja	resistant		
Vann	resistant		
Xylen	not_resistant		
Ättiksyra	resistant	100%	