



**PET FG 2000x1000x6 mm natur**

Artikelnr P1004044

● Beständigt    ● Delvis beständigt    ● Ej beständigt

| Kemikalie              | Konsentrasjon | Temp.  | Best ndighet |
|------------------------|---------------|--------|--------------|
| 1,4-Dioxan             | 100           | 60   C |              |
| 1,4-Dioxan             | 100           | 20   C |              |
| Aceton                 | 100           | 60   C |              |
| Aceton                 | 100           | 20   C |              |
| Ammoniak               | conc.         | 20   C |              |
| Ammoniak               | conc.         | 60   C |              |
| Bensen                 |               | 60   C |              |
| Bensen                 |               | 20   C |              |
| Bensin (premium)       |               | 20   C |              |
| Bensin (premium)       |               | 60   C |              |
| Blekningsl  sning      |               | 20   C |              |
| Bremsev  lske          |               | 20   C |              |
| Bremsev  lske          |               | 60   C |              |
| Br   nsle, aromatfritt |               | 20   C |              |
| Br   nsle, aromatfritt |               | 60   C |              |
| Butylacetat            |               | 20   C |              |
| Butylacetat            |               | 60   C |              |
| Citronsyra             | 10            | 60   C |              |
| Citronsyra             | 10            | 20   C |              |
| Diesel                 |               | 60   C |              |
| Diesel                 |               | 20   C |              |
| Dietylenoxid           |               | 20   C |              |
| Dietylenoxid           |               | 20   C |              |
| Eddik, standard        | 5-10%         | 20   C |              |
| Eddik, standard        | 5-10          | 60   C |              |
| Eddik, standard        | 5-10          | 20   C |              |
| Eplejuice              |               | 20   C |              |

| Kemikalie              | Konsentrasjon | Temp.  | BestÅndighet |
|------------------------|---------------|--------|--------------|
| Eplejuice              | â€”           | 20 Å°C | ●            |
| Etylacetat             | 100           | 20 Å°C | ●            |
| Etylacetat             | 100           | 60 Å°C | ●            |
| Etylalkohol (etanol)   | 96            | 20 Å°C | ●            |
| Etylalkohol (etanol)   | 96%           | 20 Å°C | ●            |
| Etylalkohol (etanol)   | 96            | 60 Å°C | ●            |
| Etylenklorid           | 100           | 20 Å°C | ●            |
| Etylenklorid           | 100           | 60 Å°C | ●            |
| Fenol, vattenl.        | ca.9          | 20 Å°C | ●            |
| Flussyre               | 40            | 20 Å°C | ●            |
| Flussyre               | 40%           | 20 Å°C | ●            |
| Flussyre               | 40            | 60 Å°C | ●            |
| Fosforsyra             | 50            | 60 Å°C | ●            |
| Fosforsyra             | 50            | 20 Å°C | ●            |
| FrostvÃ¸ske            | â€”           | 60 Å°C | ●            |
| FrostvÃ¸ske            | â€”           | 20 Å°C | ●            |
| Fyringsolje            | â€”           | 20 Å°C | ●            |
| Fyringsolje            | â€”           | 60 Å°C | ●            |
| Glycerin               | 100           | 20 Å°C | ●            |
| Glycerin               | 100           | 60 Å°C | ●            |
| Glycerin               | 100%          | 20 Å°C | ●            |
| Glykol                 | 100           | 60 Å°C | ●            |
| Glykol                 | 100           | 20 Å°C | ●            |
| Heptan                 | 100           | 60 Å°C | ●            |
| Heptan                 | 100           | 20 Å°C | ●            |
| Hydrogenperoksid       | 10            | 60 Å°C | ●            |
| Hydrogenperoksid       | 10            | 20 Å°C | ●            |
| Isopropylalkohol       | 100%          | 20 Å°C | ●            |
| Isopropylalkohol       | 100           | 20 Å°C | ●            |
| Isopropylalkohol       | 100           | 60 Å°C | ●            |
| Kalciumklorid          | â€”           | 20 Å°C | ●            |
| Kalciumklorid          | â€”           | 60 Å°C | ●            |
| KaliumhydroxidlÅ¶sning | 50            | 60 Å°C | ●            |
| KaliumhydroxidlÅ¶sning | 50            | 20 Å°C | ●            |

| Kemikalie                          | Konsentrasjon | Temp. | Best ndighet |
|------------------------------------|---------------|-------|--------------|
| Klorbensen                         | 100           | 60  C |              |
| Klorbensen                         | 100           | 20  C |              |
| Klorbensen                         | 100%          | 20  C |              |
| Kloroform                          |               | 20  C |              |
| Kloroform                          |               | 60  C |              |
| Koldisulfid                        | 100           | 20  C |              |
| Koldisulfid                        | 100           | 60  C |              |
| Koltetraklorid                     |               | 20  C |              |
| Koltetraklorid                     |               | 60  C |              |
| Koltetraklorid                     |               | 20  C |              |
| Linolje                            |               | 60  C |              |
| Linolje                            |               | 20  C |              |
| Matolje                            |               | 20  C |              |
| Matolje                            |               | 60  C |              |
| Matolje                            |               | 20  C |              |
| Maursyre                           | 10            | 20  C |              |
| Maursyre                           | 10            | 60  C |              |
| Melk                               |               | 20  C |              |
| Melk                               |               | 60  C |              |
| Merkurokrom                        |               | 20  C |              |
| Metylalkohol (metanol)             | 100           | 20  C |              |
| Metylalkohol (metanol)             | 100           | 60  C |              |
| Metylalkohol (metanol)             | 100%          | 20  C |              |
| Metylenklorid                      | 100           | 60  C |              |
| Metylenklorid                      | 100           | 20  C |              |
| Metyletylketon (MEK)               | 100           | 20  C |              |
| Metyletylketon (MEK)               | 100           | 60  C |              |
| Mineraloljer, aromatfrie           |               | 20  C |              |
| Mineraloljer, aromatfrie           |               | 60  C |              |
| Natriumhydroxidl sning (natronlut) | 60            | 20  C |              |
| Natriumhydroxidl sning (natronlut) | 15            | 20  C |              |
| Natriumhydroxidl sning (natronlut) | 15            | 60  C |              |
| Natriumhydroxidl sning (natronlut) | 60            | 60  C |              |
| Natriumkarbonat, vattenl sning     |               | 60  C |              |

| Kemikalie                 | Konsentrasjon | Temp.  | Best ndighet |
|---------------------------|---------------|--------|--------------|
| Natriumkarbonat, vattenl. | â€”           | 20 Â°C | ●            |
| Natriumklorid, vattenl.   | â€”           | 20 Â°C | ●            |
| Natriumklorid, vattenl.   | â€”           | 60 Â°C | ●            |
| Natriumnitrat, vattenl.   | â€”           | 20 Â°C | ●            |
| Natriumtiosulfat          | â€”           | 20 Â°C | ●            |
| Natriumv  tesulfit        | â€”           | 60 Â°C | ●            |
| Natriumv  tesulfit        | â€”           | 20 Â°C | ●            |
| Natriumv  tesulfit        | â€”           | 20 Â°C | ●            |
| Paraffinolje              | 100           | 20 Â°C | ●            |
| Paraffinolje              | 100           | 60 Â°C | ●            |
| Perkloretylen             | â€”           | 60 Â°C | ●            |
| Perkloretylen             | â€”           | 20 Â°C | ●            |
| Petroleum                 | 100           | 20 Â°C | ●            |
| Petroleum                 | 100%          | 20 Â°C | ●            |
| Petroleumeter             | 100%          | 20 Â°C | ●            |
| Petroleumeter             | 100           | 60 Â°C | ●            |
| Petroleumeter             | 100           | 20 Â°C | ●            |
| Propylalkohol             | â€”           | 60 Â°C | ●            |
| Propylalkohol             | â€”           | 20 Â°C | ●            |
| Salpetersyra              | 50            | 60 Â°C | ●            |
| Salpetersyra              | 10            | 60 Â°C | ●            |
| Salpetersyra              | 10            | 20 Â°C | ●            |
| Salpetersyra              | 10%           | 20 Â°C | ●            |
| Salpetersyra              | 50            | 20 Â°C | ●            |
| Saltsyra                  | 10            | 20 Â°C | ●            |
| Saltsyra                  | 10            | 60 Â°C | ●            |
| Saltsyra                  | conc.         | 20 Â°C | ●            |
| Saltsyra                  | conc.         | 60 Â°C | ●            |
| Saltsyra (konc.)          | conc.         | 20 Â°C | ●            |
| Silikonolje               | â€”           | 60 Â°C | ●            |
| Silikonolje               | â€”           | 20 Â°C | ●            |
| Svavelsyra                | 96            | 60 Â°C | ●            |
| Svavelsyra                | 96            | 20 Â°C | ●            |
| Tetrahydrofuran (THF)     | 100           | 20 Â°C | ●            |
| Tetrahydrofuran (THF)     | 100           | 60 Â°C | ●            |

| Kemikalie             | Konsentrasjon | Temp. | Best ndighet |
|-----------------------|---------------|-------|--------------|
| Toluen                | 100%          | 20  C | ●            |
| Toluen                | 100           | 20  C | ●            |
| Toluen                | 100           | 60  C | ●            |
| Transformatorolje     |               | 20  C | ●            |
| Transformatorolje     |               | 60  C | ●            |
| Trikloret n           | 100           | 60  C | ●            |
| Trikloret n           | 100           | 20  C | ●            |
| Vann                  |               | 20  C | ●            |
| Vann                  |               | 60  C | ●            |
| V  tesulfid, vattenl. |               | 20  C | ●            |
| Xylen                 |               | 20  C | ●            |
| Xylen                 |               | 60  C | ●            |
|   ttiksyra            | 100           | 60  C | ●            |
|   ttiksyra            | 100           | 20  C | ●            |
|   ttiksyra            | 100%          | 20  C | ●            |