



Artikelnr P1005876

● Beständigt ● Delvis beständigt ● Ej beständigt

Kemikalie	Konsentrasjon	Temp.	BestÅndighet
1,4-Dioxan	100%	20 Å°C	●
2-Hydroxiopionsyra (mjÅllksyra)	90%	20 Å°C	●
Aceton	100%	20 Å°C	●
Ammoniak	conc.	20 Å°C	●
Ammoniumklorid	â€”	20 Å°C	●
Amylalkohol	â€”	20 Å°C	●
Bensen	â€”	20 Å°C	●
Bensin (premium)	â€”	20 Å°C	●
BlekningslÅsning	12.5 cl	20 Å°C	●
Borsyra	100%	20 Å°C	●
BremsevÅlske	â€”	20 Å°C	●
BrÅnsle, aromatfritt	â€”	20 Å°C	●
Butylacetat	â€”	20 Å°C	●
Citronsyra	10%	20 Å°C	●
Cyklohexanon	100%	20 Å°C	●
Cyklohexen	100%	20 Å°C	●
Diesel	â€”	20 Å°C	●
Dietylenoxid	â€”	20 Å°C	●
Eddik, standard	5-10%	20 Å°C	●
Eplejuice	â€”	20 Å°C	●
Etylacetat	100%	20 Å°C	●
Etylalkohol (etanol)	96%	20 Å°C	●
Fenol, vattenl.	ca. 9%	20 Å°C	●
Flussyre	40%	20 Å°C	●
Formaldehyd, vattenl.	40%	20 Å°C	●
Fosforsyra	50%	20 Å°C	●
FrostvÅlske	â€”	20 Å°C	●

[illegible]

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Propylalkohol	��	20 �C	�
Salpetersyra	10%	20 �C	�
Salpetersyra (50%)	50%	20 �C	�
Saltsyra	10%	20 �C	�
Saltsyra (konc.)	conc.	20 �C	�
Silikonolje	��	20 �C	�
Svavelsyra	96%	20 �C	�
Tetrahydrofuran (THF)	100%	20 �C	�
Toluen	100%	20 �C	�
Transformatorolje	��	20 �C	�
Trikloreten	100%	20 �C	�
Vann	��	20 �C	�
V��tesulfid, vattenl.	��	20 �C	�
Xylen	��	20 �C	�
��ttiksyra	100%	20 �C	�