

## POM C FG 28/15x1000 mm trafikklå

Artikkelnr P1007569

● Bestandig
 ● Delvis bestandig
 ● Ikke bestandig

| Kjemikalie                       | Konsentrasjon | Bestand. |
|----------------------------------|---------------|----------|
| 1,4-Dioxan                       | 100%          | ●        |
| 2-Hydroxipropionsyra (mjølksyra) | 90%           | ●        |
| Aceton                           | 100%          | ●        |
| Ammoniak                         | conc.         | ●        |
| Ammoniumklorid                   | —             | ●        |
| Amylalkohol                      | —             | ●        |
| Bensen                           | —             | ●        |
| Bensin (premium)                 | —             | ●        |
| Blekningsløsning                 | 12.5 cl       | ●        |
| Borsyra                          | 100%          | ●        |
| Bremsevæske                      | —             | ●        |
| Bränsle, aromatfritt             | —             | ●        |
| Butylacetat                      | —             | ●        |
| Citronsyra                       | 10%           | ●        |
| Cyklohexanon                     | 100%          | ●        |
| Cyklohexen                       | 100%          | ●        |
| Diesel                           | —             | ●        |
| Dietylenoxid                     | —             | ●        |
| Eddik, standard                  | 5-10%         | ●        |
| Eplejuice                        | —             | ●        |
| Etylacetat                       | 100%          | ●        |
| Etylalkohol (etanol)             | 96%           | ●        |
| Fenol, vattenl.                  | ca. 9%        | ●        |
| Flussyre                         | 40%           | ●        |
| Formaldehyd, vattenl.            | 40%           | ●        |

| Kjemikalie                | Konsentrasjon | Bestand. |
|---------------------------|---------------|----------|
| Fosforsyra                | 50%           | ●        |
| Frostvæske                | —             | ●        |
| Fyringsolje               | —             | ●        |
| Glycerin                  | 100%          | ●        |
| Glykol                    | 100%          | ●        |
| Heptan                    | 100%          | ●        |
| Hydrogenperoksid          | 10%           | ●        |
| Isopropylalkohol          | 100%          | ●        |
| Kalciumklorid             | —             | ●        |
| Kaliumhydroxidløsning     | 50%           | ●        |
| Klorbensen                | 100%          | ●        |
| Kloroform                 | —             | ●        |
| Koldisulfid               | 100%          | ●        |
| Koltetraklorid            | —             | ●        |
| Linolje                   | —             | ●        |
| Matolje                   | —             | ●        |
| Maursyre                  | 10%           | ●        |
| Melk                      | —             | ●        |
| Merkurokrom               | —             | ●        |
| Metylalkohol (metanol)    | 100%          | ●        |
| Metylenklorid             | 100%          | ●        |
| Metyletylketon (MEK)      | 100%          | ●        |
| Mineraloljer (aromatfrie) | —             | ●        |
| Natriumkarbonat, vattenl. | —             | ●        |
| Natriumklorid, vattenl.   | —             | ●        |
| Natriumnitrat, vattenl.   | —             | ●        |
| Natriumvâtesulfit         | —             | ●        |
| Natronlut (15%)           | 15%           | ●        |
| Natronlut (60%)           | 60%           | ●        |
| Nitrobensen               | —             | ●        |
| Oxalsyra                  | —             | ●        |
| Ozon (gas)                | ≤0.5 ppm      | ●        |

| Kjemikalie            | Konsentrasjon | Bestand. |
|-----------------------|---------------|----------|
| Paraffinolja          | 100%          | ●        |
| Perkloretylen         | —             | ●        |
| Petroleum             | 100%          | ●        |
| Petroleumeter         | 100%          | ●        |
| Propylalkohol         | —             | ●        |
| Salpetersyra          | 10%           | ●        |
| Salpetersyra (50%)    | 50%           | ●        |
| Saltsyra              | 10%           | ●        |
| Saltsyra (konc.)      | conc.         | ●        |
| Silikonolje           | —             | ●        |
| Svavelsyra            | 96%           | ●        |
| Tetrahydrofuran (THF) | 100%          | ●        |
| Toluen                | 100%          | ●        |
| Transformatorolje     | —             | ●        |
| Trikloretan           | 100%          | ●        |
| Vann                  | —             | ●        |
| Vätesulfid, vattenl.  | —             | ●        |
| Xylen                 | —             | ●        |
| Ättiksyra             | 100%          | ●        |