



POM C FG 70/50x3000 mm marinbl 

Artikelnr P1007320

Best ndig

Delvis best ndig

Ej best ndig

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
1,4-Dioxan	100%	20 �C	
2-Hydroxipropionsyra (mj�lksyra)	90%	20 �C	
Aceton	100%	20 �C	
Ammoniak	conc.	20 �C	
Ammoniumklorid	��	20 �C	
Amylalkohol	��	20 �C	
Bensen	��	20 �C	
Bensin (premium)	��	20 �C	
Blekningsl�sning	12.5 cl	20 �C	
Borsyra	100%	20 �C	
Bremsev�jske	��	20 �C	
Br�nsle, aromatfritt	��	20 �C	
Butylacetat	��	20 �C	
Citronsyra	10%	20 �C	
Cyklohexanon	100%	20 �C	
Cyklohexen	100%	20 �C	
Diesel	��	20 �C	
Dietylenoxid	��	20 �C	
Eddik, standard	5-10%	20 �C	
Eplejuice	��	20 �C	
Etylacetat	100%	20 �C	
Etylalkohol (etanol)	96%	20 �C	
Fenol, vattenl.	ca. 9%	20 �C	
Flussyre	40%	20 �C	
Formaldehyd, vattenl.	40%	20 �C	
Fosforsyra	50%	20 �C	
Frostv�jske	��	20 �C	

Kemikalie	Konsentrasjon	Temp.	BestÅndighet
Fyringsolje	â€”	20 Å°C	●
Glycerin	100%	20 Å°C	●
Glykol	100%	20 Å°C	●
Heptan	100%	20 Å°C	●
Hydrogenperoksid	10%	20 Å°C	●
Isopropylalkohol	100%	20 Å°C	●
Kalciumklorid	â€”	20 Å°C	●
KaliumhydroxidÅtsning	50%	20 Å°C	●
Klorbensen	100%	20 Å°C	●
Kloroform	â€”	20 Å°C	●
Koldisulfid	100%	20 Å°C	●
Koltetraklorid	â€”	20 Å°C	●
Linolje	â€”	20 Å°C	●
Matolje	â€”	20 Å°C	●
Maurisyre	10%	20 Å°C	●
Melk	â€”	20 Å°C	●
Merkurokrom	â€”	20 Å°C	●
Metylalkohol (metanol)	100%	20 Å°C	●
Metylenklorid	100%	20 Å°C	●
Metyletylketon (MEK)	100%	20 Å°C	●
Mineraloljer (aromatfrie)	â€”	20 Å°C	●
Natriumkarbonat, vattenl.	â€”	20 Å°C	●
Natriumklorid, vattenl.	â€”	20 Å°C	●
Natriumnitrat, vattenl.	â€”	20 Å°C	●
NatriumvÃtesulfitt	â€”	20 Å°C	●
Natronlut (15%)	15%	20 Å°C	●
Natronlut (60%)	60%	20 Å°C	●
Nitrobensen	â€”	20 Å°C	●
Oxalsyra	â€”	20 Å°C	●
Ozon (gas)	â‰¤0.5 ppm	20 Å°C	●
Paraffinolja	100%	20 Å°C	●
Perkloretylen	â€”	20 Å°C	●
Petroleum	100%	20 Å°C	●
Petroleometer	100%	20 Å°C	●

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Propylalkohol	��	20 �C	�
Salpetersyra	10%	20 �C	�
Salpetersyra (50%)	50%	20 �C	�
Saltsyra	10%	20 �C	�
Saltsyra (konc.)	conc.	20 �C	�
Silikonolje	��	20 �C	�
Svavelsyra	96%	20 �C	�
Tetrahydrofuran (THF)	100%	20 �C	�
Toluen	100%	20 �C	�
Transformatorolje	��	20 �C	�
Trikloreten	100%	20 �C	�
Vann	��	20 �C	�
V��tesulfid, vattenl.	��	20 �C	�
Xylen	��	20 �C	�
��ttiksyra	100%	20 �C	�