

POM CGL 1000x1000x45 mm blå

Artikelnr P1008120

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konsentrasjon	Temp.	Beständighet
1,4-Dioxan	100%	20 °C	●
2-Hydroxypropionic Acid	90%	20 °C	●
Acetic Acid	100%	20 °C	●
Aceton	100%	20 °C	●
Ammoniak	conc.	20 °C	●
Ammonium Chloride	-	20 °C	●
Amyl Alcohol	-	20 °C	●
Apple Juice	-	20 °C	●
Bensen	-	20 °C	●
Bleaching Solution	12.5 cl	20 °C	●
Boric Acid	100%	20 °C	●
Brake Fluid	-	20 °C	●
Bränsle, aromatfritt	-	20 °C	●
Butyl Acetate	-	20 °C	●
Calcium Chloride	-	20 °C	●
Carbon Disulfide	100%	20 °C	●
Carbon Tetrachloride	-	20 °C	●
Citric Acid	10%	20 °C	●
Cyklohexanon	100%	20 °C	●
Cyklohexen	100%	20 °C	●
Diesel Fuel	-	20 °C	●
Diethylene Oxide	-	20 °C	●
Eddik, standard	5-10%	20 °C	●
Ethyl Acetate	100%	20 °C	●
Ethyl Alcohol	96%	20 °C	●
Ethylene Chloride	100%	20 °C	●

Kemikalie	Konsentrasjon	Temp.	Beständighet
Fenol, vattenl.	ca. 9%	20 °C	
Food Oil	-	20 °C	
Formaldehyd, vattenl.	40%	20 °C	
Formic Acid	10%	20 °C	
Frost Protection Agent	-	20 °C	
Glycerin	100%	20 °C	
Glykol	100%	20 °C	
Heating Oil	-	20 °C	
Heptan	100%	20 °C	
Hydrochloric Acid	10%	20 °C	
Hydrochloric Acid (concentrated)	conc.	20 °C	
Hydrofluoric Acid	40%	20 °C	
Hydrogen Peroxide	10%	20 °C	
Hydrogen Sulfide, aqueous solution	-	20 °C	
Isopropyl Alcohol	100%	20 °C	
Klor (gas)	100%	20 °C	
Klorbensen	100%	20 °C	
Kloroform	-	20 °C	
Kresol	-	20 °C	
Linseed Oil	-	20 °C	
Melk	-	20 °C	
Merkurokrom	-	20 °C	
Methyl Alcohol	100%	20 °C	
Methyl Ethyl Ketone (MEK)	100%	20 °C	
Methylene Chloride	100%	20 °C	
Mineral Oils (aromatic free)	-	20 °C	
Nitric Acid	10%	20 °C	
Nitric Acid (50%)	50%	20 °C	
Nitrobensen	-	20 °C	
Oxalic Acid	-	20 °C	
Ozone Gas	≤0.5 ppm	20 °C	
Paraffine Oil	100%	20 °C	
Perkloretylen	-	20 °C	
Petroleum	100%	20 °C	

Kemikalie	Konsentrasjon	Temp.	Beständighet
Petroleum Ether	100%	20 °C	
Phosphoric Acid	50%	20 °C	
Potassium Hydroxide liquor	50%	20 °C	
Premium Fuel	-	20 °C	
Propyl Alcohol	-	20 °C	
Pyridin	-	20 °C	
Silicone Oil	-	20 °C	
Sodium Carbonate, aqueous	-	20 °C	
Sodium Chloride, aqueous	-	20 °C	
Sodium Hydrogen Sulfite	-	20 °C	
Sodium Hydroxide liquor (15%)	15%	20 °C	
Sodium Hydroxide liquor (60%)	60%	20 °C	
Sodium Nitrate, aqueous	-	20 °C	
Sodium Thiosulfate	-	20 °C	
Sulfuric Acid	96%	20 °C	
Tetrahydrofuran, THF	100%	20 °C	
Toluen	100%	20 °C	
Transformer Oil	-	20 °C	
Trikloreten	100%	20 °C	
Vann	-	20 °C	
Xylen	-	20 °C	