

PP-C 2440x1220x4,5 mm svart

Artikelnr P2201579

1. Tekniskt datablad

Egenskap	VÄrde	Enhet	Standard
Tetthet	0.9	g/cm ³	DIN EN ISO 1183-1
StreckgrenseSpänning	24	MPa	DIN EN ISO 527
Elastisitetsmodul (trek)	1241.2	MPa	DIN EN ISO 527
Brottsdeformasjon	50	%	DIN EN ISO 527
Smeltepunkt	164	Å°C	ISO 11357-3
Maksimal drifttemperatur (kortvarig)	116	Å°C	
Maksimal driftstemperatur	75	Å°C	
Minstemperatur	-23	Å°C	
Vicat-mykningstemperatur (VST/B/50)	87	Å°C	DIN EN ISO 306
Dielektrisk Styrke	40	kV/mm	IEC 60243
VolumResistivitet	10 ¹⁴ Å	Î©Å·cm	DIN EN 62631-3-1
Dielektrisk konstant (1 MHz)	2.48	-	IEC 60250
Dielektrisk dissipasjonsfaktor (1 MHz)	0.0	-	IEC 60250
Dielektrisk tapfaktor (100 Hz)	0.0	-	IEC 60250
Termisk konduktivitet	0.2	W/(mÅ·K)	DIN 52612-1
Overflatemotstand	10 ¹⁴ Å	Î©	DIN EN 62631-3-2
SammenligningskrypstrÅmsindeks (CTI)	600	V	IEC 60112
Fuktabsorpsjon til metning	0.1	%	DIN EN ISO 62
Vannabsorpsjon til metning	0.1	%	DIN EN ISO 62
SkÅret slagfasthet (Charpy)	4	kJ/mÅ ²	DIN EN ISO 179
Termisk utvidelseskoeffisient	0.0	10 ⁴ Å/K	DIN 53752
Hardhet Shore D	67.25	Å° Shore D	DIN EN ISO 868
Kuletrykkshardhet	50	MPa	DIN EN ISO 2039-1

2. Kemisk bestÅndighet

● BestÅndig ● Delvis bestÅndig ● Ej bestÅndig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Aceton	100	●
Ammoniak	â€”	●
Ammonium Chloride	â€”	●
Amyl Alcohol	â€”	●
Apple Juice	â€”	●
Bensen	â€”	●
Bleaching Solution	â€”	●
Boric Acid	100	●
Brake Fluid	â€”	●
Br�nsle, aromatfritt	â€”	●
Butyl Acetate	â€”	●
Calcium Chloride	â€”	●
Carbon Disulfide	100	●
Carbon Tetrachloride	â€”	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	â€”	●
Diethylene Oxide	â€”	●
Eddik, standard	5 - 10	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol, vattenl.	ca. 9	●
Food Oil	â€”	●
Formaldehyd, vattenl.	40	●
Formic Acid	10	●
Frost Protection Agent	â€”	●
Glycerin	100	●
Glykol	100	●
Heating Oil	â€”	●
Heptan	100	●

Kemikalie	Konc.	Resultat
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	â€”	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide, aqueous solution	â€”	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	â€”	●
Kresol	â€”	●
Linseed Oil	â€”	●
Melk	â€”	●
Merkurokrom	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	â€”	●
Nitric Acid	50	●
Nitric Acid	10	●
Nitrobensen	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â‰ƒ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridin	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate, aqueous	â€”	●
Sodium Chloride, aqueous	â€”	●
Sodium Hydrogen Sulfite	â€”	●

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor	60	●
Sodium Nitrate, aqueous	â€”	●
Sodium Thiosulfate	â€”	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluen	100	●
Transformer Oil	â€”	●
Trikloretan	100	●
Vann	â€”	●
Xylen	â€”	●