



# PP-C 3000x1500x10 mm grÅ

Artikelnr P2201573

## 1. Tekniskt datablad

| Egenskap                               | Värde     | Enhet     | Standard          |
|----------------------------------------|-----------|-----------|-------------------|
| Tetthet                                | 0.9       | g/cm³     | DIN EN ISO 1183-1 |
| Streckgren                             | 24        | MPa       | DIN EN ISO 527    |
| Elastisitetsmodul (trek)               | 1241.2    | MPa       | DIN EN ISO 527    |
| Brottsdeformasjon                      | 50        | %         | DIN EN ISO 527    |
| Smeltepunkt                            | 164       | °C        | ISO 11357-3       |
| Maksimal drifttemperatur (kortvarig)   | 116       | °C        |                   |
| Maksimal drifttemperatur               | 75        | °C        |                   |
| Minstemperatur                         | -23       | °C        |                   |
| Vicat-mykningstemperatur (VST/B/50)    | 87        | °C        | DIN EN ISO 306    |
| Dielektrisk styrke                     | 40        | kV/mm     | IEC 60243         |
| Volumresistivitet                      | 10¹¹ Ω·cm | Ω·cm      | DIN EN 62631-3-1  |
| Dielektrisk konstant (1 MHz)           | 2.48      | -         | IEC 60250         |
| Dielektrisk dissipasjonsfaktor (1 MHz) | 0.0       | -         | IEC 60250         |
| Dielektrisk tapfaktor (100 Hz)         | 0.0       | -         | IEC 60250         |
| Termisk konduktivitet                  | 0.2       | W/(m·K)   | DIN 52612-1       |
| Overflatemotstand                      | 10¹¹ Ω    | Ω         | DIN EN 62631-3-2  |
| Sammenligningskrypsrømsindeks (CTI)    | 600       | V         | IEC 60112         |
| Fuktabsorpsjon til metning             | 0.1       | %         | DIN EN ISO 62     |
| Vannabsorpsjon til metning             | 0.1       | %         | DIN EN ISO 62     |
| Skårret slagfasthet (Charpy)           | 4         | kJ/m²     | DIN EN ISO 179    |
| Termisk utvidelseskoeffisient          | 0.0       | 10⁻⁵ /K   | DIN 53752         |
| Hardhet Shore D                        | 67.25     | ° Shore D | DIN EN ISO 868    |
| Kuletrykkshardhet                      | 50        | MPa       | DIN EN ISO 2039-1 |

## 2. Kjemisk bestandighet

Beständig Delvis beständig Ej beständig

| Kemikalie               | Konc.  | Resultat    |
|-------------------------|--------|-------------|
| 1,4-Dioxan              | 100    | <div></div> |
| 2-Hydroxypropionic Acid | 90     | <div></div> |
| Acetic Acid             | 100    | <div></div> |
| Aceton                  | 100    | <div></div> |
| Ammoniak                | â€”    | <div></div> |
| Ammonium Chloride       | â€”    | <div></div> |
| Amyl Alcohol            | â€”    | <div></div> |
| Apple Juice             | â€”    | <div></div> |
| Bensen                  | â€”    | <div></div> |
| Bleaching Solution      | â€”    | <div></div> |
| Boric Acid              | 100    | <div></div> |
| Brake Fluid             | â€”    | <div></div> |
| Br  nsle, aromatfritt   | â€”    | <div></div> |
| Butyl Acetate           | â€”    | <div></div> |
| Calcium Chloride        | â€”    | <div></div> |
| Carbon Disulfide        | 100    | <div></div> |
| Carbon Tetrachloride    | â€”    | <div></div> |
| Citric Acid             | 10     | <div></div> |
| Cyklohexanon            | 100    | <div></div> |
| Cyklohexen              | 100    | <div></div> |
| Diesel Fuel             | â€”    | <div></div> |
| Diethylene Oxide        | â€”    | <div></div> |
| Eddik, standard         | 5 - 10 | <div></div> |
| Ethyl Acetate           | 100    | <div></div> |
| Ethyl Alcohol           | 96     | <div></div> |
| Ethylene Chloride       | 100    | <div></div> |
| Fenol, vattenl.         | ca. 9  | <div></div> |
| Food Oil                | â€”    | <div></div> |
| Formaldehyd, vattenl.   | 40     | <div></div> |
| Formic Acid             | 10     | <div></div> |
| Frost Protection Agent  | â€”    | <div></div> |
| Glycerin                | 100    | <div></div> |
| Glykol                  | 100    | <div></div> |
| Heating Oil             | â€”    | <div></div> |
| Heptan                  | 100    | <div></div> |

| Kemikalie                          | Konc.      | Resultat |
|------------------------------------|------------|----------|
| Hydrochloric Acid                  | 10         | ●        |
| Hydrochloric Acid (concentrated)   | â€”        | ●        |
| Hydrofluoric Acid                  | 40         | ●        |
| Hydrogen Peroxide                  | 10         | ●        |
| Hydrogen Sulfide, aqueous solution | â€”        | ●        |
| Isopropyl Alcohol                  | 100        | ●        |
| Klor (gas)                         | 100        | ●        |
| Klorbensen                         | 100        | ●        |
| Kloroform                          | â€”        | ●        |
| Kresol                             | â€”        | ●        |
| Linseed Oil                        | â€”        | ●        |
| Melk                               | â€”        | ●        |
| Merkurokrom                        | â€”        | ●        |
| Methyl Alcohol                     | 100        | ●        |
| Methyl Ethyl Ketone (MEK)          | 100        | ●        |
| Methylene Chloride                 | 100        | ●        |
| Mineral Oils (aromatic free)       | â€”        | ●        |
| Nitric Acid                        | 50         | ●        |
| Nitric Acid                        | 10         | ●        |
| Nitrobensen                        | â€”        | ●        |
| Oxalic Acid                        | â€”        | ●        |
| Ozone Gas                          | â‰¥0.5 ppm | ●        |
| Paraffine Oil                      | 100        | ●        |
| Perkloretylen                      | â€”        | ●        |
| Petroleum                          | 100        | ●        |
| Petroleum Ether                    | 100        | ●        |
| Phosphoric Acid                    | 50         | ●        |
| Potassium Hydroxide liquor         | 50         | ●        |
| Premium Fuel                       | â€”        | ●        |
| Propyl Alcohol                     | â€”        | ●        |
| Pyridin                            | â€”        | ●        |
| Silicone Oil                       | â€”        | ●        |
| Sodium Carbonate, aqueous          | â€”        | ●        |
| Sodium Chloride, aqueous           | â€”        | ●        |
| Sodium Hydrogen Sulfite            | â€”        | ●        |

| Kemikalie               | Konc. | Resultat |
|-------------------------|-------|----------|
| Sodium Hydroxide liquor | 15    | ●        |
| Sodium Hydroxide liquor | 60    | ●        |
| Sodium Nitrate, aqueous | â€”   | ●        |
| Sodium Thiosulfate      | â€”   | ●        |
| Sulfuric Acid           | 96    | ●        |
| Tetrahydrofuran (THF)   | 100   | ●        |
| Toluen                  | 100   | ●        |
| Transformer Oil         | â€”   | ●        |
| Trikloreten             | 100   | ●        |
| Vann                    | â€”   | ●        |
| Xylen                   | â€”   | ●        |