



ABS 90x1000 mm natur

Artikelnr P1000017

Beständig Delvis beständig Ej beständig

Kemikalie	Konsentrasjon	Temp.	Beständighet
1,4-Dioxan	100	20 Å°C	
2-Hydroxipropionsyra (mjölksyra)	90	20 Å°C	
Aceton	100	20 Å°C	
Ammoniak	â€	20 Å°C	
Ammoniumklorid	â€	20 Å°C	
Amylalkohol	â€	20 Å°C	
Bensen	â€	20 Å°C	
Bensin (premium)	â€	20 Å°C	
Bremseväske	â€	20 Å°C	
Bränsle, aromatfritt	â€	20 Å°C	
Butylacetat	â€	20 Å°C	
Citronsyra	10	20 Å°C	
Cyklohexanon	100	20 Å°C	
Cyklohexen	100	20 Å°C	
Diesel	â€	20 Å°C	
Eddik (standard)	5-10	20 Å°C	
Eplejuice	â€	20 Å°C	
Etylacetat	100	20 Å°C	
Etylalkohol (etanol)	96	20 Å°C	
Etylenklorid	100	20 Å°C	
Fenol, vattenl.	9	20 Å°C	
Flussyre	40	20 Å°C	
Formaldehyd, vattenl.	40	20 Å°C	
Fosforsyra	50	20 Å°C	
Frostväske	â€	20 Å°C	
Fyringsolja	â€	20 Å°C	
Glycerin	100	20 Å°C	

Kemikalie		Konsentrasjon	Temp.	Best�ndighet
Glykol	100	20 �C		●
Heptan	100	20 �C		●
Hydrogenperoksid	10	20 �C		●
Isopropylalkohol	100	20 �C		●
Kalciumklorid	��	20 �C		●
Kaliumhydroxid��sning	50	20 �C		●
Klorbensen	100	20 �C		●
Klorgas	100	20 �C		●
Kloroform	��	20 �C		●
Koldisulfid	100	20 �C		●
Koltetraklorid	��	20 �C		●
Kresol	��	20 �C		●
Linolje	��	20 �C		●
Matolje	��	20 �C		●
Maursyre	10	20 �C		●
Melk	��	20 �C		●
Merkurokrom	��	20 �C		●
Metylalkohol (metanol)	100	20 �C		●
Metylenklorid	100	20 �C		●
Metyletylketon (MEK)	100	20 �C		●
Natriumhydroxid��sning (natronlut)	60	20 �C		●
Natriumhydroxid��sning (natronlut)	15	20 �C		●
Natriumkarbonat, vattenl.	��	20 �C		●
Natriumklorid, vattenl.	��	20 �C		●
Natriumnitrat, vattenl.	��	20 �C		●
Natriumtiosulfat	��	20 �C		●
Natriumv��tesulfit	��	20 �C		●
Nitrobensen	��	20 �C		●
Oxalsyra	��	20 �C		●
Ozon (gas)	��	20 �C		●
Paraffinolja	100	20 �C		●
Perkloretylen	��	20 �C		●
Petroleum	100	20 �C		●
Petroleumeter	100	20 �C		●

