



PE-1000 125x1000 mm grön

Artikelnr P2200831

● Beständig

● Delvis beständig

● Ej beständig

Kemikalie	Konsentrasjon	Temp.	Beständighet
1,4-Dioxan	100	20 Å°C	●
2-Hydroxipropionsyra (mjölksyra)	90	20 Å°C	●
Aceton	100	20 Å°C	●
Ammoniak	â€”	20 Å°C	●
Ammoniumklorid	â€”	20 Å°C	●
Amylalkohol	â€”	20 Å°C	●
Bensen	â€”	20 Å°C	●
Bensin (premium)	â€”	20 Å°C	●
Borsyra	100	20 Å°C	●
Bremsevåske	â€”	20 Å°C	●
Brännole, aromatfritt	â€”	20 Å°C	●
Butylacetat	â€”	20 Å°C	●
Citronsyra	10	20 Å°C	●
Cyklohexanon	100	20 Å°C	●
Cyklohexen	100	20 Å°C	●
Diesel	â€”	20 Å°C	●
Eddik, standard	5 - 10	20 Å°C	●
Etylacetat	100	20 Å°C	●
Etylalkohol (etanol)	96	20 Å°C	●
Fenol, vattenl.	ca. 9	20 Å°C	●
Formaldehyd, vattenl.	40	20 Å°C	●
Fosforsyra	50	20 Å°C	●
Frostvåske	â€”	20 Å°C	●
Fyringsolje	â€”	20 Å°C	●
Glycerin	100	20 Å°C	●
Glykol	100	20 Å°C	●
Heptan	100	20 Å°C	●

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Hydrogenperoksid	10	20 �C	�
Isopropylalkohol	100	20 �C	�
Kalciumklorid	��	20 �C	�
Kaliumhydroxid��sning	50	20 �C	�
Kresol	��	20 �C	�
Linolje	��	20 �C	�
Matolje	��	20 �C	�
Maursyre	10	20 �C	�
Melk	��	20 �C	�
Merkurokrom	��	20 �C	�
Metylalkohol (metanol)	100	20 �C	�
Metylenklorid	100	20 �C	�
Mineraloljer, aromatfrie	��	20 �C	�
Natriumhydroxid��sning (natronlut)	15	20 �C	�
Natriumhydroxid��sning (natronlut)	60	20 �C	�
Natriumkarbonat, vattenl.	��	20 �C	�
Natriumklorid, vattenl.	��	20 �C	�
Natriumnitrat, vattenl.	��	20 �C	�
Natriumtiosulfat	��	20 �C	�
Natriumv��tesulfit	��	20 �C	�
Nitrobensen	��	20 �C	�
Oxalsyra	��	20 �C	�
Ozon (gas)	��� 0.5 ppm	20 �C	�
Paraffinolja	100	20 �C	�
Perkloretylen	��	20 �C	�
Petroleumeter	100	20 �C	�
Propylalkohol	��	20 �C	�
Salpetersyra	50	20 �C	�
Salpetersyra	10	20 �C	�
Saltsyra	10	20 �C	�
Saltsyra (konc.)	��	20 �C	�
Silikonolje	��	20 �C	�
Svavelsyra	96	20 �C	�
Transformatorolje	��	20 �C	�

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Vann	��	20 �C	�
Xylen	��	20 �C	�
�ttiksyra	100	20 �C	�