



# PE-1000 40x2000 mm grön

Artikelnr P1200237

● Beständig

● Delvis beständig

● Ej beständig

| Kemikalie                        | Konsentrasjon | Temp.  | Beständighet |
|----------------------------------|---------------|--------|--------------|
| 1,4-Dioxan                       | 100           | 20 Å°C | ●            |
| 2-Hydroxipropionsyra (mjölksyra) | 90            | 20 Å°C | ●            |
| Aceton                           | 100           | 20 Å°C | ●            |
| Ammoniak                         | â€”           | 20 Å°C | ●            |
| Ammoniumklorid                   | â€”           | 20 Å°C | ●            |
| Amylalkohol                      | â€”           | 20 Å°C | ●            |
| Bensen                           | â€”           | 20 Å°C | ●            |
| Bensin (premium)                 | â€”           | 20 Å°C | ●            |
| Borsyra                          | 100           | 20 Å°C | ●            |
| Bremsevåske                      | â€”           | 20 Å°C | ●            |
| Brännole, aromatfritt            | â€”           | 20 Å°C | ●            |
| Butylacetat                      | â€”           | 20 Å°C | ●            |
| Citronsyra                       | 10            | 20 Å°C | ●            |
| Cyklohexanon                     | 100           | 20 Å°C | ●            |
| Cyklohexen                       | 100           | 20 Å°C | ●            |
| Diesel                           | â€”           | 20 Å°C | ●            |
| Eddik, standard                  | 5 - 10        | 20 Å°C | ●            |
| Etylacetat                       | 100           | 20 Å°C | ●            |
| Etylalkohol (etanol)             | 96            | 20 Å°C | ●            |
| Fenol, vattenl.                  | ca. 9         | 20 Å°C | ●            |
| Formaldehyd, vattenl.            | 40            | 20 Å°C | ●            |
| Fosforsyra                       | 50            | 20 Å°C | ●            |
| Frostvåske                       | â€”           | 20 Å°C | ●            |
| Fyringsolje                      | â€”           | 20 Å°C | ●            |
| Glycerin                         | 100           | 20 Å°C | ●            |
| Glykol                           | 100           | 20 Å°C | ●            |
| Heptan                           | 100           | 20 Å°C | ●            |

| Kemikalie                          | Konsentrasjon | Temp. | Best ndighet |
|------------------------------------|---------------|-------|--------------|
| Hydrogenperoksid                   | 10            | 20  C | ●            |
| Isopropylalkohol                   | 100           | 20  C | ●            |
| Kalciumklorid                      |               | 20  C | ●            |
| Kaliumhydroxid  sning              | 50            | 20  C | ●            |
| Kresol                             |               | 20  C | ●            |
| Linolje                            |               | 20  C | ●            |
| Matolje                            |               | 20  C | ●            |
| Maursyre                           | 10            | 20  C | ●            |
| Melk                               |               | 20  C | ●            |
| Merkurokrom                        |               | 20  C | ●            |
| Metylalkohol (metanol)             | 100           | 20  C | ●            |
| Metylenklorid                      | 100           | 20  C | ●            |
| Mineraloljer, aromatfrie           |               | 20  C | ●            |
| Natriumhydroxid  sning (natronlut) | 15            | 20  C | ●            |
| Natriumhydroxid  sning (natronlut) | 60            | 20  C | ●            |
| Natriumkarbonat, vattenl.          |               | 20  C | ●            |
| Natriumklorid, vattenl.            |               | 20  C | ●            |
| Natriumnitrat, vattenl.            |               | 20  C | ●            |
| Natriumtiosulfat                   |               | 20  C | ●            |
| Natriumv  tesulfit                 |               | 20  C | ●            |
| Nitrobensen                        |               | 20  C | ●            |
| Oxalsyra                           |               | 20  C | ●            |
| Ozon (gas)                         |     0.5 ppm   | 20  C | ●            |
| Paraffinolja                       | 100           | 20  C | ●            |
| Perkloretylen                      |               | 20  C | ●            |
| Petroleumeter                      | 100           | 20  C | ●            |
| Propylalkohol                      |               | 20  C | ●            |
| Salpetersyra                       | 50            | 20  C | ●            |
| Salpetersyra                       | 10            | 20  C | ●            |
| Saltsyra                           | 10            | 20  C | ●            |
| Saltsyra (konc.)                   |               | 20  C | ●            |
| Silikonolje                        |               | 20  C | ●            |
| Svavelsyra                         | 96            | 20  C | ●            |
| Transformatorolje                  |               | 20  C | ●            |

| Kemikalie | Konsentrasjon | Temp. | Best ndighet |
|-----------|---------------|-------|--------------|
| Vann      |               | 20  C |              |
| Xylen     |               | 20  C |              |
|  ttiksyra | 100           | 20  C |              |