



PEEK+PTFE 28x3000 mm blå

Artikelnr P1501469

Beständig

Delvis beständig

Ej beständig

Kemikalie	Konsentrasjon	Temp.	Beständighet
1,4-Dioxan	100	20 Å°C	Beständig
2-Hydroxypropionic Acid	90	20 Å°C	Beständig
Acetic Acid	100	20 Å°C	Beständig
Aceton	100	20 Å°C	Beständig
Ammoniak	â€”	20 Å°C	Beständig
Ammonium Chloride	â€”	20 Å°C	Beständig
Amyl Alcohol	â€”	20 Å°C	Beständig
Apple Juice	â€”	20 Å°C	Beständig
Bensen	â€”	20 Å°C	Beständig
Bleaching Solution	â€”	20 Å°C	Beständig
Boric Acid	100	20 Å°C	Beständig
Brake Fluid	â€”	20 Å°C	Beständig
Br�nsle, aromatfritt	â€”	20 Å°C	Beständig
Butyl Acetate	â€”	20 Å°C	Beständig
Calcium Chloride	â€”	20 Å°C	Beständig
Carbon Disulfide	100	20 Å°C	Beständig
Carbon Tetrachloride	â€”	20 Å°C	Beständig
Citric Acid	10	20 Å°C	Beständig
Cyklohexanon	100	20 Å°C	Beständig
Cyklohexen	100	20 Å°C	Beständig
Diesel Fuel	â€”	20 Å°C	Beständig
Diethylene Oxide	â€”	20 Å°C	Beständig
Eddik (standard)	5-10	20 Å°C	Beständig
Ethyl Acetate	100	20 Å°C	Beständig
Ethyl Alcohol	96	20 Å°C	Beständig
Ethylene Chloride	100	20 Å°C	Beständig
Fenol (vattenl.)	9	20 Å°C	Beständig

Kemikalie	Konsentrasjon	Temp.	BestÅndighet
Food Oil	â€”	20 Â°C	●
Formaldehyd (vattent.)	40	20 Â°C	●
Formic Acid	10	20 Â°C	●
Frost Protection Agent	â€”	20 Â°C	●
Glycerin	100	20 Â°C	●
Glykol	100	20 Â°C	●
Heating Oil	â€”	20 Â°C	●
Heptan	100	20 Â°C	●
Hydrochloric Acid	10	20 Â°C	●
Hydrochloric Acid (concentrated)	â€”	20 Â°C	●
Hydrofluoric Acid	40	20 Â°C	●
Hydrogen Peroxide	10	20 Â°C	●
Hydrogen Sulfide (aqueous)	â€”	20 Â°C	●
Isopropyl Alcohol	100	20 Â°C	●
Klor (gas)	100	20 Â°C	●
Klorbensen	100	20 Â°C	●
Kloroform	â€”	20 Â°C	●
Kresol	â€”	20 Â°C	●
Linseed Oil	â€”	20 Â°C	●
Melk	â€”	20 Â°C	●
Merkurokrom	â€”	20 Â°C	●
Methyl Alcohol	100	20 Â°C	●
Methyl Ethyl Ketone (MEK)	100	20 Â°C	●
Methylene Chloride	100	20 Â°C	●
Mineral Oils (aromatic free)	â€”	20 Â°C	●
Nitric Acid	10	20 Â°C	●
Nitric Acid	50	20 Â°C	●
Nitrobensen	â€”	20 Â°C	●
Oxalic Acid	â€”	20 Â°C	●
Ozone Gas	â€”	20 Â°C	●
Paraffine Oil	100	20 Â°C	●
Perkloretylen	â€”	20 Â°C	●
Petroleum	100	20 Â°C	●
Petroleum Ether	100	20 Â°C	●
Phosphoric Acid	50	20 Â°C	●

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Potassium Hydroxide liquor	50	20 �C	●
Premium Fuel	��	20 �C	●
Propyl Alcohol	��	20 �C	●
Pyridin	��	20 �C	●
Silicone Oil	��	20 �C	●
Sodium Carbonate (aqueous)	��	20 �C	●
Sodium Chloride (aqueous)	��	20 �C	●
Sodium Hydrogen Sulfite	��	20 �C	●
Sodium Hydroxide liquor	15	20 �C	●
Sodium Hydroxide liquor	60	20 �C	●
Sodium Nitrate (aqueous)	��	20 �C	●
Sodium Thiosulfate	��	20 �C	●
Sulfuric Acid	96	20 �C	●
Tetrahydrofuran (THF)	100	20 �C	●
Toluen	100	20 �C	●
Transformer Oil	��	20 �C	●
Trikloret�n	100	20 �C	●
Vann	��	20 �C	●
Xylen	��	20 �C	●