

PMMA E 10x2000 mm gjennomsiktig

Artikelnr P1200648

● Best ndig
 ● Delvis best ndig
 ● Ej best ndig

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Aceton	100%	20 �C	●
Ammoniak	conc.	20 �C	●
Amylalkohol	��	20 �C	●
Bensen	��	20 �C	●
Bensin (premium)	��	20 �C	●
Br�nsle, aromatfritt	��	20 �C	●
Butylacetat	��	20 �C	●
Citronsyra	10%	20 �C	●
Cyklohexanon	100%	20 �C	●
Cyklohexen	100%	20 �C	●
Diesel	��	20 �C	●
Dietylenoxid	��	20 �C	●
Eddik, standard	5-10%	20 �C	●
Eplejuice	��	20 �C	●
Etylacetat	100%	20 �C	●
Etylalkohol (etanol)	96%	20 �C	●
Etylenklorid	100%	20 �C	●
Fenol, vattenl.	ca. 9%	20 �C	●
Flussyre	40%	20 �C	●
Formaldehyd, vattenl.	40%	20 �C	●
Fosforsyra	50%	20 �C	●
Fyringsolje	��	20 �C	●
Glycerin	100%	20 �C	●
Glykol	100%	20 �C	●
Heptan	100%	20 �C	●
Hydrogenperoksid	10%	20 �C	●
Isopropylalkohol	100%	20 �C	●

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Kalciumklorid	��	20 �C	�
Kaliumhydroxidl�sning	50%	20 �C	�
Klorgas	100%	20 �C	�
Kloroform	��	20 �C	�
Koldisulfid	100%	20 �C	�
Koltetraklorid	��	20 �C	�
Kresol	��	20 �C	�
Linolje	��	20 �C	�
Maursyre	10%	20 �C	�
Melk	��	20 �C	�
Merkurokrom	��	20 �C	�
Metylalkohol (metanol)	100%	20 �C	�
Metylenklorid	100%	20 �C	�
Metyletylketon (MEK)	100%	20 �C	�
Mineraloljer, aromاتفrie	��	20 �C	�
Natriumhydroxidl�sning (natronlut)	15%	20 �C	�
Natriumkarbonat, vattenl.	��	20 �C	�
Natriumklorid, vattenl.	��	20 �C	�
Natriumtiosulfat	��	20 �C	�
Natriumv�ttesulfitt	��	20 �C	�
Natronlut (60%)	60%	20 �C	�
Nitrobensen	��	20 �C	�
Oxalsyra	��	20 �C	�
Ozon (gas)	�� 0.5 ppm	20 �C	�
Paraffinolja	100%	20 �C	�
Perkloretylen	��	20 �C	�
Petroleum	100%	20 �C	�
Petroleumeter	100%	20 �C	�
Salpetersyra	10%	20 �C	�
Salpetersyra (50%)	50%	20 �C	�
Saltsyra	10%	20 �C	�
Saltsyra (konc.)	conc.	20 �C	�
Silikonolje	��	20 �C	�
Svavelsyra	96%	20 �C	�

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Tetrahydrofuran (THF)	100%	20 �C	●
Toluen	100%	20 �C	●
Transformatorolje	��	20 �C	●
Trikloretan	100%	20 �C	●
Vann	��	20 �C	●
V�ttesulfid, vattenl.	��	20 �C	●
Xylen	��	20 �C	●
�ttiksyra	100%	20 �C	●