



POM C 175x1000 mm trafikrÄd

Artikelnr P1005161

Beständig

Delvis beständig

Ej beständig

Kemikalie	Konsentrasjon	Temp.	Beständighet
1,4-Dioxan	100%	20 Å°C	
2-Hydroxipropionsyra (mjÄlksyra)	90%	20 Å°C	
Aceton	100%	20 Å°C	
Ammoniak	conc.	20 Å°C	
Ammoniumklorid	â€”	20 Å°C	
Amylalkohol	â€”	20 Å°C	
Bensen	â€”	20 Å°C	
Bensin (premium)	â€”	20 Å°C	
BlekningslÄsning	12.5 cl	20 Å°C	
Borsyra	100%	20 Å°C	
BremsevÄjske	â€”	20 Å°C	
BrÄnnsle, aromatfritt	â€”	20 Å°C	
Butylacetat	â€”	20 Å°C	
Citronsyra	10%	20 Å°C	
Cyklohexanon	100%	20 Å°C	
Cyklohexen	100%	20 Å°C	
Diesel	â€”	20 Å°C	
Dietylenoxid	â€”	20 Å°C	
Eddik, standard	5-10%	20 Å°C	
Eplejuice	â€”	20 Å°C	
Etylacetat	100%	20 Å°C	
Etylalkohol (etanol)	96%	20 Å°C	
Fenol, vattenl.	ca. 9%	20 Å°C	
Flussyre	40%	20 Å°C	
Formaldehyd, vattenl.	40%	20 Å°C	
Fosforsyra	50%	20 Å°C	
FrostvÄjske	â€”	20 Å°C	

[illegible]

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Propylalkohol	��	20 �C	�
Salpetersyra	10%	20 �C	�
Salpetersyra (50%)	50%	20 �C	�
Saltsyra	10%	20 �C	�
Saltsyra (konc.)	conc.	20 �C	�
Silikonolje	��	20 �C	�
Svavelsyra	96%	20 �C	�
Tetrahydrofuran (THF)	100%	20 �C	�
Toluen	100%	20 �C	�
Transformatorolje	��	20 �C	�
Trikloreten	100%	20 �C	�
Vann	��	20 �C	�
V��tesulfid, vattenl.	��	20 �C	�
Xylen	��	20 �C	�
��ttiksyra	100%	20 �C	�