



POM H 120x3000 mm svart

Artikelnr P1008607
Material POM

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tetthet	3	g/cm³	DIN EN ISO 1183-1
StreckgrenseSpenning	53	MPa	DIN EN ISO 527-2
Elastisitetsmodul (trek)	3000	MPa	DIN EN ISO 527-2
Brottsdeformasjon	8	%	DIN EN ISO 527-2
Smeltepunkt	179	°C	DIN EN ISO 11357
Maksimal drifttemperatur (kortvarig)	150	°C	
Maksimal driftstemperatur	110	°C	
Varme-forvrengning (HDT/A)	141	°C	
Vicat-mykningstemperatur (VST/B/50)	90	°C	DIN EN ISO 306
Dielektrisk Styrke	23	kV/mm	ISO 60243-1
VolumResistivitet	10 ¹⁴	Ω	DIN EN 62631-3-1
Dielektrisk konstant (1 MHz)	2.4	-	IEC 60250
Brannklasse (UL 94)	60695		UL 94
Bøyhållfasthet	53	MPa	DIN EN ISO 527-2
Termisk konduktivitet	0.46	W/(m·K)	ISO 22007-4
Overflatemotstand	10 ¹⁴	Ω	DIN EN 62631-3-2
Fuktabsorpsjon til metning	0.1	%	DIN EN ISO 62
Skåret slagfasthet (Charpy)	25	kJ/m²	DIN EN ISO 179-1
Slagsegghet (Charpy)	2	kJ/m²	DIN EN ISO 179-1
Termisk utvidelseskoeffisient	23	10 ⁻⁴ /K	DIN EN ISO 11359-1
Hardhet Shore D	81	° Shore D	DIN EN ISO 868

2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

Kemikalie	Konc.	Resultat
-----------	-------	----------

Kemikalie	Konc.	Resultat
1,4-Dioxan	100%	
2-Hydroxypropionic Acid	90%	
Acetic Acid	100%	
Aceton	100%	
Ammoniak	conc.	
Ammonium Chloride	-	
Amyl Alcohol	-	
Apple Juice	-	
Bensen	-	
Bleaching Solution	12.5 cl	
Boric Acid	100%	
Brake Fluid	-	
Bränsle, aromatfritt	-	
Butyl Acetate	-	
Calcium Chloride	-	
Carbon Disulfide	100%	
Carbon Tetrachloride	-	
Citric Acid	10%	
Cyklohexanon	100%	
Cyklohexen	100%	
Diesel Fuel	-	
Diethylene Oxide	-	
Eddik, standard	5-10%	
Ethyl Acetate	100%	
Ethyl Alcohol	96%	
Ethylene Chloride	100%	
Fenol, vattenl.	ca. 9%	
Food Oil	-	
Formaldehyd, vattenl.	40%	
Formic Acid	10%	
Frost Protection Agent	-	
Glycerin	100%	
Glykol	100%	
Heating Oil	-	
Heptan	100%	

Kemikalie	Konc.	Resultat
Hydrochloric Acid	10%	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40%	●
Hydrogen Peroxide	10%	●
Hydrogen Sulfide, aqueous solution	-	●
Isopropyl Alcohol	100%	●
Klor (gas)	100%	●
Klorbensen	100%	●
Kloroform	-	●
Kresol	-	●
Linseed Oil	-	●
Melk	-	●
Merkurokrom	-	●
Methyl Alcohol	100%	●
Methyl Ethyl Ketone (MEK)	100%	●
Methylene Chloride	100%	●
Mineral Oils (aromatic free)	-	●
Nitric Acid	10%	●
Nitric Acid (50%)	50%	●
Nitrobensen	-	●
Oxalic Acid	-	●
Ozone Gas	≤0.5 ppm	●
Paraffine Oil	100%	●
Perkloretylen	-	●
Petroleum	100%	●
Petroleum Ether	100%	●
Phosphoric Acid	50%	●
Potassium Hydroxide liquor	50%	●
Premium Fuel	-	●
Propyl Alcohol	-	●
Pyridin	-	●
Silicone Oil	-	●
Sodium Carbonate, aqueous	-	●
Sodium Chloride, aqueous	-	●
Sodium Hydrogen Sulfite	-	●

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor (15%)	15%	●
Sodium Hydroxide liquor (60%)	60%	●
Sodium Nitrate, aqueous	-	●
Sodium Thiosulfate	-	●
Sulfuric Acid	96%	●
Tetrahydrofuran, THF	100%	●
Toluen	100%	●
Transformer Oil	-	●
Trikloreten	100%	●
Vann	-	●
Xylen	-	●