



PP-H 65x2000 mm grå

Artikelnr P1010055

Beständig

Delvis beständig

Ej beständig

Kemikalie	Konsentrasjon	Temp.	Beständighet
1,4-Dioxan	100	20 °C	
2-Hydroxipropionsyra (mjölksyra)	90	20 °C	
Aceton	100	20 °C	
Ammoniak	â€	20 °C	
Ammoniumklorid	â€	20 °C	
Amylalkohol	â€	20 °C	
Bensen	â€	20 °C	
Bensin (premium)	â€	20 °C	
Blekningsl�sning	â€	20 °C	
Borsyra	100	20 °C	
Bremsev�jske	â€	20 °C	
Br�nsle, aromatfritt	â€	20 °C	
Butylacetat	â€	20 °C	
Citronsyra	10	20 °C	
Cyklohexanon	100	20 °C	
Cyklohexen	100	20 °C	
Diesel	â€	20 °C	
Dietylenoxid	â€	20 °C	
Eddik, standard	5 - 10	20 °C	
Etylacetat	100	20 °C	
Etylalkohol (etanol)	96	20 °C	
Etylenklorid	100	20 °C	
Fenol, vattenl.	ca. 9	20 °C	
Flussyre	40	20 °C	
Formaldehyd, vattenl.	40	20 °C	
Fosforsyra	50	20 °C	
Frostv�jske	â€	20 °C	

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Fyringsolje	��	20 ��C	�
Glycerin	100	20 ��C	�
Glykol	100	20 ��C	�
Heptan	100	20 ��C	�
Hydrogenperoksid	10	20 ��C	�
Isopropylalkohol	100	20 ��C	�
Kalciumklorid	��	20 ��C	�
Kaliumhydroxid��sning	50	20 ��C	�
Klor (gas)	100	20 ��C	�
Klorbensen	100	20 ��C	�
Kloroform	��	20 ��C	�
Koldisulfid	100	20 ��C	�
Koltetraklorid	��	20 ��C	�
Kresol	��	20 ��C	�
Linolje	��	20 ��C	�
Matolje	��	20 ��C	�
Maursyre	10	20 ��C	�
Melk	��	20 ��C	�
Merkurokrom	��	20 ��C	�
Metylalkohol (metanol)	100	20 ��C	�
Metylenklorid	100	20 ��C	�
Metyletylketon (MEK)	100	20 ��C	�
Mineraloljer (aromatfrie)	��	20 ��C	�
Natriumhydroxid��sning (natronlut)	15	20 ��C	�
Natriumhydroxid��sning (natronlut)	60	20 ��C	�
Natriumkarbonat, vattenl.	��	20 ��C	�
Natriumklorid, vattenl.	��	20 ��C	�
Natriumnitrat, vattenl.	��	20 ��C	�
Natriumtiosulfat	��	20 ��C	�
Natriumv��tesulfit	��	20 ��C	�
Nitrobensen	��	20 ��C	�
Oxalsyra	��	20 ��C	�
Ozon (gas)	��� 0.5 ppm	20 ��C	�
Paraffinolja	100	20 ��C	�

Kemikalie	Konsentrasjon	Temp.	Best�ndighet
Perkloretylen	��	20 �C	�
Petroleumeter	100	20 �C	�
Propylalkohol	��	20 �C	�
Pyridin	��	20 �C	�
Salpetersyra	50	20 �C	�
Salpetersyra	10	20 �C	�
Saltsyra	10	20 �C	�
Saltsyra (konc.)	��	20 �C	�
Silikonolje	��	20 �C	�
Svavelsyra	96	20 �C	�
Tetrahydrofuran (THF)	100	20 �C	�
Toluen	100	20 �C	�
Transformatorolje	��	20 �C	�
Trikloreten	100	20 �C	�
Vann	��	20 �C	�
V��tesulfid, vattenl.	��	20 �C	�
Xylen	��	20 �C	�
��ttiksyra	100	20 �C	�