



Platta i PA6 C 1000x1000x70 mm natur

Artikelnr P1001771
Material PA

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densitet	1.1	g/cm³	ISO 1183
Sträckgränsspänning	75	MPa	ISO 527
Elasticitetsmodul (drag)	3500	MPa	ISO 527-2
Brotttöjning	25	%	ISO 527-2
Smältpunkt	220	°C	ISO 3146
Maximal drifttemperatur (korttid)	170	°C	
Maximal drifttemperatur	105	°C	
Minsta temperatur	-30	°C	
Värmeförvrängning (HDT/A)	80	°C	ISO 75-2
Dielektrisk styrka	25	kV/mm	IEC 60243-1
Volymresistivitet	10 ¹⁴	Ω·cm	IEC 60093
Dielektrisk konstant (1 MHz)	3.2	-	IEC 60250
Dielektrisk konstant (100 Hz)	3.6	-	IEC 60250
Dielektrisk förlustfaktor (1 MHz)	0.0	-	IEC 60250
Dielektrisk förlustfaktor (100 Hz)	0.0	-	IEC 60250
Böjhållfasthet	85	MPa	ISO 527-2
Termisk konduktivitet	0.29	W/(m·K)	DIN 52612
Ytresistivitet	10 ¹³	Ω	IEC 60093
Jämförande krypströmsindex (CTI)	600	V	IEC 60112
Fuktabsorption till mättnad	2.3	%	ISO 62
Vattenabsorption till mättnad	6.5	%	ISO 62
Skårad slagseghet (Charpy)	3.5	kJ/m²	ISO 179/1eA
Termisk utvidgningskoefficient	0.8	10 ⁻⁴ /K	ISO 11359
Kultryckshårdhet	148.3	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Aceton	100	●
Ammoniak	conc.	●
Ammonium Chloride	-	●
Amyl Alcohol	-	●
Apple Juice	-	●
Bensen	-	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	-	●
Bränsle (aromatfritt)	-	●
Butyl Acetate	-	●
Calcium Chloride	-	●
Carbon Disulfide	100	●
Carbon Tetrachloride	-	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	-	●
Diethylene Oxide	-	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol (vattenl.)	ca. 9	●
Food Oil	-	●
Formaldehyd (vattenl.)	40	●
Formic Acid	10	●
Frost Protection Agent	-	●
Glycerin	100	●
Glykol	100	●

Kemikalie	Konc.	Resultat
Heating Oil	-	●
Heptan	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	-	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	-	●
Kresol	-	●
Linseed Oil	-	●
Merkurokrom	-	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	-	●
Mjölk	-	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	-	●
Oxalic Acid	-	●
Ozone Gas	≤ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	-	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	-	●
Propyl Alcohol	-	●
Pyridin	-	●
Silicone Oil	-	●
Sodium Carbonate (aqueous)	-	●

Kemikalie	Konc.	Resultat
Sodium Chloride (aqueous)	-	●
Sodium Hydrogen Sulfite	-	●
Sodium Hydroxide liquor	60	●
Sodium Hydroxide liquor	15	●
Sodium Nitrate (aqueous)	-	●
Sodium Thiosulfate	-	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluen	100	●
Transformer Oil	-	●
Trikloreten	100	●
Vatten	-	●
Xylen	-	●
Ättika (standard)	5 - 10	●