



## Platta i PA6 C 2000x1220x10 mm natur

Artikelnr P1001805

Material PA

### 1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densitet	<b>1.1</b>	g/cm <sup>3</sup>	ISO 1183
Sträckgränsspänning	<b>75</b>	MPa	ISO 527
Elasticitetsmodul (drag)	<b>3500</b>	MPa	ISO 527-2
Brotttöjning	<b>25</b>	%	ISO 527-2
Smältpunkt	<b>220</b>	°C	ISO 3146
Maximal drifttemperatur (korttid)	<b>170</b>	°C	
Maximal drifttemperatur	<b>105</b>	°C	
Minsta temperatur	<b>-30</b>	°C	
Värmeförvrängning (HDT/A)	<b>80</b>	°C	ISO 75-2
Dielektrisk styrka	<b>25</b>	kV/mm	IEC 60243-1
Volymresistivitet	<b>10<sup>14</sup></b>	Ω·cm	IEC 60093
Dielektrisk konstant (1 MHz)	<b>3.2</b>	-	IEC 60250
Dielektrisk konstant (100 Hz)	<b>3.6</b>	-	IEC 60250
Dielektrisk förlustfaktor (1 MHz)	<b>0.0</b>	-	IEC 60250
Dielektrisk förlustfaktor (100 Hz)	<b>0.0</b>	-	IEC 60250
Böjhållfasthet	<b>85</b>	MPa	ISO 527-2
Termisk konduktivitet	<b>0.29</b>	W/(m·K)	DIN 52612
Ytresistivitet	<b>10<sup>13</sup></b>	Ω	IEC 60093
Jämförande krypströmsindex (CTI)	<b>600</b>	V	IEC 60112
Fuktabsorption till mättnad	<b>2.3</b>	%	ISO 62
Vattenabsorption till mättnad	<b>6.5</b>	%	ISO 62
Skårad slagseghet (Charpy)	<b>3.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Termisk utvidgningskoefficient	<b>0.8</b>	10 <sup>-4</sup> /K	ISO 11359
Kultryckshårdhet	<b>148.3</b>	MPa	ISO 2039-1

## 2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxan	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Aceton	100	●
Ammoniak	conc.	●
Ammonium Chloride	-	●
Amyl Alcohol	-	●
Apple Juice	-	●
Bensen	-	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	-	●
Bränsle (aromatfritt)	-	●
Butyl Acetate	-	●
Calcium Chloride	-	●
Carbon Disulfide	100	●
Carbon Tetrachloride	-	●
Citric Acid	10	●
Cyklohexanon	100	●
Cyklohexen	100	●
Diesel Fuel	-	●
Diethylene Oxide	-	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Fenol (vattenl.)	ca. 9	●
Food Oil	-	●
Formaldehyd (vattenl.)	40	●
Formic Acid	10	●
Frost Protection Agent	-	●
Glycerin	100	●
Glykol	100	●

Kemikalie	Konc.	Resultat
Heating Oil	-	●
Heptan	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	-	●
Isopropyl Alcohol	100	●
Klor (gas)	100	●
Klorbensen	100	●
Kloroform	-	●
Kresol	-	●
Linseed Oil	-	●
Merkurokrom	-	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Mineral Oils (aromatic free)	-	●
Mjök	-	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobensen	-	●
Oxalic Acid	-	●
Ozone Gas	≤ 0.5 ppm	●
Paraffine Oil	100	●
Perkloretylen	-	●
Petroleum	100	●
Petroleum Ether	100	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	-	●
Propyl Alcohol	-	●
Pyridin	-	●
Silicone Oil	-	●
Sodium Carbonate (aqueous)	-	●

Kemikalie	Konc.	Resultat
Sodium Chloride (aqueous)	-	●
Sodium Hydrogen Sulfite	-	●
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor	60	●
Sodium Nitrate (aqueous)	-	●
Sodium Thiosulfate	-	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluen	100	●
Transformer Oil	-	●
Trikloretan	100	●
Vatten	-	●
Xylen	-	●
Ättika (standard)	5 - 10	●