



Platta i PA6 GL 2000x1000x95 mm grålln

Artikelnr P1600249

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxan	100	20 Å°C	
2-Hydroxypropionic Acid	90	20 Å°C	
Acetic Acid	100	20 Å°C	
Aceton	100	20 Å°C	
Ammoniak	conc.	20 Å°C	
Ammonium Chloride	â€	20 Å°C	
Amyl Alcohol	â€	20 Å°C	
Apple Juice	â€	20 Å°C	
Bensen	â€	20 Å°C	
Bleaching Solution	12.5 cl	20 Å°C	
Boric Acid	100	20 Å°C	
Brake Fluid	â€	20 Å°C	
Bränsle (aromatfritt)	â€	20 Å°C	
Butyl Acetate	â€	20 Å°C	
Calcium Chloride	â€	20 Å°C	
Carbon Disulfide	100	20 Å°C	
Carbon Tetrachloride	â€	20 Å°C	
Citric Acid	10	20 Å°C	
Cyklohexanon	100	20 Å°C	
Cyklohexen	100	20 Å°C	
Diesel Fuel	â€	20 Å°C	
Diethylene Oxide	â€	20 Å°C	
Ethyl Acetate	100	20 Å°C	
Ethyl Alcohol	96	20 Å°C	
Ethylene Chloride	100	20 Å°C	
Fenol (vattenl.)	ca. 9	20 Å°C	
Food Oil	â€	20 Å°C	

Kemikalie	Koncentration	Temp.	Best�ndighet
Formaldehyd (vattenl.)	40	20 ��C	�
Formic Acid	10	20 ��C	�
Frost Protection Agent	���	20 ��C	�
Glycerin	100	20 ��C	�
Glykol	100	20 ��C	�
Heating Oil	���	20 ��C	�
Heptan	100	20 ��C	�
Hydrochloric Acid	10	20 ��C	�
Hydrochloric Acid (concentrated)	conc.	20 ��C	�
Hydrofluoric Acid	40	20 ��C	�
Hydrogen Peroxide	10	20 ��C	�
Hydrogen Sulfide (aqueous)	���	20 ��C	�
Isopropyl Alcohol	100	20 ��C	�
Klor (gas)	100	20 ��C	�
Klorbensen	100	20 ��C	�
Kloroform	���	20 ��C	�
Kresol	���	20 ��C	�
Linseed Oil	���	20 ��C	�
Merkurokrom	���	20 ��C	�
Methyl Alcohol	100	20 ��C	�
Methyl Ethyl Ketone (MEK)	100	20 ��C	�
Methylene Chloride	100	20 ��C	�
Mineral Oils (aromatic free)	���	20 ��C	�
Mj��lk	���	20 ��C	�
Nitric Acid	10	20 ��C	�
Nitric Acid	50	20 ��C	�
Nitrobensen	���	20 ��C	�
Oxalic Acid	���	20 ��C	�
Ozone Gas	��� 0.5 ppm	20 ��C	�
Paraffine Oil	100	20 ��C	�
Perkloretylen	���	20 ��C	�
Petroleum	100	20 ��C	�
Petroleum Ether	100	20 ��C	�
Phosphoric Acid	50	20 ��C	�
Potassium Hydroxide liquor	50	20 ��C	�

