

PC GF30 1000x500x25 mm natur

Artikelnummer: P1002904

Kemisk beständighet

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
1,4-Dioxan	partially_resistant	100%%	
2-Hydroxiopropionsyra (mjölksyra)	resistant	90%%	
Aceton	not_resistant	100%%	
Ammoniak	not_resistant	conc.%	
Ammoniumklorid	resistant		
Bensen	not_resistant		
Bensin (premium)	not_resistant		
Blekningslösning	not_resistant	12.5 cl%	
Borsyra	resistant	100%%	
Bränsle, aromatfritt	partially_resistant		
Butylacetat	not_resistant		
Citronsyra	resistant	10%%	
Cyklohexanon	not_resistant	100%%	
Cyklohexen	not_resistant	100%%	
Diesel	partially_resistant		
Dietylenoxid	not_resistant		
Eldningsolja	partially_resistant		
Etylacetat	not_resistant	100%%	
Etylalkohol (etanol)	partially_resistant	96%%	
Etylenklorid	not_resistant	100%%	
Fenol, vattenl.	not_resistant	ca. 9%%	
Fluorvätesyra	not_resistant	40%%	

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
Formaldehyd, vattenl.	resistant	40%%	
Fosforsyra	resistant	50%%	
Frostskyddsmedel	resistant		
Glycerin	partially_resistant	100%%	
Glykol	resistant	100%%	
Heptan	resistant	100%%	
Isopropylalkohol	partially_resistant	100%%	
Kalciumklorid	resistant		
Kaliumhydroxidlösning	not_resistant	50%%	
Klor (gas)	partially_resistant	100%%	
Klorbensen	not_resistant	100%%	
Kloroform	not_resistant		
Koldisulfid	not_resistant	100%%	
Koltetraklorid	not_resistant		
Kresol	not_resistant		
Linolja	resistant		
Matolja	resistant		
Merкуроkrom	partially_resistant		
Metylalkohol (metanol)	not_resistant	100%%	
Metylenklorid	not_resistant	100%%	
Metyletylketon (MEK)	not_resistant	100%%	
Mjök	resistant		
Myrsyra	resistant	10%%	
Natriumkarbonat, vattenl.	resistant		
Natriumklorid, vattenl.	resistant		
Natriumnitrat, vattenl.	resistant		
Natriumvätesulfit	resistant		
Natronlut (15%)	not_resistant	15%%	
Natronlut (60%)	not_resistant	60%%	
Nitrobensen	not_resistant		
Oxalsyra	resistant		

KEMIKALIE	BETYG	KONCENTRATION	TEMPERATUR
Ozon (gas)	partially_resistant	≤ 0.5 ppm%	
Paraffinolja	resistant	100%%	
Perkloretylen	not_resistant		
Petroleum	partially_resistant	100%%	
Petroleometer	partially_resistant	100%%	
Propylalkohol	resistant		
Pyridin	not_resistant		
Salpetersyra (10%)	partially_resistant	10%%	
Salpetersyra (50%)	not_resistant	50%%	
Saltsyra	resistant	10%%	
Saltsyra (konc.)	partially_resistant	conc.%	
Silikonolja	resistant		
Svavelsyra	not_resistant	96%%	
Tetrahydrofuran (THF)	not_resistant	100%%	
Toluen	not_resistant	100%%	
Trikloretan	not_resistant	100%%	
Vatten	resistant		
Väteperoxid	resistant	10%%	
Vätesulfid, vattenl.	resistant		
Xylen	not_resistant		
Äppeljuice	partially_resistant		
Ättika, standard	resistant	5-10%%	
Ättiksyra	not_resistant	100%%	