



Platta i PE-1000 2000x1000x50 mm svart

Artikelnr P1400288

Best ndig

Delvis best ndig

Ej best ndig

Kemikalie	Koncentration	Temp.	Best�ndighet
1,4-Dioxan	100	20 �C	
2-Hydroxipropionsyra (mj�lkssyra)	90	20 �C	
Aceton	100	20 �C	
Ammoniak	��	20 �C	
Ammoniumklorid	��	20 �C	
Amylalkohol	��	20 �C	
Bensen	��	20 �C	
Bensin (premium)	��	20 �C	
Borsyra	100	20 �C	
Bromsv��tska	��	20 �C	
Br��nsle, aromatfritt	��	20 �C	
Butylacetat	��	20 �C	
Citronsyra	10	20 �C	
Cyklohexanon	100	20 �C	
Cyklohexen	100	20 �C	
Diesel	��	20 �C	
Eldningsolja	��	20 �C	
Etylacetat	100	20 �C	
Etylalkohol (etanol)	96	20 �C	
Fenol, vattenl.	ca. 9	20 �C	
Formaldehyd, vattenl.	40	20 �C	
Fosforsyra	50	20 �C	
Frostskyddsmedel	��	20 �C	
Glycerin	100	20 �C	
Glykol	100	20 �C	
Heptan	100	20 �C	
Isopropylalkohol	100	20 �C	

Kemikalie	Koncentration	Temp.	Beständighet
Kalciumklorid	â€”	20 Å°C	●
Kaliumhydroxidl�sning	50	20 Å°C	●
Kresol	â€”	20 Å°C	●
Linolja	â€”	20 Å°C	●
Matolja	â€”	20 Å°C	●
Merkurokrom	â€”	20 Å°C	●
Metylalkohol (metanol)	100	20 Å°C	●
Metylenklorid	100	20 Å°C	●
Mineraloljor, aromatfria	â€”	20 Å°C	●
Mj�lk	â€”	20 Å°C	●
Myrsyra	10	20 Å°C	●
Natriumhydroxidl�sning (natronlut)	60	20 Å°C	●
Natriumhydroxidl�sning (natronlut)	15	20 Å°C	●
Natriumkarbonat, vattenl.	â€”	20 Å°C	●
Natriumklorid, vattenl.	â€”	20 Å°C	●
Natriumnitrat, vattenl.	â€”	20 Å°C	●
Natriumtiosulfat	â€”	20 Å°C	●
Natriumv�tesulfit	â€”	20 Å°C	●
Nitrobensen	â€”	20 Å°C	●
Oxalsyra	â€”	20 Å°C	●
Ozon (gas)	��� 0.5 ppm	20 Å°C	●
Paraffinolja	100	20 Å°C	●
Perkloretylen	â€”	20 Å°C	●
Petroleumeter	100	20 Å°C	●
Propylalkohol	â€”	20 Å°C	●
Salpetersyra	50	20 Å°C	●
Salpetersyra	10	20 Å°C	●
Saltsyra	10	20 Å°C	●
Saltsyra (konc.)	â€”	20 Å°C	●
Silikonolja	â€”	20 Å°C	●
Svavelsyra	96	20 Å°C	●
Transformatorolja	â€”	20 Å°C	●
Vatten	â€”	20 Å°C	●
V�teperoxid	10	20 Å°C	●

Kemikalie	Koncentration	Temp.	Beständighet
Xylen	â€”	20 Å°C	
Ättika, standard	5 - 10	20 Å°C	
Ättiksyra	100	20 Å°C	