



Platta i PE-500 2000x1000x15 mm rÅld

Artikelnr P1400461

● Beständig

● Delvis beständig

● Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxan	100%	20 Å°C	●
2-Hydroxypropionic Acid	90%	20 Å°C	●
Acetaldehyd	â€”	20 Å°C	●
Acetic Acid	100%	20 Å°C	●
Aceton	â€”	20 Å°C	●
Aceton	100%	20 Å°C	●
Acronal-dispersjoner	â€”	20 Å°C	●
Akrylonitril	â€”	20 Å°C	●
Allylacetat	â€”	20 Å°C	●
Allylalkohol	96%	20 Å°C	●
Allylklorid	â€”	20 Å°C	●
Aluminiumfluorid	Conc.	20 Å°C	●
Aluminiumhydroxid	â€”	20 Å°C	●
Aluminiumklorid, fast	â€”	20 Å°C	●
Aluminiumklorid, vattenl.	any	20 Å°C	●
Aluminiummetafosfat	â€”	20 Å°C	●
Aluminiumsulfat, fast	â€”	20 Å°C	●
Aluminiumsulfat, vattenl. mÅttad	â€”	20 Å°C	●
Ammoniak	concentrated	20 Å°C	●
Ammoniak, flytande	â€”	20 Å°C	●
Ammoniak, gas	â€”	20 Å°C	●
Ammonium Chloride	â€”	20 Å°C	●
Amyl Alcohol	â€”	20 Å°C	●
Anilin	any	20 Å°C	●
Anisol	â€”	20 Å°C	●
Apple Juice	â€”	20 Å°C	●
Bensen	â€”	20 Å°C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Bensen	technically grade	20 �C	�
Bensoesyra, vattenl.	any	20 �C	�
Bensylalkohol	��	20 �C	�
Benzaldehyd, vattenl.	any	20 �C	�
Bitumen	��	20 �C	�
Bleaching Solution	12.5 cl	20 �C	�
Bl�ck	��	20 �C	�
Boric Acid	100%	20 �C	�
Brake Fluid	��	20 �C	�
Brom, flytande	100%	20 �C	�
Bromv�tesyra, vattenl.	50%	20 �C	�
Br�nsle (aromatfritt)	��	20 �C	�
Butanol, vattenl.	any	20 �C	�
Butyl Acetate	��	20 �C	�
Calcium Chloride	��	20 �C	�
Calcium carbonate	��	20 �C	�
Calcium carbonate	��	20 �C	�
Carbon Disulfide	100%	20 �C	�
Carbon Tetrachloride	��	20 �C	�
Caustic soda	any	20 �C	�
Cider	��	20 �C	�
Citric Acid	10%	20 �C	�
Citrusfruktjuicer	��	20 �C	�
Cyklohexan	��	20 �C	�
Cyklohexanol	��	20 �C	�
Cyklohexanon	100%	20 �C	�
Cyklohexanon	��	20 �C	�
Cyklohexen	100%	20 �C	�
Dibutyleter	��	20 �C	�
Dibutylftalat	��	20 �C	�
Diesel Fuel	��	20 �C	�
Diesel fuel	��	20 �C	�
Diethylene Oxide	��	20 �C	�
Diglykolsyra, vattenl.	30%	20 �C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Diklorethan	â€”	20 Â°C	●
Diklor�ttiksyra	â€”	20 Â°C	●
Dimethyl formamide	â€”	20 Â°C	●
Dimetylamin	â€”	20 Â°C	●
Dioxan	â€”	20 Â°C	●
Diskmedel	â€”	20 Â°C	●
Eldningsolja	â€”	20 Â°C	●
Ethanol	10%	100 Â°C	●
Ethanol	10%	100 Â°C	●
Ethanol	10%	100 Â°C	●
Ethanol	10% v/v	20 Â°C	●
Ethyl Acetate	100%	20 Â°C	●
Ethyl Alcohol	96%	20 Â°C	●
Ethylene Chloride	100%	20 Â°C	●
Etylacetat	â€”	20 Â°C	●
Etylenalkohol	96%	20 Â°C	●
Etylendiamin	â€”	20 Â°C	●
Etylenglykol	â€”	20 Â°C	●
Etylenklorid	â€”	20 Â°C	●
Fenol	â€”	20 Â°C	●
Fenol (vattenl.)	â‰ƒ9%	20 Â°C	●
Ferrous (III) nitrate, aqueous saturated	â€”	20 Â°C	●
Ferrous (III) sulfate, aqueous saturated	â€”	20 Â°C	●
Food Oil	â€”	20 Â°C	●
Formaldehyd (vattenl.)	40%	20 Â°C	●
Formaldehyd, vattenl.	â‰ƒ40%	20 Â°C	●
Formic Acid	10%	20 Â°C	●
Fosforsyra, vattenl.	80% L 95%	20 Â°C	●
Fosforsyra, vattenl.	50%	20 Â°C	●
Fosfortriklorid	â€”	20 Â°C	●
Fotogen	â€”	20 Â°C	●
Frigen 12 (Freon 12)	100%	20 Â°C	●
Frost Protection Agent	â€”	20 Â°C	●
Fruktjuicer	any	20 Â°C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Ftalsyra, vattenl.	50%	20 �C	●
Furfurol	��	20 �C	●
Garvsyra (tannin), vattenl.	10%	20 �C	●
Glycerin	100%	20 �C	●
Glycerin, aqueous	any	20 �C	●
Glykol	100%	20 �C	●
Glykol, aqueous	as supplied	20 �C	●
Glysantin	��	20 �C	●
Havsvatten	��	20 �C	●
Heating Oil	��	20 �C	●
Heptan	��	20 �C	●
Heptan	100%	20 �C	●
Hexan	��	20 �C	●
Honung	��	20 �C	●
Hydrochloric Acid	10%	20 �C	●
Hydrochloric Acid (concentrated)	concentrated	20 �C	●
Hydrofluoric Acid	40%	20 �C	●
Hydrogen Peroxide	10%	20 �C	●
Hydrogen Sulfide (aqueous solution)	��	20 �C	●
Isooktan	��	20 �C	●
Isopropanol	��	20 �C	●
Isopropyl Alcohol	100%	20 �C	●
Isopropyleter	��	20 �C	●
Jod i kaliumjodidl�sning	3% iodine	20 �C	●
J��rn(II)klorid, vattenl. m�ttad	��	20 �C	●
J��rn(II)sulfat, vattenl. m�ttad	��	20 �C	●
J��rn(III)klorid, vattenl.	any	20 �C	●
J��rn(III)klorid, vattenl. m�ttad	��	20 �C	●
J��rn(III)nitrat, vattenl. m�ttad	��	20 �C	●
J��rn(III)sulfat, vattenl. m�ttad	��	20 �C	●
Kalciumhypoklorit, vattenl. suspension	any	20 �C	●
Kamfer	��	20 �C	●
Klor (gas)	100%	20 �C	●
Klor, flytande	��	20 �C	●
Klorbensen	��	20 �C	●

Kemikalie	Koncentration	Temp.	Beständighet
Klorbensen	100%	20 Å°C	●
Kloroform	technically grade	20 Å°C	●
Kloroform	â€”	20 Å°C	●
KlorÄttiksyra, vattenl.	â‰∞85%	20 Å°C	●
Kokosolja	â€”	20 Å°C	●
Koldisulfid	â€”	20 Å°C	●
Kresol	100%	20 Å°C	●
Kresol	â€”	20 Å°C	●
Kromsyra-svavelsyra	â€”	20 Å°C	●
Kungsvatten	â€”	20 Å°C	●
Kvikksilver	â€”	20 Å°C	●
Linolja	technically grade	20 Å°C	●
Linseed Oil	â€”	20 Å°C	●
Litiumbromid	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Maleinsyra, vattenl.	any	20 Å°C	●
Melass	â€”	20 Å°C	●
Mentol	â€”	20 Å°C	●
Merkurokrom	â€”	20 Å°C	●
Metanol	technically grade	20 Å°C	●
Methyl Alcohol	100%	20 Å°C	●
Methyl Ethyl Ketone (MEK)	100%	20 Å°C	●
Methyl ethyl ketone	technically grade	20 Å°C	●
Methylene Chloride	100%	20 Å°C	●
Metylklorid	gaseous, technically grade	20 Å°C	●
Mineral Oil (aromatic free)	â€”	20 Å°C	●
MjÄlk	â€”	20 Å°C	●
MjÄlk	â€”	20 Å°C	●
Motor oil (heavy duty oil) without additives	â€”	20 Å°C	●
Myrsyra, vattenl.	85%	20 Å°C	●
Nafta	â€”	20 Å°C	●
Naftalen	â€”	20 Å°C	●
Natriumbromid	â€”	20 Å°C	●

Kemikalie	Koncentration	Temp.	Beskrivning
Natriumhydroxid, fast	â€”	20 Â°C	●
Natriumhydroxid, vattenl.	any	20 Â°C	●
Nitric Acid	10%	20 Â°C	●
Nitric Acid (50%)	50%	20 Â°C	●
Nitrobensen	â€”	20 Â°C	●
Nitrobensen	â€”	20 Â°C	●
Oils, ethereal	â€”	20 Â°C	●
Oleum	any	20 Â°C	●
Olive oil	â€”	100 Â°C	●
Olive oil	â€”	20 Â°C	●
Olive oil	â€”	100 Â°C	●
Olive oil	â€”	100 Â°C	●
Oljesyra	â€”	20 Â°C	●
Oljor, vegetabiliska och animaliska	â€”	20 Â°C	●
Oxalic Acid	â€”	20 Â°C	●
Oxalsyra, vattenl.	any	20 Â°C	●
Ozon	50 ppm	20 Â°C	●
Ozone Gas	â‰¤0.5 ppm	20 Â°C	●
Paraffine Oil	100%	20 Â°C	●
Perkloretylen	â€”	20 Â°C	●
Perklorsyra, vattenl.	20%	20 Â°C	●
Perklorsyra, vattenl.	70%	20 Â°C	●
Perklorsyra, vattenl.	50%	20 Â°C	●
Petroleum	â€”	20 Â°C	●
Petroleum	100%	20 Â°C	●
Petroleum Ether	100%	20 Â°C	●
Petroleometer	â€”	20 Â°C	●
Phosphoric Acid	50%	20 Â°C	●
Photographic developers	â€”	20 Â°C	●
Photographic emulsions	as supplied	20 Â°C	●
Photographic fixing baths	as supplied	20 Â°C	●
Polyesterhartser	â€”	20 Â°C	●
Potassium Hydroxide liquor	50%	20 Â°C	●
Premium Fuel	â€”	20 Â°C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Propionsyra, vattenl.	any	20 �C	●
Propyl Alcohol	��	20 �C	●
Pyridin	��	20 �C	●
Pyridin	��	20 �C	●
Salpetersyra, vattenl.	25%	20 �C	●
Salpetersyra, vattenl.	50%	20 �C	●
Saltsyra, vattenl.	any	20 �C	●
Silicon dioxide	��	20 �C	●
Silicon dioxide	��	20 �C	●
Silicone Oil	��	20 �C	●
Silikonolja	technically grade	20 �C	●
Sm�r	��	20 �C	●
Sockersirap	��	20 �C	●
Sodium Carbonate (aqueous)	��	20 �C	●
Sodium Chloride (aqueous)	��	20 �C	●
Sodium Hydrogen Sulfite	��	20 �C	●
Sodium Hydroxide liquor	15%	20 �C	●
Sodium Hydroxide liquor (60%)	60%	20 �C	●
Sodium Nitrate (aqueous)	��	20 �C	●
Sodium Thiosulfate	��	20 �C	●
Sodium borate	��	20 �C	●
Stearinsyra	��	20 �C	●
Sulfuric Acid	96%	20 �C	●
Svavelsyra, vattenl.	80%	20 �C	●
Svavelsyra, vattenl.	70%	20 �C	●
Svavelsyra, vattenl.	98%	20 �C	●
Svavelsyra, vattenl.	���50%	20 �C	●
Sylt	��	20 �C	●
Syre	��	20 �C	●
Talg	technically grade	20 �C	●
Tenn(II)klorid, vattenl.	any	20 �C	●
Tenn(IV)klorid, vattenl.	saturated	20 �C	●
Terpentinolja	technically grade	20 �C	●
Tetrahydrofuran	technically grade	20 �C	●
Tetrahydrofuran (THF)	100%	20 �C	●

