# Platta i PE-500 2000x1000x20 mm brun

Artikelnr P1400432

BestÃ¤ndig Delvis bestÃ¤ndig Ej bestÃ¤ndig

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| 1,4-Dioxan | 100% | 20 Â°C | |
| 2-Hydroxypropionic Acid | 90% | 20 Â°C | |
| Acetaldehyd | â€” | 20 Â°C | |
| Acetic Acid | 100% | 20 Â°C | |
| Aceton | â€” | 20 Â°C | |
| Aceton | 100% | 20 Â°C | |
| Acronal-dispersioner | â€” | 20 Â°C | |
| Akrylonitril | â€” | 20 Â°C | |
| Allylacetat | â€” | 20 Â°C | |
| Allylalkohol | 96% | 20 Â°C | |
| Allylklorid | â€” | 20 Â°C | |
| Aluminiumfluorid | Conc. | 20 Â°C | |
| Aluminiumhydroxid | â€” | 20 Â°C | |
| Aluminiumklorid, fast | â€” | 20 Â°C | |
| Aluminiumklorid, vattenl. | any | 20 Â°C | |
| Aluminiummetafosfat | â€” | 20 Â°C | |
| Aluminiumsulfat, fast | â€” | 20 Â°C | |
| Aluminiumsulfat, vattenl. mÃ¤ttad | â€” | 20 Â°C | |
| Ammoniak | concentrated | 20 Â°C | |
| Ammoniak, flytande | â€” | 20 Â°C | |
| Ammoniak, gas | â€” | 20 Â°C | |
| Ammonium Chloride | â€” | 20 Â°C | |
| Amyl Alcohol | â€” | 20 Â°C | |
| Anilin | any | 20 Â°C | |
| Anisol | â€” | 20 Â°C | |
| Apple Juice | â€” | 20 Â°C | |
| Bensen | â€” | 20 Â°C | |

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| Bensen | technically grade | 20 Â°C | 🔴 |
| Bensoesyra, vattenl. | any | 20 Â°C | 🟢 |
| Bensylalkohol | â€” | 20 Â°C | 🟢 |
| Benzaldehyd, vattenl. | any | 20 Â°C | 🟢 |
| Bitumen | â€” | 20 Â°C | 🟢 |
| Bleaching Solution | 12.5 cl | 20 Â°C | 🟡 |
| BlÃ¤ck | â€” | 20 Â°C | 🟢 |
| Boric Acid | 100% | 20 Â°C | 🟢 |
| Brake Fluid | â€” | 20 Â°C | 🟢 |
| Brom, flytande | 100% | 20 Â°C | 🔴 |
| BromvÃ¤tesyra, vattenl. | 50% | 20 Â°C | 🟢 |
| BrÃ¤nsle (aromatfritt) | â€” | 20 Â°C | 🟢 |
| Butanol, vattenl. | any | 20 Â°C | 🟢 |
| Butyl Acetate | â€” | 20 Â°C | 🟢 |
| Calcium Chloride | â€” | 20 Â°C | 🟢 |
| Calcium carbonate | â€” | 20 Â°C | 🟢 |
| Calcium carbonate | â€” | 20 Â°C | 🟢 |
| Carbon Disulfide | 100% | 20 Â°C | 🟡 |
| Carbon Tetrachloride | â€” | 20 Â°C | 🟡 |
| Caustic soda | any | 20 Â°C | 🟢 |
| Cider | â€” | 20 Â°C | 🟢 |
| Citric Acid | 10% | 20 Â°C | 🟢 |
| Citrusfruktjuicer | â€” | 20 Â°C | 🟢 |
| Cyklohexan | â€” | 20 Â°C | 🟢 |
| Cyklohexanol | â€” | 20 Â°C | 🟢 |
| Cyklohexanon | 100% | 20 Â°C | 🟢 |
| Cyklohexanon | â€” | 20 Â°C | 🟢 |
| Cyklohexen | 100% | 20 Â°C | 🟢 |
| Dibutyleter | â€” | 20 Â°C | 🟢 |
| Dibutylftalat | â€” | 20 Â°C | 🟢 |
| Diesel Fuel | â€” | 20 Â°C | 🟢 |
| Diesel fuel | â€” | 20 Â°C | 🟢 |
| Diethylene Oxide | â€” | 20 Â°C | 🟢 |
| Diglykolsyra, vattenl. | 30% | 20 Â°C | 🟢 |

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| Dikloretan | â€” | 20 Â°C | 🟡 |
| DiklorÃ¤ttiksyra | â€” | 20 Â°C | 🟢 |
| Dimethyl formamide | â€” | 20 Â°C | 🟢 |
| Dimetylamin | â€” | 20 Â°C | 🟢 |
| Dioxan | â€” | 20 Â°C | 🟢 |
| Diskmedel | â€” | 20 Â°C | 🟢 |
| Eldningsolja | â€” | 20 Â°C | 🟢 |
| Ethanol | 10% | 100 Â°C | 🟢 |
| Ethanol | 10% | 100 Â°C | 🟢 |
| Ethanol | 10% | 100 Â°C | 🟢 |
| Ethanol | 10% v/v | 20 Â°C | 🟢 |
| Ethyl Acetate | 100% | 20 Â°C | 🟢 |
| Ethyl Alcohol | 96% | 20 Â°C | 🟢 |
| Ethylene Chloride | 100% | 20 Â°C | 🟢 |
| Etylacetat | â€” | 20 Â°C | 🟢 |
| Etylenalkohol | 96% | 20 Â°C | 🟢 |
| Etylendiamin | â€” | 20 Â°C | 🟢 |
| Etylenglykol | â€” | 20 Â°C | 🟢 |
| Etylenklorid | â€” | 20 Â°C | 🔴 |
| Fenol | â€” | 20 Â°C | 🟢 |
| Fenol (vattenl.) | â‰ˆ9% | 20 Â°C | 🟢 |
| Ferrous (III) nitrate, aqueous saturated | â€” | 20 Â°C | 🟢 |
| Ferrous (III) sulfate, aqueous saturated | â€” | 20 Â°C | 🟢 |
| Food Oil | â€” | 20 Â°C | 🟢 |
| Formaldehyd (vattenl.) | 40% | 20 Â°C | 🟢 |
| Formaldehyd, vattenl. | â‰¤40% | 20 Â°C | 🟢 |
| Formic Acid | 10% | 20 Â°C | 🟢 |
| Fosforsyra, vattenl. | 80% L 95% | 20 Â°C | 🟢 |
| Fosforsyra, vattenl. | 50% | 20 Â°C | 🟢 |
| Fosfortriklorid | â€” | 20 Â°C | 🔴 |
| Fotogen | â€” | 20 Â°C | 🟢 |
| Frigen 12 (Freon 12) | 100% | 20 Â°C | 🔴 |
| Frost Protection Agent | â€” | 20 Â°C | 🟢 |
| Fruktjuicer | any | 20 Â°C | 🟢 |

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| Ftalsyra, vattenl. | 50% | 20 Â°C | 🟢 |
| Furfurol | â€” | 20 Â°C | 🟢 |
| Garvsyra (tannin), vattenl. | 10% | 20 Â°C | 🟢 |
| Glycerin | 100% | 20 Â°C | 🟢 |
| Glycerin, aqueous | any | 20 Â°C | 🟢 |
| Glykol | 100% | 20 Â°C | 🟢 |
| Glykol, aqueous | as supplied | 20 Â°C | 🟢 |
| Glysantin | â€” | 20 Â°C | 🟢 |
| Havsvatten | â€” | 20 Â°C | 🟢 |
| Heating Oil | â€” | 20 Â°C | 🟢 |
| Heptan | â€” | 20 Â°C | 🟢 |
| Heptan | 100% | 20 Â°C | 🟢 |
| Hexan | â€” | 20 Â°C | 🟢 |
| Honung | â€” | 20 Â°C | 🟢 |
| Hydrochloric Acid | 10% | 20 Â°C | 🟢 |
| Hydrochloric Acid (concentrated) | concentrated | 20 Â°C | 🟢 |
| Hydrofluoric Acid | 40% | 20 Â°C | 🟢 |
| Hydrogen Peroxide | 10% | 20 Â°C | 🟢 |
| Hydrogen Sulfide (aqueous solution) | â€” | 20 Â°C | 🟢 |
| Isooktan | â€” | 20 Â°C | 🟢 |
| Isopropanol | â€” | 20 Â°C | 🟢 |
| Isopropyl Alcohol | 100% | 20 Â°C | 🟢 |
| Isopropyleter | â€” | 20 Â°C | 🟡 |
| Jod i kaliumjodidlÃ¶sning | 3% iodine | 20 Â°C | 🟢 |
| JÃ¤rn(II)klorid, vattenl. mÃ¤ttad | â€” | 20 Â°C | 🟢 |
| JÃ¤rn(II)sulfat, vattenl. mÃ¤ttad | â€” | 20 Â°C | 🟢 |
| JÃ¤rn(III)klorid, vattenl. | any | 20 Â°C | 🟢 |
| JÃ¤rn(III)klorid, vattenl. mÃ¤ttad | â€” | 20 Â°C | 🟢 |
| JÃ¤rn(III)nitrat, vattenl. mÃ¤ttad | â€” | 20 Â°C | 🟢 |
| JÃ¤rn(III)sulfat, vattenl. mÃ¤ttad | â€” | 20 Â°C | 🟢 |
| Kalciumhypoklorit, vattenl. suspension | any | 20 Â°C | 🟢 |
| Kamfer | â€” | 20 Â°C | 🟡 |
| Klor (gas) | 100% | 20 Â°C | 🟡 |
| Klor, flytande | â€” | 20 Â°C | 🔴 |
| Klorbensen | â€” | 20 Â°C | 🟡 |

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| Klorbensen | 100% | 20 Â°C | 🟡 |
| Kloroform | technically grade | 20 Â°C | 🟡 |
| Kloroform | â€” | 20 Â°C | 🟡 |
| KlorÃ¤ttiksyra, vattenl. | â‰¤85% | 20 Â°C | 🟢 |
| Kokosolja | â€” | 20 Â°C | 🟢 |
| Koldisulfid | â€” | 20 Â°C | 🔴 |
| Kresol | 100% | 20 Â°C | 🟢 |
| Kresol | â€” | 20 Â°C | 🟢 |
| Kromsyra-svavelsyra | â€” | 20 Â°C | 🔴 |
| Kungsvatten | â€” | 20 Â°C | 🔴 |
| Kvicksilver | â€” | 20 Â°C | 🟢 |
| Linolja | technically grade | 20 Â°C | 🟢 |
| Linseed Oil | â€” | 20 Â°C | 🟢 |
| Litiumbromid | â€” | 20 Â°C | 🟢 |
| Magnesium stearate | â€” | 20 Â°C | 🟢 |
| Magnesium stearate | â€” | 20 Â°C | 🟢 |
| Maleinsyra, vattenl. | any | 20 Â°C | 🟢 |
| Melass | â€” | 20 Â°C | 🟢 |
| Mentol | â€” | 20 Â°C | 🟢 |
| Merkurokrom | â€” | 20 Â°C | 🟢 |
| Metanol | technically grade | 20 Â°C | 🟢 |
| Methyl Alcohol | 100% | 20 Â°C | 🟢 |
| Methyl Ethyl Ketone (MEK) | 100% | 20 Â°C | 🔴 |
| Methyl ethyl ketone | technically grade | 20 Â°C | 🟢 |
| Methylene Chloride | 100% | 20 Â°C | 🟡 |
| Metylklorid | gaseous, technically grade | 20 Â°C | 🔴 |
| Mineral Oil (aromatic free) | â€” | 20 Â°C | 🟢 |
| MjÃ¶lk | â€” | 20 Â°C | 🟢 |
| MjÃ¶lk | â€” | 20 Â°C | 🟢 |
| Motor oil (heavy duty oil) without additives | â€” | 20 Â°C | 🟢 |
| Myrsyra, vattenl. | 85% | 20 Â°C | 🟢 |
| Nafta | â€” | 20 Â°C | 🟢 |
| Naftalen | â€” | 20 Â°C | 🟢 |
| Natriumbromid | â€” | 20 Â°C | 🟢 |

| Kemikalie | Koncentration | Temp. | BestÃ□ndighet |
|---|---|---|---|
| Natriumhydroxid, fast | â€” | 20 Â°C | 🟢 |
| Natriumhydroxid, vattenl. | any | 20 Â°C | 🟢 |
| Nitric Acid | 10% | 20 Â°C | 🟢 |
| Nitric Acid (50%) | 50% | 20 Â°C | 🟡 |
| Nitrobensen | â€” | 20 Â°C | 🟢 |
| Nitrobensen | â€” | 20 Â°C | 🟢 |
| Oils, ethereal | â€” | 20 Â°C | 🟡 |
| Oleum | any | 20 Â°C | 🔴 |
| Olive oil | â€” | 100 Â°C | 🟢 |
| Olive oil | â€” | 20 Â°C | 🟢 |
| Olive oil | â€” | 100 Â°C | 🟢 |
| Olive oil | â€” | 100 Â°C | 🟢 |
| Oljesyra | â€” | 20 Â°C | 🟢 |
| Oljor, vegetabiliska och animaliska | â€” | 20 Â°C | 🟢 |
| Oxalic Acid | â€” | 20 Â°C | 🟢 |
| Oxalsyra, vattenl. | any | 20 Â°C | 🟢 |
| Ozon | 50 ppm | 20 Â°C | 🟡 |
| Ozone Gas | â‰¤0.5 ppm | 20 Â°C | 🟢 |
| Paraffine Oil | 100% | 20 Â°C | 🟢 |
| Perkloretylen | â€” | 20 Â°C | 🟡 |
| Perklorsyra, vattenl. | 20% | 20 Â°C | 🟢 |
| Perklorsyra, vattenl. | 70% | 20 Â°C | 🟢 |
| Perklorsyra, vattenl. | 50% | 20 Â°C | 🟢 |
| Petroleum | â€” | 20 Â°C | 🟢 |
| Petroleum | 100% | 20 Â°C | 🟢 |
| Petroleum Ether | 100% | 20 Â°C | 🟢 |
| Petroleumeter | â€” | 20 Â°C | 🟢 |
| Phosphoric Acid | 50% | 20 Â°C | 🟢 |
| Photographic developers | â€” | 20 Â°C | 🟢 |
| Photographic emulsions | as supplied | 20 Â°C | 🟢 |
| Photographic fixing baths | as supplied | 20 Â°C | 🟢 |
| Polyesterhartser | â€” | 20 Â°C | 🔴 |
| Potassium Hydroxide liquor | 50% | 20 Â°C | 🟢 |
| Premium Fuel | â€” | 20 Â°C | 🟢 |

| Kemikalie | Koncentration | Temp. | BestÃ□ndighet |
|---|---|---|---|
| Propionsyra, vattenl. | any | 20 Â°C | 🟢 |
| Propyl Alcohol | â€” | 20 Â°C | 🟢 |
| Pyridin | â€” | 20 Â°C | 🟢 |
| Pyridin | â€” | 20 Â°C | 🟢 |
| Salpetersyra, vattenl. | 25% | 20 Â°C | 🟢 |
| Salpetersyra, vattenl. | 50% | 20 Â°C | 🟡 |
| Saltsyra, vattenl. | any | 20 Â°C | 🟢 |
| Silicon dioxide | â€” | 20 Â°C | 🟢 |
| Silicon dioxide | â€” | 20 Â°C | 🟢 |
| Silicone Oil | â€” | 20 Â°C | 🟢 |
| Silikonolja | technically grade | 20 Â°C | 🟢 |
| SmÃ¶r | â€” | 20 Â°C | 🟢 |
| Sockersirap | â€” | 20 Â°C | 🟢 |
| Sodium Carbonate (aqueous) | â€” | 20 Â°C | 🟢 |
| Sodium Chloride (aqueous) | â€” | 20 Â°C | 🟢 |
| Sodium Hydrogen Sulfite | â€” | 20 Â°C | 🟢 |
| Sodium Hydroxide liquor | 15% | 20 Â°C | 🟢 |
| Sodium Hydroxide liquor (60%) | 60% | 20 Â°C | 🟢 |
| Sodium Nitrate (aqueous) | â€” | 20 Â°C | 🟢 |
| Sodium Thiosulfate | â€” | 20 Â°C | 🟢 |
| Sodium borate | â€” | 20 Â°C | 🟢 |
| Stearinsyra | â€” | 20 Â°C | 🟢 |
| Sulfuric Acid | 96% | 20 Â°C | 🟡 |
| Svavelsyra, vattenl. | 80% | 20 Â°C | 🟢 |
| Svavelsyra, vattenl. | 70% | 20 Â°C | 🟢 |
| Svavelsyra, vattenl. | 98% | 20 Â°C | 🟢 |
| Svavelsyra, vattenl. | â‰¤50% | 20 Â°C | 🟢 |
| Sylt | â€” | 20 Â°C | 🟢 |
| Syre | â€” | 20 Â°C | 🟢 |
| Talg | technically grade | 20 Â°C | 🟢 |
| Tenn(II)klorid, vattenl. | any | 20 Â°C | 🟢 |
| Tenn(IV)klorid, vattenl. | saturated | 20 Â°C | 🟢 |
| Terpentinolja | technically grade | 20 Â°C | 🟢 |
| Tetrahydrofuran | technically grade | 20 Â°C | 🔴 |
| Tetrahydrofuran (THF) | 100% | 20 Â°C | 🟡 |

| Kemikalie | Koncentration | Temp. | BestÃ□ndighet |
|---|---|---|---|
| Tiofen | â€” | 20 Â°C | 🔴 |
| Tionylklorid | â€” | 20 Â°C | 🔴 |
| Titanium dioxide | â€” | 20 Â°C | 🟢 |
| Titanium dioxide | â€” | 20 Â°C | 🟢 |
| Toluen | technically grade | 20 Â°C | 🔴 |
| Toluen | 100% | 20 Â°C | 🟡 |
| Torskleversolja | â€” | 20 Â°C | 🟢 |
| Transformatorolja (isolerolja) | technically grade | 20 Â°C | 🟢 |
| Transformer Oil | â€” | 20 Â°C | 🟢 |
| Trichloracetic acid | technically grade | 20 Â°C | 🟢 |
| Trietanolamin | â€” | 20 Â°C | 🟢 |
| Trietanolamin | â€” | 20 Â°C | 🟢 |
| Trikloreten | 100% | 20 Â°C | 🟢 |
| Trikloreten | technically grade | 20 Â°C | 🔴 |
| Urea, aqueous | â‰¤33% | 20 Â°C | 🟢 |
| Vaselin | technically grade | 20 Â°C | 🟢 |
| Vatten | â€” | 20 Â°C | 🟢 |
| Vatten, destillerat | â€” | 20 Â°C | 🟢 |
| Vin | â€” | 20 Â°C | 🟢 |
| Washing up liquids | usual | 20 Â°C | 🟢 |
| Xylen | â€” | 20 Â°C | 🔴 |
| Xylen | â€” | 20 Â°C | 🔴 |
| Zinkslam | â€” | 20 Â°C | 🟢 |
| Ã„ttika (standard) | 5-10% | 20 Â°C | 🟢 |
| Ã„ttiksyra | 3% | 100 Â°C | 🟢 |
| Ã„ttiksyra | 3% | 100 Â°C | 🟢 |
| Ã„ttiksyra | 100% | 20 Â°C | 🟢 |
| Ã„ttiksyra | 3% w/w | 20 Â°C | 🟢 |
| Ã„ttiksyra | 3% | 100 Â°C | 🟢 |
| Ã„ttiksyra, vattenl. | 70% | 20 Â°C | 🟢 |
| Ã„ttiksyraanhydrid | â€” | 20 Â°C | 🟢 |
| Ã–l | â€” | 20 Â°C | 🟢 |


*This document is for informational purposes only. Specifications may change without notice. Generated 2026-03-18*