

# PEEK 25/18x3000 mm beige

Artikelnummer: P1500160

## Kemisk beständighet

**A** Utmärkt   **B** God   **C** Begränsad   **D** Ej rekommenderad

| KEMIKALE                         | BETYG     | KONCENTRATION | TEMPERATUR |
|----------------------------------|-----------|---------------|------------|
| 1,4-Dioxan                       | resistant | 100%          |            |
| 2-Hydroxipropionsyra (mjölksyra) | resistant | 90%           |            |
| Aceton                           | resistant | 100%          |            |
| Ammoniak                         | resistant |               |            |
| Ammoniumklorid                   | resistant |               |            |
| Amylalkohol                      | resistant |               |            |
| Bensen                           | resistant |               |            |
| Bensin (premium)                 | resistant |               |            |
| Borsyra                          | resistant | 100%          |            |
| Bromsvätska                      | resistant |               |            |
| Bränsle, aromatfritt             | resistant |               |            |
| Butylacetat                      | resistant |               |            |
| Citronsyra                       | resistant | 10%           |            |
| Cyklohexanon                     | resistant | 100%          |            |
| Cyklohexen                       | resistant | 100%          |            |
| Diesel                           | resistant |               |            |
| Dietylenoxid                     | resistant |               |            |
| Eldningsolja                     | resistant |               |            |
| Etylacetat                       | resistant | 100%          |            |
| Etylalkohol (etanol)             | resistant | 96%           |            |
| Etylenklorid                     | resistant | 100%          |            |
| Fenol (vattenl.)                 | resistant | 9%            |            |

| KEMIKALE                           | BETYG               | KONCENTRATION | TEMPERATUR |
|------------------------------------|---------------------|---------------|------------|
| Fluorvätesyra                      | not_resistant       | 40%           |            |
| Formaldehyd (vattenl.)             | resistant           | 40%           |            |
| Fosforsyra                         | resistant           | 50%           |            |
| Frostskyddsmedel                   | resistant           |               |            |
| Glycerin                           | resistant           | 100%          |            |
| Glykol                             | resistant           | 100%          |            |
| Heptan                             | resistant           | 100%          |            |
| Isopropylalkohol                   | resistant           | 100%          |            |
| Kalciumklorid                      | resistant           |               |            |
| Kaliumhydroxidlösning              | resistant           | 50%           |            |
| Klor (gas)                         | resistant           | 100%          |            |
| Klorbensen                         | resistant           | 100%          |            |
| Kloroform                          | resistant           |               |            |
| Koltetraklorid                     | resistant           |               |            |
| Linolja                            | resistant           |               |            |
| Matolja                            | resistant           |               |            |
| Merkurokrom                        | partially_resistant |               |            |
| Metylalkohol (metanol)             | resistant           | 100%          |            |
| Metylenklorid                      | resistant           | 100%          |            |
| Metyletylketon (MEK)               | resistant           | 100%          |            |
| Mineraloljor (aromatfria)          | resistant           |               |            |
| Mjök                               | resistant           |               |            |
| Myrsyra                            | partially_resistant | 10%           |            |
| Natriumhydroxidlösning (natronlut) | resistant           | 60%           |            |
| Natriumhydroxidlösning (natronlut) | resistant           | 15%           |            |
| Natriumkarbonat (vattenl.)         | resistant           |               |            |
| Natriumklorid (vattenl.)           | resistant           |               |            |
| Natriumnitrat (vattenl.)           | resistant           |               |            |
| Natriumtiosulfat                   | resistant           |               |            |
| Natriumvätesulfit                  | resistant           |               |            |
| Nitrobensen                        | resistant           |               |            |

| KEMIKALE              | BETYG               | KONCENTRATION | TEMPERATUR |
|-----------------------|---------------------|---------------|------------|
| Oxalsyra              | resistant           |               |            |
| Ozon (gas)            | resistant           |               |            |
| Paraffinolja          | resistant           | 100%          |            |
| Perkloretylen         | resistant           |               |            |
| Petroleum             | resistant           | 100%          |            |
| Petroleometer         | resistant           | 100%          |            |
| Propylalkohol         | resistant           |               |            |
| Pyridin               | resistant           |               |            |
| Salpetersyra          | resistant           | 50%           |            |
| Salpetersyra          | resistant           | 10%           |            |
| Saltsyra              | resistant           | 10%           |            |
| Saltsyra (konc.)      | partially_resistant |               |            |
| Silikonolja           | resistant           |               |            |
| Svavelsyra            | not_resistant       | 96%           |            |
| Tetrahydrofuran (THF) | resistant           | 100%          |            |
| Toluen                | resistant           | 100%          |            |
| Transformatorolja     | resistant           |               |            |
| Trikloreten           | resistant           | 100%          |            |
| Vatten                | resistant           |               |            |
| Väteperoxid           | resistant           | 10%           |            |
| Vätesulfid (vattenl.) | resistant           |               |            |
| Xylen                 | resistant           |               |            |
| Äppeljuice            | resistant           |               |            |
| Ättika (standard)     | resistant           | 5-10%         |            |
| Ättiksyra             | resistant           | 100%          |            |